



ABS 1000x610x25 mm natural

Artikelnr P1000115

Best ndig Delvis best ndig Ej best ndig

Kemikalie	Koncentration	Temp.	Best�ndighet
1,4-Dioxane	100	20 �C	Ej best�ndig
2-Hydroxypropionic acid (lactic acid)	90	20 �C	Best�ndig
Acetic acid	100	20 �C	Ej best�ndig
Acetone	100	20 �C	Ej best�ndig
Ammonia	��	20 �C	Best�ndig
Ammonium chloride	��	20 �C	Best�ndig
Amyl alcohol	��	20 �C	Best�ndig
Apple juice	��	20 �C	Best�ndig
Benzene	��	20 �C	Ej best�ndig
Brake fluid	��	20 �C	Ej best�ndig
Butyl acetate	��	20 �C	Ej best�ndig
Calcium chloride	��	20 �C	Best�ndig
Carbon disulphide	100	20 �C	Ej best�ndig
Carbon tetrachloride	��	20 �C	Ej best�ndig
Chlorine gas	100	20 �C	Ej best�ndig
Chlorobenzene	100	20 �C	Ej best�ndig
Chloroform	��	20 �C	Ej best�ndig
Citric acid	10	20 �C	Best�ndig
Cresol	��	20 �C	Ej best�ndig
Cyclohexanone	100	20 �C	Ej best�ndig
Cyclohexene	100	20 �C	Best�ndig
Diesel	��	20 �C	Best�ndig
Ethyl acetate	100	20 �C	Ej best�ndig
Ethyl alcohol (ethanol)	96	20 �C	Ej best�ndig
Ethylene chloride	100	20 �C	Ej best�ndig
Food oil	��	20 �C	Best�ndig
Formaldehyde, aqueous	40	20 �C	Best�ndig

Kemikalie	Koncentration	Temp.	Best�ndighet
Formic acid	10	20 ��C	�
Frost protection agent	����	20 ��C	�
Fuel oil	����	20 ��C	�
Fuel, aromatic free	����	20 ��C	�
Glycerine	100	20 ��C	�
Glycol	100	20 ��C	�
Heptane	100	20 ��C	�
Hydrochloric acid	10	20 ��C	�
Hydrochloric acid (concentrated)	����	20 ��C	�
Hydrofluoric acid	40	20 ��C	��
Hydrogen peroxide	10	20 ��C	�
Hydrogen sulfide, aqueous	����	20 ��C	�
Isopropyl alcohol	100	20 ��C	��
Linseed oil	����	20 ��C	�
Mercurochrome	����	20 ��C	��
Methyl alcohol (methanol)	100	20 ��C	��
Methyl ethyl ketone (MEK)	100	20 ��C	��
Methylene chloride	100	20 ��C	��
Milk	����	20 ��C	�
Nitric acid	10	20 ��C	�
Nitric acid	50	20 ��C	�
Nitrobenzene	����	20 ��C	��
Oxalic acid	����	20 ��C	�
Ozone (gas)	����	20 ��C	�
Paraffin oil	100	20 ��C	�
Perchloroethylene	����	20 ��C	��
Petroleum	100	20 ��C	��
Petroleum ether	100	20 ��C	��
Phenol, aqueous	9	20 ��C	��
Phosphoric acid	50	20 ��C	�
Potassium hydroxide solution	50	20 ��C	�
Premium fuel	����	20 ��C	��
Propyl alcohol	����	20 ��C	�
Pyridine	����	20 ��C	��
Silicone oil	����	20 ��C	�

