



PA6 E 3000x500x70 mm svart

Artikelnr P1001056

1. Tekniskt datablad

Egenskap	VÄrde	Enhet	Standard
Density	1.14	g/cm ³	ISO 1183
Tensile Strength	70	MPa	DIN EN ISO 527
Modulus of elasticity (tensile)	3250	MPa	ISO 527-2
Breakdown Voltage	75	MPa	ISO 527-2
Break Elongation	40	%	ISO 527-2
Melting point	220	°C	ISO 3146
Maximal operating temperature (short-term)	160	°C	
Maximum Operating Temperature	90.5	°C	
Minimum temperature	-36	°C	
Heat deflection temperature (HDT/A)	70	°C	ISO 75-2
Heat deflection temperature (HDT/B)	140	°C	ISO 75-2
Vicat softening temperature (VST/B/50)	190	°C	ISO 306
Dielectric Strength	25	kV/mm	IEC 60243-1
Volume Resistivity	10 ¹¹ Å²	Î©Å·cm	IEC 60093
Dielectric Constant (1 MHz)	3.7	-	IEC 60250
Dielectric Constant (100 Hz)	3.9	-	IEC 60250
Dielectric loss factor (1 MHz)	0.0	-	IEC 60250
Dielectric loss factor (100 Hz)	0.0	-	IEC 60250
Flammability Classification (UL 94)	3		UL 94
Flexural Strength	76	MPa	ISO 527-2
Thermal Conductivity	0.28	W/(mÅ·K)	DIN 52612
Surface Resistivity	10 ¹¹ Å³	Î©	IEC 60093
Comparative Tracking Index (CTI)	600	V	IEC 60112
Water absorption to saturation	2.5	%	ISO 62
Water Absorption to Saturation	9	%	ISO 62
Notched impact strength (Charpy)	5.5	kJ/mÅ²	ISO 179/1eA
Thermal Expansion Coefficient	0.9	10 ⁻⁶ Å/K	ISO 11359

Egenskap	V�rde	Enhet	Standard
Hardness Shore D	82	� Shore D	DIN EN ISO 868
Ball pressure hardness	150	MPa	ISO 2039-1

2. Kemisk best ndighet

● Best ndig ● Delvis best ndig ● Ej best ndig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100	●
2-Hydroxypropionic Acid	90	●
Acetic Acid	100	●
Acetone	100	●
Ammonia	conc.	●
Ammonium Chloride	��	●
Amyl Alcohol	��	●
Apple Juice	��	●
Benzene	��	●
Bleaching Solution	12.5 cl	●
Boric Acid	100	●
Brake Fluid	��	●
Butyl Acetate	��	●
Calcium Chloride	��	●
Carbon Disulfide	100	●
Carbon Tetrachloride	��	●
Chlorine (gas)	100	●
Chlorobenzene	100	●
Chloroform	��	●
Citric Acid	10	●
Cresol	��	●
Cyclohexanone	100	●
Cyclohexene	100	●
Diesel Fuel	��	●
Diethylene Oxide	��	●
Ethyl Acetate	100	●
Ethyl Alcohol	96	●

Kemikalie	Konc.	Resultat
Ethylene Chloride	100	
Food Oil	â€”	
Formaldehyde (aqueous)	40	
Formic Acid	10	
Frost Protection Agent	â€”	
Fuel (aromatic free)	â€”	
Glycerine	100	
Glycol	100	
Heating Oil	â€”	
Heptane	100	
Hydrochloric Acid	10	
Hydrochloric Acid (concentrated)	conc.	
Hydrofluoric Acid	40	
Hydrogen Peroxide	10	
Hydrogen Sulfide (aqueous)	â€”	
Isopropyl Alcohol	100	
Linseed Oil	â€”	
Mercurochrome	â€”	
Methyl Alcohol	100	
Methyl Ethyl Ketone (MEK)	100	
Methylene Chloride	100	
Milk	â€”	
Mineral Oils (aromatic free)	â€”	
Nitric Acid	10	
Nitric Acid	50	
Nitrobenzene	â€”	
Oxalic Acid	â€”	
Ozone Gas	â‰‰ 0.5 ppm	
Paraffine Oil	100	
Perchloroethylene	â€”	
Petroleum	100	
Petroleum Ether	100	
Phenol (aqueous)	ca. 9	
Phosphoric Acid	50	
Potassium Hydroxide liquor	50	

Kemikalie	Konc.	Resultat
Premium Fuel	â€”	
Propyl Alcohol	â€”	
Pyridine	â€”	
Silicone Oil	â€”	
Sodium Carbonate (aqueous)	â€”	
Sodium Chloride (aqueous)	â€”	
Sodium Hydrogen Sulfite	â€”	
Sodium Hydroxide liquor	60	
Sodium Hydroxide liquor	15	
Sodium Nitrate (aqueous)	â€”	
Sodium Thiosulfate	â€”	
Sulfuric Acid	96	
Tetrahydrofuran (THF)	100	
Toluene	100	
Transformer Oil	â€”	
Trichloroethylene	100	
Vinegar (standard)	5 - 10	
Water	â€”	
Xylene	â€”	