



## PA6.6 1000x500x30 mm natur

Artikelnr P1002114

Material PA

### Tekniska egenskaper

#### Density & Weight

| Egenskap | Värde | Enhet             | Provningsstandard |
|----------|-------|-------------------|-------------------|
| Density  | 1.14  | g/cm <sup>3</sup> | ISO 1183          |

#### Tensile Properties

| Egenskap                        | Värde | Enhet | Provningsstandard |
|---------------------------------|-------|-------|-------------------|
| Tensile Strength                | 85    | MPa   | DIN EN ISO 527    |
| Modulus of elasticity (tensile) | 3100  | MPa   | ISO 527-2         |
| Break Elongation                | 40    | %     | ISO 527-2         |

#### Temperature Limits

| Egenskap                                   | Värde | Enhet | Provningsstandard |
|--------------------------------------------|-------|-------|-------------------|
| Melting point                              | 260   | °C    | ISO 3146          |
| Maximal operating temperature (short-term) | 175   | °C    |                   |
| Maximum Operating Temperature              | 95    | °C    |                   |
| Minimum temperature                        | -30   | °C    |                   |
| Heat deflection temperature (HDT/A)        | 85    | °C    | ISO 75-2          |

#### Insulation Properties

| Egenskap            | Värde            | Enhet | Provningsstandard |
|---------------------|------------------|-------|-------------------|
| Dielectric Strength | 27               | kV/mm | IEC 60243-1       |
| Volume Resistivity  | 10 <sup>14</sup> | Ω·cm  | IEC 60093         |

| Egenskap                        | Värde | Enhet | Provningsstandard |
|---------------------------------|-------|-------|-------------------|
| Dielectric Constant (1 MHz)     | 3.55  | -     | IEC 60250         |
| Dielectric Constant (100 Hz)    | 3.8   | -     | IEC 60250         |
| Dielectric loss factor (1 MHz)  | 0.02  | -     | IEC 60250         |
| Dielectric loss factor (100 Hz) | 0.0   | -     | IEC 60250         |

Flexural Properties

| Egenskap          | Värde | Enhet | Provningsstandard |
|-------------------|-------|-------|-------------------|
| Flexural Strength | 998.3 | MPa   | ISO 178           |

Thermal Conductivity

| Egenskap             | Värde | Enhet   | Provningsstandard |
|----------------------|-------|---------|-------------------|
| Thermal Conductivity | 0.28  | W/(m·K) | DIN 52612         |

Static spread

| Egenskap                         | Värde            | Enhet | Provningsstandard |
|----------------------------------|------------------|-------|-------------------|
| Surface Resistivity              | 10 <sup>13</sup> | Ω     | IEC 60093         |
| Comparative Tracking Index (CTI) | 600              | V     | IEC 60112         |

Moisture Absorption

| Egenskap                       | Värde | Enhet | Provningsstandard |
|--------------------------------|-------|-------|-------------------|
| Water absorption to saturation | 2.4   | %     | ISO 62            |
| Water Absorption to Saturation | 8     | %     | ISO 62            |

Impact Resistance

| Egenskap                         | Värde | Enhet | Provningsstandard |
|----------------------------------|-------|-------|-------------------|
| Notched impact strength (Charpy) | 6     | kJ/m² | ISO 179/1eA       |
| Impact Resistance (Charpy)       | 50    | kJ/m² | ISO 179           |

Thermal Expansion

| Egenskap                      | Värde | Enhet               | Provningsstandard |
|-------------------------------|-------|---------------------|-------------------|
| Thermal Expansion Coefficient | 0.8   | 10 <sup>-4</sup> /K | ISO 11359         |

Hardness

| Egenskap               | Värde | Enhet     | Provningsstandard |
|------------------------|-------|-----------|-------------------|
| Hardness Shore D       | 83    | ° Shore D | DIN EN ISO 868    |
| Ball pressure hardness | 174   | MPa       | ISO 2039-1        |

# Godkännanden

- REACH
- RoHS