

PC 2050x1250x1,5 mm transparent

Artikelnr P1200153

1. Tekniskt datablad

| Egenskap | Värde | Enhet | Standard |
|--|----------------------|---------------------|-------------|
| Density | 1.2 | g/cm ³ | ISO 1183 |
| Tensile Strength | 75 | MPa | ISO 527 |
| Modulus of elasticity (tensile) | 2400 | MPa | ISO 527-2 |
| Breakdown Voltage | 60 | MPa | |
| Break Elongation | 50 | % | ISO 527-2 |
| Melting point | 160 | °C | ISO 3146 |
| Maximal operating temperature (short-term) | 119 | °C | UL746B |
| Maximum Operating Temperature | 113.75 | °C | |
| Minimum temperature | -54 | °C | UL746B |
| Heat deflection temperature (HDT/A) | 130 | °C | ISO 75-2 |
| Heat deflection temperature (HDT/B) | 140 | °C | ISO 75 |
| Vicat softening temperature (VST/B/50) | 150 | °C | ISO 306 |
| Dielectric Strength | 29 | kV/mm | IEC 60243-1 |
| Volume Resistivity | 10 ¹⁴ Ω·m | Ω·m | IEC 60093 |
| Dielectric Constant (1 MHz) | 2.98 | - | IEC 60250 |
| Dielectric Constant (100 Hz) | 3 | - | IEC 60250 |
| Dielectric loss factor (1 MHz) | 0.0 | - | IEC 60250 |
| Dielectric loss factor (100 Hz) | 0.0 | - | IEC 60250 |
| Flammability Classification (UL 94) | 0 | | UL 94 |
| Flexural Strength | 2400 | MPa | ISO 178 |
| Thermal Conductivity | 0.21 | W/(m·K) | DIN 52612 |
| Surface Resistivity | 10 ¹⁴ Ω·m | Ω | IEC 60093 |
| Comparative Tracking Index (CTI) | 279.2 | V | IEC 60112 |
| Water absorption to saturation | 0.15 | % | ISO 62 |
| Water Absorption to Saturation | 0.35 | % | ISO 62 |
| Notched impact strength (Charpy) | 9 | kJ/m ² | ISO 179/1eA |
| Thermal Expansion Coefficient | 0.65 | 10 ⁻⁶ /K | DIN 11359 |

| Egenskap | V rde | Enhet | Standard |
|------------------------|-------|-----------|------------|
| Hardness Shore D | 85 |   Shore D | ISO 868 |
| Ball pressure hardness | 120 | MPa | ISO 2039-1 |

2. Kemisk best ndighet

● Best ndig
 ● Delvis best ndig
 ● Ej best ndig

| Kemikalie | Konc. | Resultat |
|---------------------------------------|---------|----------|
| 1,4-Dioxane | 100% | ● |
| 2-Hydroxypropionic acid (lactic acid) | 90% | ● |
| Acetic acid | 100% | ● |
| Acetone | 100% | ● |
| Ammonia | conc. | ● |
| Ammonium chloride |    | ● |
| Apple juice |    | ● |
| Benzene |    | ● |
| Bleaching solution | 12.5 cl | ● |
| Boric acid | 100% | ● |
| Butyl acetate |    | ● |
| Calcium chloride |    | ● |
| Carbon disulphide | 100% | ● |
| Carbon tetrachloride |    | ● |
| Chlorine (gas) | 100% | ● |
| Chlorobenzene | 100% | ● |
| Chloroform |    | ● |
| Citric acid | 10% | ● |
| Cresol |    | ● |
| Cyclohexanone | 100% | ● |
| Cyclohexene | 100% | ● |
| Diesel |    | ● |
| Diethylene oxide |    | ● |
| Ethyl acetate | 100% | ● |
| Ethyl alcohol (ethanol) | 96% | ● |
| Ethylene chloride | 100% | ● |
| Food oil |    | ● |
| Formaldehyde, aqueous | 40% | ● |

| Kemikalie | Konc. | Resultat |
|----------------------------------|-------------|----------|
| Formic acid | 10% | ● |
| Frost protection agent | â€” | ● |
| Fuel oil | â€” | ● |
| Fuel, aromatic free | â€” | ● |
| Glycerine | 100% | ● |
| Glycol | 100% | ● |
| Heptane | 100% | ● |
| Hydrochloric acid | 10% | ● |
| Hydrochloric acid (concentrated) | conc. | ● |
| Hydrofluoric acid | 40% | ● |
| Hydrogen peroxide | 10% | ● |
| Hydrogen sulfide, aqueous | â€” | ● |
| Isopropyl alcohol | 100% | ● |
| Linseed oil | â€” | ● |
| Mercurochrome | â€” | ● |
| Methyl alcohol (methanol) | 100% | ● |
| Methyl ethyl ketone (MEK) | 100% | ● |
| Methylene chloride | 100% | ● |
| Milk | â€” | ● |
| Nitric acid (10%) | 10% | ● |
| Nitric acid (50%) | 50% | ● |
| Nitrobenzene | â€” | ● |
| Oxalic acid | â€” | ● |
| Ozone (gas) | â‰ƒ 0.5 ppm | ● |
| Paraffin oil | 100% | ● |
| Perchloroethylene | â€” | ● |
| Petroleum | 100% | ● |
| Petroleum ether | 100% | ● |
| Phenol, aqueous | ca. 9% | ● |
| Phosphoric acid | 50% | ● |
| Potassium hydroxide solution | 50% | ● |
| Premium fuel | â€” | ● |
| Propyl alcohol | â€” | ● |
| Pyridine | â€” | ● |

| Kemikalie | Konc. | Resultat |
|---------------------------------|-------|----------|
| Silicone oil | â€” | ● |
| Sodium carbonate, aqueous | â€” | ● |
| Sodium chloride, aqueous | â€” | ● |
| Sodium hydrogen sulfite | â€” | ● |
| Sodium hydroxide solution (15%) | 15% | ● |
| Sodium hydroxide solution (60%) | 60% | ● |
| Sodium nitrate, aqueous | â€” | ● |
| Sulphuric acid | 96% | ● |
| Tetrahydrofuran (THF) | 100% | ● |
| Toluene | 100% | ● |
| Trichloroethylene | 100% | ● |
| Vinegar, standard | 5-10% | ● |
| Water | â€” | ● |
| Xylene | â€” | ● |