

PE-1000 4000x2000x15 mm natur

Artikelnr P1400553

● Beständig ● Delvis beständig ● Ej beständig

| Kemikalie                             | Koncentration | Temp. | Beständighet |
|---------------------------------------|---------------|-------|--------------|
| 1,4-Dioxane                           | 100           | 20 °C | ●            |
| 2-Hydroxypropionic acid (lactic acid) | 90            | 20 °C | ●            |
| Acetic acid                           | 100           | 20 °C | ●            |
| Acetone                               | 100           | 20 °C | ●            |
| Ammonia                               | -             | 20 °C | ●            |
| Ammonium chloride                     | -             | 20 °C | ●            |
| Amyl alcohol                          | -             | 20 °C | ●            |
| Benzene                               | -             | 20 °C | ●            |
| Boric acid                            | 100           | 20 °C | ●            |
| Brake fluid                           | -             | 20 °C | ●            |
| Butyl acetate                         | -             | 20 °C | ●            |
| Calcium chloride                      | -             | 20 °C | ●            |
| Citric acid                           | 10            | 20 °C | ●            |
| Cresol                                | -             | 20 °C | ●            |
| Cyclohexanone                         | 100           | 20 °C | ●            |
| Cyclohexene                           | 100           | 20 °C | ●            |
| Diesel                                | -             | 20 °C | ●            |
| Ethyl acetate                         | 100           | 20 °C | ●            |
| Ethyl alcohol (ethanol)               | 96            | 20 °C | ●            |
| Food oil                              | -             | 20 °C | ●            |
| Formaldehyde, aqueous                 | 40            | 20 °C | ●            |
| Formic acid                           | 10            | 20 °C | ●            |
| Frost protection agent                | -             | 20 °C | ●            |
| Fuel oil                              | -             | 20 °C | ●            |
| Fuel, aromatic free                   | -             | 20 °C | ●            |
| Glycerine                             | 100           | 20 °C | ●            |

| Kemikalie                                | Koncentration | Temp. | Beständighet |
|------------------------------------------|---------------|-------|--------------|
| Glycol                                   | 100           | 20 °C | ●            |
| Heptane                                  | 100           | 20 °C | ●            |
| Hydrochloric acid                        | 10            | 20 °C | ●            |
| Hydrochloric acid (concentrated)         | -             | 20 °C | ●            |
| Hydrogen peroxide                        | 10            | 20 °C | ●            |
| Isopropyl alcohol                        | 100           | 20 °C | ●            |
| Linseed oil                              | -             | 20 °C | ●            |
| Mercurochrome                            | -             | 20 °C | ●            |
| Methyl alcohol (methanol)                | 100           | 20 °C | ●            |
| Methylene chloride                       | 100           | 20 °C | ●            |
| Milk                                     | -             | 20 °C | ●            |
| Mineral oils, aromatic free              | -             | 20 °C | ●            |
| Nitric acid                              | 50            | 20 °C | ●            |
| Nitric acid                              | 10            | 20 °C | ●            |
| Nitrobenzene                             | -             | 20 °C | ●            |
| Oxalic acid                              | -             | 20 °C | ●            |
| Ozone (gas)                              | ≤ 0.5 ppm     | 20 °C | ●            |
| Paraffin oil                             | 100           | 20 °C | ●            |
| Perchloroethylene                        | -             | 20 °C | ●            |
| Petroleum ether                          | 100           | 20 °C | ●            |
| Phenol, aqueous                          | ca. 9         | 20 °C | ●            |
| Phosphoric acid                          | 50            | 20 °C | ●            |
| Potassium hydroxide solution             | 50            | 20 °C | ●            |
| Premium fuel                             | -             | 20 °C | ●            |
| Propyl alcohol                           | -             | 20 °C | ●            |
| Silicone oil                             | -             | 20 °C | ●            |
| Sodium carbonate, aqueous                | -             | 20 °C | ●            |
| Sodium chloride, aqueous                 | -             | 20 °C | ●            |
| Sodium hydrogen sulfite                  | -             | 20 °C | ●            |
| Sodium hydroxide solution (caustic soda) | 60            | 20 °C | ●            |
| Sodium hydroxide solution (caustic soda) | 15            | 20 °C | ●            |
| Sodium nitrate, aqueous                  | -             | 20 °C | ●            |
| Sodium thiosulfate                       | -             | 20 °C | ●            |
| Sulphuric acid                           | 96            | 20 °C | ●            |
| Transformer oil                          | -             | 20 °C | ●            |

| Kemikalie         | Koncentration | Temp. | Beständighet |
|-------------------|---------------|-------|--------------|
| Vinegar, standard | 5 - 10        | 20 °C | <div></div>  |
| Water             | -             | 20 °C | <div></div>  |
| Xylene            | -             | 20 °C | <div></div>  |