



## PE-1000 Life 2000x1000x1 mm green

Artikelnummer: P2200965

### 3. Chemical Resistance

**A** Utmärkt **B** God **C** Begränsad **D** Ej rekommenderad

CHEMICAL	BETYG	CONC.	TEMP.
1,4-Dioxane	resistant	100%	
2-Hydroxypropionic acid (lactic acid)	resistant	90%	
Acetic acid	resistant	100%	
Acetone	resistant	100%	
Ammonia	resistant		
Ammonium chloride	resistant		
Amyl alcohol	resistant		
Benzene	resistant		
Boric acid	resistant	100%	
Brake fluid	resistant		
Butyl acetate	resistant		
Calcium chloride	resistant		
Citric acid	resistant	10%	
Cresol	resistant		
Cyclohexanone	resistant	100%	
Cyclohexene	resistant	100%	
Diesel	resistant		
Ethyl acetate	resistant	100%	
Ethyl alcohol (ethanol)	resistant	96%	

CHEMICAL	BETYG	CONC.	TEMP.
Food oil	resistant		
Formaldehyde, aqueous	resistant	40%	
Formic acid	resistant	10%	
Frost protection agent	resistant		
Fuel oil	resistant		
Fuel, aromatic free	resistant		
Glycerine	resistant	100%	
Glycol	resistant	100%	
Heptane	resistant	100%	
Hydrochloric acid	resistant	10%	
Hydrochloric acid (concentrated)	resistant		
Hydrogen peroxide	resistant	10%	
Isopropyl alcohol	resistant	100%	
Linseed oil	resistant		
Mercurochrome	resistant		
Methyl alcohol (methanol)	resistant	100%	
Methylene chloride	partially_resistant	100%	
Milk	resistant		
Mineral oils, aromatic free	resistant		
Nitric acid	resistant	10%	
Nitric acid	partially_resistant	50%	
Nitrobenzene	resistant		
Oxalic acid	resistant		
Ozone (gas)	resistant	≤ 0.5 ppm%	
Paraffin oil	resistant	100%	
Perchloroethylene	partially_resistant		
Petroleum ether	resistant	100%	
Phenol, aqueous	resistant	ca. 9%	
Phosphoric acid	resistant	50%	
Potassium hydroxide solution	resistant	50%	
Premium fuel	resistant		

CHEMICAL	BETYG	CONC.	TEMP.
Propyl alcohol	resistant		
Silicone oil	resistant		
Sodium carbonate, aqueous	resistant		
Sodium chloride, aqueous	resistant		
Sodium hydrogen sulfite	resistant		
Sodium hydroxide solution (caustic soda)	resistant	60%	
Sodium hydroxide solution (caustic soda)	resistant	15%	
Sodium nitrate, aqueous	resistant		
Sodium thiosulfate	resistant		
Sulphuric acid	partially_resistant	96%	
Transformer oil	resistant		
Vinegar, standard	resistant	5 - 10%	
Water	resistant		
Xylene	not_resistant		