



PE-500 2000x1000x50 mm brun

Artikelnr P1400437

Beständig

Delvis beständig

Ej beständig

Kemikalie	Koncentration	Temp.	Beständighet
1,4-Dioxane	100%	20 Å°C	
2-Hydroxypropionic Acid	90%	20 Å°C	
Acetaldehyde	â€”	20 Å°C	
Acetic Acid	100%	20 Å°C	
Acetic acid	100%	20 Å°C	
Acetic acid	3%	100 Å°C	
Acetic acid	3% w/w	20 Å°C	
Acetic acid	3%	100 Å°C	
Acetic acid	3%	100 Å°C	
Acetic acid, aqueous	70%	20 Å°C	
Acetic anhydride	â€”	20 Å°C	
Acetone	â€”	20 Å°C	
Acetone	100%	20 Å°C	
Acronal dispersions	â€”	20 Å°C	
Acrylonitrile	â€”	20 Å°C	
Allyl acetate	â€”	20 Å°C	
Allyl alcohol	96%	20 Å°C	
Allyl chloride	â€”	20 Å°C	
Aluminium chloride, aqueous	any	20 Å°C	
Aluminium chloride, solid	â€”	20 Å°C	
Aluminium fluoride	Conc.	20 Å°C	
Aluminium hydroxide	â€”	20 Å°C	
Aluminium metaphosphate	â€”	20 Å°C	
Aluminium sulphate, aqueous saturated	â€”	20 Å°C	
Aluminium sulphate, solid	â€”	20 Å°C	
Ammonia	concentrated	20 Å°C	
Ammonia, gaseous	â€”	20 Å°C	

Kemikalie	Koncentration	Temp.	Beskrivning
Ammonia, liquid	any	20 Â°C	●
Ammonium Chloride	any	20 Â°C	●
Amyl Alcohol	any	20 Â°C	●
Aniline	any	20 Â°C	●
Anisole	any	20 Â°C	●
Apple Juice	any	20 Â°C	●
Aqua regia	any	20 Â°C	●
Beer	any	20 Â°C	●
Benzaldehyde, aqueous	any	20 Â°C	●
Benzene	technically grade	20 Â°C	●
Benzene	any	20 Â°C	●
Benzoic acid, aqueous	any	20 Â°C	●
Benzyl alcohol	any	20 Â°C	●
Bitumen	any	20 Â°C	●
Bleaching Solution	12.5 cl	20 Â°C	●
Boric Acid	100%	20 Â°C	●
Brake Fluid	any	20 Â°C	●
Bromine, liquid	100%	20 Â°C	●
Butanol, aqueous	any	20 Â°C	●
Butter	any	20 Â°C	●
Butyl Acetate	any	20 Â°C	●
Calcium Chloride	any	20 Â°C	●
Calcium carbonate	any	20 Â°C	●
Calcium carbonate	any	20 Â°C	●
Calcium hypochlorite, aqueous suspension	any	20 Â°C	●
Camphor	any	20 Â°C	●
Carbon Disulfide	100%	20 Â°C	●
Carbon Tetrachloride	any	20 Â°C	●
Carbon disulphide	any	20 Â°C	●
Caustic soda	any	20 Â°C	●
Chlorine (gas)	100%	20 Â°C	●
Chlorine, liquid	any	20 Â°C	●
Chloroacetic acid, aqueous	any	20 Â°C	●
Chlorobenzene	100%	20 Â°C	●

Kemikalie	Koncentrasie	Temp.	Bestandigheit
Chlorobenzene	â€”	20 Â°C	⚠
Chloroform	technically grade	20 Â°C	⚠
Chloroform	â€”	20 Â°C	⚠
Chromosulphuric acid	â€”	20 Â°C	⚠
Cider	â€”	20 Â°C	✅
Citric Acid	10%	20 Â°C	✅
Citrus fruit juices	â€”	20 Â°C	✅
Coconut oil	â€”	20 Â°C	✅
Cod liver oil	â€”	20 Â°C	✅
Cresol	â€”	20 Â°C	✅
Cresol	100%	20 Â°C	✅
Cyclohexane	â€”	20 Â°C	✅
Cyclohexanol	â€”	20 Â°C	✅
Cyclohexanone	100%	20 Â°C	✅
Cyclohexanone	â€”	20 Â°C	✅
Cyclohexene	100%	20 Â°C	✅
Detergents	â€”	20 Â°C	✅
Dibutyl ether	â€”	20 Â°C	✅
Dibutyl phthalate	â€”	20 Â°C	✅
Dichloroacetic acid	â€”	20 Â°C	✅
Dichloroethane	â€”	20 Â°C	⚠
Diesel Fuel	â€”	20 Â°C	✅
Diesel fuel	â€”	20 Â°C	✅
Diethylene Oxide	â€”	20 Â°C	✅
Diglycolic acid, aqueous	30%	20 Â°C	✅
Dimethyl formamide	â€”	20 Â°C	✅
Dimethylamine	â€”	20 Â°C	✅
Dioxane	â€”	20 Â°C	✅
Ethanol	10%	100 Â°C	✅
Ethanol	10%	100 Â°C	✅
Ethanol	10% v/v	20 Â°C	✅
Ethanol	10%	100 Â°C	✅
Ethyl Acetate	100%	20 Â°C	✅
Ethyl Alcohol	96%	20 Â°C	✅
Ethyl acetate	â€”	20 Â°C	✅

Kemikalie	Koncentration	Temp.	Beständighet
Ethylene Chloride	100%	20 Å°C	●
Ethylene alcohol	96%	20 Å°C	●
Ethylene chloride	â€”	20 Å°C	●
Ethylene diamine	â€”	20 Å°C	●
Ethylene glycol	â€”	20 Å°C	●
Ferric chloride, aqueous	any	20 Å°C	●
Ferric nitrate, aqueous saturated	â€”	20 Å°C	●
Ferric sulphate, aqueous saturated	â€”	20 Å°C	●
Ferrous (II) chloride, aqueous saturated	â€”	20 Å°C	●
Ferrous (II) sulfate, aqueous saturated	â€”	20 Å°C	●
Ferrous (III) chloride, aqueous saturated	â€”	20 Å°C	●
Ferrous (III) nitrate, aqueous saturated	â€”	20 Å°C	●
Ferrous (III) sulfate, aqueous saturated	â€”	20 Å°C	●
Food Oil	â€”	20 Å°C	●
Formaldehyde (aqueous)	40%	20 Å°C	●
Formaldehyde, aqueous	â‰ƒ40%	20 Å°C	●
Formic Acid	10%	20 Å°C	●
Formic acid, aqueous	85%	20 Å°C	●
Frigen 12 (Freon 12)	100%	20 Å°C	●
Frost Protection Agent	â€”	20 Å°C	●
Fruit juices	any	20 Å°C	●
Fuel (aromatic free)	â€”	20 Å°C	●
Fuel oil	â€”	20 Å°C	●
Furfural	â€”	20 Å°C	●
Glycerin, aqueous	any	20 Å°C	●
Glycerine	100%	20 Å°C	●
Glycol	100%	20 Å°C	●
Glykol, aqueous	as supplied	20 Å°C	●
Glysantin	â€”	20 Å°C	●
Heating Oil	â€”	20 Å°C	●
Heptane	â€”	20 Å°C	●
Heptane	100%	20 Å°C	●
Hexane	â€”	20 Å°C	●
Honey	â€”	20 Å°C	●
Hydrobromic acid, aqueous	50%	20 Å°C	●

Kemikalie	Koncentration	Temp.	Beständighet
Hydrochloric Acid	10%	20 Å°C	●
Hydrochloric Acid (concentrated)	concentrated	20 Å°C	●
Hydrochloric acid, aqueous	any	20 Å°C	●
Hydrofluoric Acid	40%	20 Å°C	●
Hydrogen Peroxide	10%	20 Å°C	●
Hydrogen Sulfide (aqueous solution)	â€”	20 Å°C	●
Ink	â€”	20 Å°C	●
Iodine in potassium iodide solution	3% iodine	20 Å°C	●
Isooctane	â€”	20 Å°C	●
Isopropanol	â€”	20 Å°C	●
Isopropyl Alcohol	100%	20 Å°C	●
Isopropyl ether	â€”	20 Å°C	●
Jam	â€”	20 Å°C	●
Kerosene	â€”	20 Å°C	●
Linseed Oil	â€”	20 Å°C	●
Linseed oil	technically grade	20 Å°C	●
Lithium bromide	â€”	20 Å°C	●
Magnesium stearate	â€”	20 Å°C	●
Magnesium stearate	â€”	20 Å°C	●
Maleic acid, aqueous	any	20 Å°C	●
Menthol	â€”	20 Å°C	●
Mercurochrome	â€”	20 Å°C	●
Mercury	â€”	20 Å°C	●
Methanol	technically grade	20 Å°C	●
Methyl Alcohol	100%	20 Å°C	●
Methyl Ethyl Ketone (MEK)	100%	20 Å°C	●
Methyl chloride	gaseous, technically grade	20 Å°C	●
Methyl ethyl ketone	technically grade	20 Å°C	●
Methylene Chloride	100%	20 Å°C	●
Milk	â€”	20 Å°C	●
Milk	â€”	20 Å°C	●
Mineral Oil (aromatic free)	â€”	20 Å°C	●
Molasses	â€”	20 Å°C	●
Motor oil (heavy duty oil) without additives	â€”	20 Å°C	●

Kemikalie		Koncentration	Temp.	Best�ndighet
Naphtha	���		20 ��C	�
Naphthalene	���		20 ��C	�
Nitric Acid	10%		20 ��C	�
Nitric Acid (50%)	50%		20 ��C	�
Nitric acid, aqueous	50%		20 ��C	�
Nitric acid, aqueous	25%		20 ��C	�
Nitrobenzene	���		20 ��C	�
Nitrobenzene	���		20 ��C	�
Oils, ethereal	���		20 ��C	�
Oils, vegetable and animal	���		20 ��C	�
Oleic acid	���		20 ��C	�
Oleum	any		20 ��C	�
Olive oil	���		100 ��C	�
Olive oil	���		100 ��C	�
Olive oil	���		100 ��C	�
Olive oil	���		20 ��C	�
Oxalic Acid	���		20 ��C	�
Oxalic acid, aqueous	any		20 ��C	�
Oxygen	���		20 ��C	�
Ozone	50 ppm		20 ��C	�
Ozone Gas	���0.5 ppm		20 ��C	�
Paraffine Oil	100%		20 ��C	�
Perchloric acid, aqueous	70%		20 ��C	�
Perchloric acid, aqueous	50%		20 ��C	�
Perchloric acid, aqueous	20%		20 ��C	�
Perchloroethylene	���		20 ��C	�
Petroleum	100%		20 ��C	�
Petroleum	���		20 ��C	�
Petroleum Ether	100%		20 ��C	�
Petroleum ether	���		20 ��C	�
Phenol	���		20 ��C	�
Phenol (aqueous)	���9%		20 ��C	�
Phosphoric Acid	50%		20 ��C	�
Phosphoric acid, aqueous	50%		20 ��C	�

Kemikalie	Koncentration	Temp.	Best�ndighet
Phosphoric acid, aqueous	80% L 95%	20 �C	●
Phosphorus trichloride	��	20 �C	●
Photographic developers	��	20 �C	●
Photographic emulsions	as supplied	20 �C	●
Photographic fixing baths	as supplied	20 �C	●
Phthalic acid, aqueous	50%	20 �C	●
Polyester resins	��	20 �C	●
Potassium Hydroxide liquor	50%	20 �C	●
Premium Fuel	��	20 �C	●
Propionic acid, aqueous	any	20 �C	●
Propyl Alcohol	��	20 �C	●
Pyridine	��	20 �C	●
Pyridine	��	20 �C	●
Sea water	��	20 �C	●
Silicon dioxide	��	20 �C	●
Silicon dioxide	��	20 �C	●
Silicone Oil	��	20 �C	●
Silicone oil	technically grade	20 �C	●
Sodium Carbonate (aqueous)	��	20 �C	●
Sodium Chloride (aqueous)	��	20 �C	●
Sodium Hydrogen Sulfite	��	20 �C	●
Sodium Hydroxide liquor	15%	20 �C	●
Sodium Hydroxide liquor (60%)	60%	20 �C	●
Sodium Nitrate (aqueous)	��	20 �C	●
Sodium Thiosulfate	��	20 �C	●
Sodium borate	��	20 �C	●
Sodium bromide	��	20 �C	●
Sodium hydroxide, aqueous	any	20 �C	●
Sodium hydroxide, solid	��	20 �C	●
Stearic acid	��	20 �C	●
Sugar syrup	��	20 �C	●
Sulfuric Acid	96%	20 �C	●
Sulphuric acid, aqueous	98%	20 �C	●
Sulphuric acid, aqueous	���50%	20 �C	●
Sulphuric acid, aqueous	70%	20 �C	●

Kemikalie	Koncentration	Temp.	Best�ndighet
Sulphuric acid, aqueous	80%	20 �C	�
Tallow	technically grade	20 �C	�
Tannic acid (tannin), aqueous	10%	20 �C	�
Tetrahydrofuran	technically grade	20 �C	�
Tetrahydrofuran (THF)	100%	20 �C	�
Thionyl chloride	��	20 �C	�
Thiophene	��	20 �C	�
Tin (II) chloride, aqueous	any	20 �C	�
Tin (IV) chloride, aqueous	saturated	20 �C	�
Titanium dioxide	��	20 �C	�
Titanium dioxide	��	20 �C	�
Toluene	100%	20 �C	�
Toluene	technically grade	20 �C	�
Transformer Oil	��	20 �C	�
Transformer oil (insulating oil)	technically grade	20 �C	�
Trichloroacetic acid	technically grade	20 �C	�
Trichloroethylene	technically grade	20 �C	�
Trichloroethylene	100%	20 �C	�
Triethanolamine	��	20 �C	�
Triethanolamine	��	20 �C	�
Turpentine oil	technically grade	20 �C	�
Urea, aqueous	���33%	20 �C	�
Vaseline	technically grade	20 �C	�
Vinegar (standard)	5-10%	20 �C	�
Washing up liquids	usual	20 �C	�
Water	��	20 �C	�
Water, distilled	��	20 �C	�
Wine	��	20 �C	�
Xylene	��	20 �C	�
Xylene	��	20 �C	�
Zinc sludge	��	20 �C	�