



PE-500 2000x1000x8 mm natur

Artikelnr P2200514

Beständig Delvis beständig Ej beständig

Kemikalie	Koncentration	Temp.	Beständighet
1,4-Dioxane	100%	20 Å°C	Beständig
2-Hydroxypropionic Acid	90%	20 Å°C	Beständig
Acetaldehyde	â€	20 Å°C	Beständig
Acetic Acid	100%	20 Å°C	Beständig
Acetic acid	100%	20 Å°C	Beständig
Acetic acid	3%	100 Å°C	Beständig
Acetic acid	3% w/w	20 Å°C	Beständig
Acetic acid	3%	100 Å°C	Beständig
Acetic acid	3%	100 Å°C	Beständig
Acetic acid, aqueous	70%	20 Å°C	Beständig
Acetic anhydride	â€	20 Å°C	Beständig
Acetone	â€	20 Å°C	Beständig
Acetone	100%	20 Å°C	Beständig
Acronal dispersions	â€	20 Å°C	Beständig
Acrylonitrile	â€	20 Å°C	Beständig
Allyl acetate	â€	20 Å°C	Beständig
Allyl alcohol	96%	20 Å°C	Beständig
Allyl chloride	â€	20 Å°C	Beständig
Aluminium chloride, aqueous	any	20 Å°C	Beständig
Aluminium chloride, solid	â€	20 Å°C	Beständig
Aluminium fluoride	Conc.	20 Å°C	Beständig
Aluminium hydroxide	â€	20 Å°C	Beständig
Aluminium metaphosphate	â€	20 Å°C	Beständig
Aluminium sulphate, aqueous saturated	â€	20 Å°C	Beständig
Aluminium sulphate, solid	â€	20 Å°C	Beständig
Ammonia	concentrated	20 Å°C	Beständig
Ammonia, gaseous	â€	20 Å°C	Beständig

Kemikalie	Koncentration	Temp.	Beskrivning
Ammonia, liquid	"	20 °C	
Ammonium Chloride	"	20 °C	
Amyl Alcohol	"	20 °C	
Aniline	any	20 °C	
Anisole	"	20 °C	
Apple Juice	"	20 °C	
Aqua regia	"	20 °C	
Beer	"	20 °C	
Benzaldehyde, aqueous	any	20 °C	
Benzene	technically grade	20 °C	
Benzene	"	20 °C	
Benzoic acid, aqueous	any	20 °C	
Benzyl alcohol	"	20 °C	
Bitumen	"	20 °C	
Bleaching Solution	12.5 cl	20 °C	
Boric Acid	100%	20 °C	
Brake Fluid	"	20 °C	
Bromine, liquid	100%	20 °C	
Butanol, aqueous	any	20 °C	
Butter	"	20 °C	
Butyl Acetate	"	20 °C	
Calcium Chloride	"	20 °C	
Calcium carbonate	"	20 °C	
Calcium carbonate	"	20 °C	
Calcium hypochlorite, aqueous suspension	any	20 °C	
Camphor	"	20 °C	
Carbon Disulfide	100%	20 °C	
Carbon Tetrachloride	"	20 °C	
Carbon disulphide	"	20 °C	
Caustic soda	any	20 °C	
Chlorine (gas)	100%	20 °C	
Chlorine, liquid	"	20 °C	
Chloroacetic acid, aqueous	>85%	20 °C	
Chlorobenzene	100%	20 °C	

Kemikalie	Konzentration	Temp.	BestÃndighet
Chlorobenzene	â€”	20 Â°C	🟡
Chloroform	technically grade	20 Â°C	🟡
Chloroform	â€”	20 Â°C	🟡
Chromosulphuric acid	â€”	20 Â°C	🔴
Cider	â€”	20 Â°C	🟢
Citric Acid	10%	20 Â°C	🟢
Citrus fruit juices	â€”	20 Â°C	🟢
Coconut oil	â€”	20 Â°C	🟢
Cod liver oil	â€”	20 Â°C	🟢
Cresol	â€”	20 Â°C	🟢
Cresol	100%	20 Â°C	🟢
Cyclohexane	â€”	20 Â°C	🟢
Cyclohexanol	â€”	20 Â°C	🟢
Cyclohexanone	100%	20 Â°C	🟢
Cyclohexanone	â€”	20 Â°C	🟢
Cyclohexene	100%	20 Â°C	🟢
Detergents	â€”	20 Â°C	🟢
Dibutyl ether	â€”	20 Â°C	🟢
Dibutyl phthalate	â€”	20 Â°C	🟢
Dichloroacetic acid	â€”	20 Â°C	🟢
Dichloroethane	â€”	20 Â°C	🟡
Diesel Fuel	â€”	20 Â°C	🟢
Diesel fuel	â€”	20 Â°C	🟢
Diethylene Oxide	â€”	20 Â°C	🟢
Diglycolic acid, aqueous	30%	20 Â°C	🟢
Dimethyl formamide	â€”	20 Â°C	🟢
Dimethylamine	â€”	20 Â°C	🟢
Dioxane	â€”	20 Â°C	🟢
Ethanol	10%	100 Â°C	🟢
Ethanol	10%	100 Â°C	🟢
Ethanol	10% v/v	20 Â°C	🟢
Ethanol	10%	100 Â°C	🟢
Ethyl Acetate	100%	20 Â°C	🟢
Ethyl Alcohol	96%	20 Â°C	🟢
Ethyl acetate	â€”	20 Â°C	🟢

Kemikalie	Koncentration	Temp.	Best�ndighet
Ethylene Chloride	100%	20 �C	●
Ethylene alcohol	96%	20 �C	●
Ethylene chloride	��	20 �C	●
Ethylene diamine	��	20 �C	●
Ethylene glycol	��	20 �C	●
Ferric chloride, aqueous	any	20 �C	●
Ferric nitrate, aqueous saturated	��	20 �C	●
Ferric sulphate, aqueous saturated	��	20 �C	●
Ferrous (II) chloride, aqueous saturated	��	20 �C	●
Ferrous (II) sulfate, aqueous saturated	��	20 �C	●
Ferrous (III) chloride, aqueous saturated	��	20 �C	●
Ferrous (III) nitrate, aqueous saturated	��	20 �C	●
Ferrous (III) sulfate, aqueous saturated	��	20 �C	●
Food Oil	��	20 �C	●
Formaldehyde (aqueous)	40%	20 �C	●
Formaldehyde, aqueous	���40%	20 �C	●
Formic Acid	10%	20 �C	●
Formic acid, aqueous	85%	20 �C	●
Frigen 12 (Freon 12)	100%	20 �C	●
Frost Protection Agent	��	20 �C	●
Fruit juices	any	20 �C	●
Fuel (aromatic free)	��	20 �C	●
Fuel oil	��	20 �C	●
Furfural	��	20 �C	●
Glycerin, aqueous	any	20 �C	●
Glycerine	100%	20 �C	●
Glycol	100%	20 �C	●
Glykol, aqueous	as supplied	20 �C	●
Glysantin	��	20 �C	●
Heating Oil	��	20 �C	●
Heptane	100%	20 �C	●
Heptane	��	20 �C	●
Hexane	��	20 �C	●
Honey	��	20 �C	●
Hydrobromic acid, aqueous	50%	20 �C	●

Kemikalie	Koncentration	Temp.	Beständighet
Hydrochloric Acid	10%	20 Å°C	●
Hydrochloric Acid (concentrated)	concentrated	20 Å°C	●
Hydrochloric acid, aqueous	any	20 Å°C	●
Hydrofluoric Acid	40%	20 Å°C	●
Hydrogen Peroxide	10%	20 Å°C	●
Hydrogen Sulfide (aqueous solution)	â€”	20 Å°C	●
Ink	â€”	20 Å°C	●
Iodine in potassium iodide solution	3% iodine	20 Å°C	●
Isooctane	â€”	20 Å°C	●
Isopropanol	â€”	20 Å°C	●
Isopropyl Alcohol	100%	20 Å°C	●
Isopropyl ether	â€”	20 Å°C	●
Jam	â€”	20 Å°C	●
Kerosene	â€”	20 Å°C	●
Linseed Oil	â€”	20 Å°C	●
Linseed oil	technically grade	20 Å°C	●
Lithium bromide	â€”	20 Å°C	●
Magnesium stearate	â€”	20 Å°C	●
Magnesium stearate	â€”	20 Å°C	●
Maleic acid, aqueous	any	20 Å°C	●
Menthol	â€”	20 Å°C	●
Mercurochrome	â€”	20 Å°C	●
Mercury	â€”	20 Å°C	●
Methanol	technically grade	20 Å°C	●
Methyl Alcohol	100%	20 Å°C	●
Methyl Ethyl Ketone (MEK)	100%	20 Å°C	●
Methyl chloride	gaseous, technically grade	20 Å°C	●
Methyl ethyl ketone	technically grade	20 Å°C	●
Methylene Chloride	100%	20 Å°C	●
Milk	â€”	20 Å°C	●
Milk	â€”	20 Å°C	●
Mineral Oil (aromatic free)	â€”	20 Å°C	●
Molasses	â€”	20 Å°C	●
Motor oil (heavy duty oil) without additives	â€”	20 Å°C	●

Kemikalie	Koncentration	Temp.	BestÃndighet
Naphtha	â€”	20 Â°C	â—•
Naphthalene	â€”	20 Â°C	â—•
Nitric Acid	10%	20 Â°C	â—•
Nitric Acid (50%)	50%	20 Â°C	â—•
Nitric acid, aqueous	50%	20 Â°C	â—•
Nitric acid, aqueous	25%	20 Â°C	â—•
Nitrobenzene	â€”	20 Â°C	â—•
Nitrobenzene	â€”	20 Â°C	â—•
Oils, ethereal	â€”	20 Â°C	â—•
Oils, vegetable and animal	â€”	20 Â°C	â—•
Oleic acid	â€”	20 Â°C	â—•
Oleum	any	20 Â°C	â—•
Olive oil	â€”	100 Â°C	â—•
Olive oil	â€”	100 Â°C	â—•
Olive oil	â€”	20 Â°C	â—•
Olive oil	â€”	100 Â°C	â—•
Oxalic Acid	â€”	20 Â°C	â—•
Oxalic acid, aqueous	any	20 Â°C	â—•
Oxygen	â€”	20 Â°C	â—•
Ozone	50 ppm	20 Â°C	â—•
Ozone Gas	â‰‰0.5 ppm	20 Â°C	â—•
Paraffine Oil	100%	20 Â°C	â—•
Perchloric acid, aqueous	70%	20 Â°C	â—•
Perchloric acid, aqueous	20%	20 Â°C	â—•
Perchloric acid, aqueous	50%	20 Â°C	â—•
Perchloroethylene	â€”	20 Â°C	â—•
Petroleum	100%	20 Â°C	â—•
Petroleum	â€”	20 Â°C	â—•
Petroleum Ether	100%	20 Â°C	â—•
Petroleum ether	â€”	20 Â°C	â—•
Phenol	â€”	20 Â°C	â—•
Phenol (aqueous)	â‰‰9%	20 Â°C	â—•
Phosphoric Acid	50%	20 Â°C	â—•
Phosphoric acid, aqueous	80% L 95%	20 Â°C	â—•

Kemikalie	Koncentration	Temp.	Best�ndighet
Phosphoric acid, aqueous	50%	20 �C	●
Phosphorus trichloride	��	20 �C	●
Photographic developers	��	20 �C	●
Photographic emulsions	as supplied	20 �C	●
Photographic fixing baths	as supplied	20 �C	●
Phthalic acid, aqueous	50%	20 �C	●
Polyester resins	��	20 �C	●
Potassium Hydroxide liquor	50%	20 �C	●
Premium Fuel	��	20 �C	●
Propionic acid, aqueous	any	20 �C	●
Propyl Alcohol	��	20 �C	●
Pyridine	��	20 �C	●
Pyridine	��	20 �C	●
Sea water	��	20 �C	●
Silicon dioxide	��	20 �C	●
Silicon dioxide	��	20 �C	●
Silicone Oil	��	20 �C	●
Silicone oil	technically grade	20 �C	●
Sodium Carbonate (aqueous)	��	20 �C	●
Sodium Chloride (aqueous)	��	20 �C	●
Sodium Hydrogen Sulfite	��	20 �C	●
Sodium Hydroxide liquor	15%	20 �C	●
Sodium Hydroxide liquor (60%)	60%	20 �C	●
Sodium Nitrate (aqueous)	��	20 �C	●
Sodium Thiosulfate	��	20 �C	●
Sodium borate	��	20 �C	●
Sodium bromide	��	20 �C	●
Sodium hydroxide, aqueous	any	20 �C	●
Sodium hydroxide, solid	��	20 �C	●
Stearic acid	��	20 �C	●
Sugar syrup	��	20 �C	●
Sulfuric Acid	96%	20 �C	●
Sulphuric acid, aqueous	70%	20 �C	●
Sulphuric acid, aqueous	80%	20 �C	●
Sulphuric acid, aqueous	98%	20 �C	●

Kemikalie	Koncentration	Temp.	Best�ndighet
Sulphuric acid, aqueous	���50%	20 ��C	�
Tallow	technically grade	20 ��C	�
Tannic acid (tannin), aqueous	10%	20 ��C	�
Tetrahydrofuran	technically grade	20 ��C	�
Tetrahydrofuran (THF)	100%	20 ��C	�
Thionyl chloride	���	20 ��C	�
Thiophene	���	20 ��C	�
Tin (II) chloride, aqueous	any	20 ��C	�
Tin (IV) chloride, aqueous	saturated	20 ��C	�
Titanium dioxide	���	20 ��C	�
Titanium dioxide	���	20 ��C	�
Toluene	technically grade	20 ��C	�
Toluene	100%	20 ��C	�
Transformer Oil	���	20 ��C	�
Transformer oil (insulating oil)	technically grade	20 ��C	�
Trichloroacetic acid	technically grade	20 ��C	�
Trichloroethylene	technically grade	20 ��C	�
Trichloroethylene	100%	20 ��C	�
Triethanolamine	���	20 ��C	�
Triethanolamine	���	20 ��C	�
Turpentine oil	technically grade	20 ��C	�
Urea, aqueous	���33%	20 ��C	�
Vaseline	technically grade	20 ��C	�
Vinegar (standard)	5-10%	20 ��C	�
Washing up liquids	usual	20 ��C	�
Water	���	20 ��C	�
Water, distilled	���	20 ��C	�
Wine	���	20 ��C	�
Xylene	���	20 ��C	�
Xylene	���	20 ��C	�
Zinc sludge	���	20 ��C	�