



PEEK CMP 360/290x1000 mm beige

Artikelnr P1500822

Beständig

Delvis beständig

Ej beständig

Kemikalie	Koncentration	Temp.	Beständighet
1,4-Dioxane	100	20 Å°C	
2-Hydroxypropionic acid (lactic acid)	90	20 Å°C	
Acetic acid	100	20 Å°C	
Acetone	100	20 Å°C	
Ammonia	â€”	20 Å°C	
Ammonium chloride	â€”	20 Å°C	
Amyl alcohol	â€”	20 Å°C	
Apple juice	â€”	20 Å°C	
Benzene	â€”	20 Å°C	
Boric acid	100	20 Å°C	
Brake fluid	â€”	20 Å°C	
Butyl acetate	â€”	20 Å°C	
Calcium chloride	â€”	20 Å°C	
Carbon tetrachloride	â€”	20 Å°C	
Chlorine (gas)	100	20 Å°C	
Chlorobenzene	100	20 Å°C	
Chloroform	â€”	20 Å°C	
Citric acid	10	20 Å°C	
Cyclohexanone	100	20 Å°C	
Cyclohexene	100	20 Å°C	
Diesel	â€”	20 Å°C	
Diethylene oxide	â€”	20 Å°C	
Ethyl acetate	100	20 Å°C	
Ethyl alcohol (ethanol)	96	20 Å°C	
Ethylene chloride	100	20 Å°C	
Food oil	â€”	20 Å°C	
Formaldehyde (aqueous)	40	20 Å°C	

Kemikalie		Koncentration	Temp.	Best�ndighet
Formic acid	10	20 �C		
Frost protection agent	��	20 �C		
Fuel oil	��	20 �C		
Fuel, aromatic free	��	20 �C		
Glycerine	100	20 �C		
Glycol	100	20 �C		
Heptane	100	20 �C		
Hydrochloric acid	10	20 �C		
Hydrochloric acid (concentrated)	��	20 �C		
Hydrofluoric acid	40	20 �C		
Hydrogen peroxide	10	20 �C		
Hydrogen sulfide (aqueous)	��	20 �C		
Isopropyl alcohol	100	20 �C		
Linseed oil	��	20 �C		
Mercurochrome	��	20 �C		
Methyl alcohol (methanol)	100	20 �C		
Methyl ethyl ketone (MEK)	100	20 �C		
Methylene chloride	100	20 �C		
Milk	��	20 �C		
Mineral oils (aromatic free)	��	20 �C		
Nitric acid	50	20 �C		
Nitric acid	10	20 �C		
Nitrobenzene	��	20 �C		
Oxalic acid	��	20 �C		
Ozone (gas)	��	20 �C		
Paraffin oil	100	20 �C		
Perchloroethylene	��	20 �C		
Petroleum	100	20 �C		
Petroleum ether	100	20 �C		
Phenol (aqueous)	9	20 �C		
Phosphoric acid	50	20 �C		
Potassium hydroxide solution	50	20 �C		
Premium fuel	��	20 �C		
Propyl alcohol	��	20 �C		
Pyridine	��	20 �C		

