



PEEK 3000x620x25 mm svart

Artikelnr P1500654
Material PEEK

Tekniska egenskaper

Density & Weight

Egenskap	Värde	Enhet	Provningsstandard
Density	1.31	g/cm³	ISO 1183

Tensile Properties

Egenskap	Värde	Enhet	Provningsstandard
Tensile Strength	112	MPa	ISO527-2
Modulus of elasticity (tensile)	4400	MPa	ISO 527-2
Breakdown Voltage	67	MPa	ISO 527
Break Elongation	20	%	ISO 527-2

Temperature Limits

Egenskap	Värde	Enhet	Provningsstandard
Melting point	340	°C	ISO 3146
Maximal operating temperature (short-term)	291	°C	UL746B
Maximum Operating Temperature	245	°C	
Minimum temperature	-35	°C	
Heat deflection temperature (HDT/A)	160	°C	ISO 75-2
Heat deflection temperature (HDT/B)	240	°C	ISO 75
Vicat softening temperature (VST/B/50)	50	°C	ISO 306

Insulation Properties

Egenskap	Värde	Enhet	Provningsstandard
Dielectric Strength	24	kV/mm	IEC 60243-1
Volume Resistivity	10 ¹⁴	Ω·cm	IEC 60093
Dielectric Constant (1 MHz)	3.6	-	IEC 60250
Dielectric Constant (100 Hz)	3.2	-	IEC 60250
Dielectric loss factor (1 MHz)	0.0	-	IEC 60250
Dielectric loss factor (100 Hz)	0.0	-	IEC 60250

Fire Classification

Egenskap	Värde	Enhet	Provningsstandard
Flammability Classification (UL 94)	0		UL 94

Flexural Properties

Egenskap	Värde	Enhet	Provningsstandard
Flexural Strength	110	MPa	ISO 527-2

Thermal Conductivity

Egenskap	Värde	Enhet	Provningsstandard
Thermal Conductivity	0.25	W/(m·K)	DIN 52612

Static spread

Egenskap	Värde	Enhet	Provningsstandard
Surface Resistivity	10 ¹³	Ω	IEC 60093
Comparative Tracking Index (CTI)	150	V	IEC 60112

Moisture Absorption

Egenskap	Värde	Enhet	Provningsstandard
Water absorption to saturation	0.2	%	ISO 62
Water Absorption to Saturation	0.45	%	ISO 62

Impact Resistance

Egenskap	Värde	Enhet	Provningsstandard
Notched impact strength (Charpy)	3.5	kJ/m²	ISO 179/1eA
Impact Resistance (Charpy)	92	kJ/m²	ISO179/1eU

Thermal Expansion

Egenskap	Värde	Enhet	Provningsstandard
----------	-------	-------	-------------------

Egenskap	Värde	Enhet	Provningsstandard
Thermal Expansion Coefficient	0.5	10 ⁻⁴ /K	DIN 11359

Hardness

Egenskap	Värde	Enhet	Provningsstandard
Hardness Shore D	90	° Shore D	DIN EN ISO 868
Ball pressure hardness	230	MPa	ISO 2039-1

Godkännanden

- EU 10/2011
- FDA
- REACH
- RoHS
- UL 94