



PEEK 255/90x3000 mm beige

Artikelnr P1500505

● Beständigt ● Delvis beständigt ● Ej beständigt

Kemikalie	Koncentrasjon	Temp.	Best�ndighet
1,4-Dioxane	100	20 ��C	�
2-Hydroxypropionic acid (lactic acid)	90	20 ��C	�
Acetic acid	100	20 ��C	�
Acetone	100	20 ��C	�
Ammonia	���	20 ��C	�
Ammonium chloride	���	20 ��C	�
Amyl alcohol	���	20 ��C	�
Apple juice	���	20 ��C	�
Benzene	���	20 ��C	�
Boric acid	100	20 ��C	�
Brake fluid	���	20 ��C	�
Butyl acetate	���	20 ��C	�
Calcium chloride	���	20 ��C	�
Carbon tetrachloride	���	20 ��C	�
Chlorine (gas)	100	20 ��C	�
Chlorobenzene	100	20 ��C	�
Chloroform	���	20 ��C	�
Citric acid	10	20 ��C	�
Cyclohexanone	100	20 ��C	�
Cyclohexene	100	20 ��C	�
Diesel	���	20 ��C	�
Diethylene oxide	���	20 ��C	�
Ethyl acetate	100	20 ��C	�
Ethyl alcohol (ethanol)	96	20 ��C	�
Ethylene chloride	100	20 ��C	�
Food oil	���	20 ��C	�
Formaldehyde (aqueous)	40	20 ��C	�

Kemikalie	Koncentration	Temp.	Best�ndighet
Formic acid	10	20 ��C	�
Frost protection agent	���	20 ��C	�
Fuel oil	���	20 ��C	�
Fuel, aromatic free	���	20 ��C	�
Glycerine	100	20 ��C	�
Glycol	100	20 ��C	�
Heptane	100	20 ��C	�
Hydrochloric acid	10	20 ��C	�
Hydrochloric acid (concentrated)	���	20 ��C	�
Hydrofluoric acid	40	20 ��C	�
Hydrogen peroxide	10	20 ��C	�
Hydrogen sulfide (aqueous)	���	20 ��C	�
Isopropyl alcohol	100	20 ��C	�
Linseed oil	���	20 ��C	�
Mercurochrome	���	20 ��C	�
Methyl alcohol (methanol)	100	20 ��C	�
Methyl ethyl ketone (MEK)	100	20 ��C	�
Methylene chloride	100	20 ��C	�
Milk	���	20 ��C	�
Mineral oils (aromatic free)	���	20 ��C	�
Nitric acid	10	20 ��C	�
Nitric acid	50	20 ��C	�
Nitrobenzene	���	20 ��C	�
Oxalic acid	���	20 ��C	�
Ozone (gas)	���	20 ��C	�
Paraffin oil	100	20 ��C	�
Perchloroethylene	���	20 ��C	�
Petroleum	100	20 ��C	�
Petroleum ether	100	20 ��C	�
Phenol (aqueous)	9	20 ��C	�
Phosphoric acid	50	20 ��C	�
Potassium hydroxide solution	50	20 ��C	�
Premium fuel	���	20 ��C	�
Propyl alcohol	���	20 ��C	�
Pyridine	���	20 ��C	�

