



PET ZX 1000x1000x35 mm light grÅ

Artikelnr P1004223

Beständig Delvis beständig Ej beständig

| Kemikalie            | Koncentration | Temp.  | Beständighet |
|----------------------|---------------|--------|--------------|
| 1,4-Dioxane          | 100           | 60 Å°C |              |
| 1,4-Dioxane          | 100           | 20 Å°C |              |
| Acetic acid          | 100           | 20 Å°C |              |
| Acetic acid          | 100%          | 20 Å°C |              |
| Acetic acid          | 100           | 60 Å°C |              |
| Acetone              | 100           | 60 Å°C |              |
| Acetone              | 100           | 20 Å°C |              |
| Ammonia              | conc.         | 20 Å°C |              |
| Ammonia              | conc.         | 60 Å°C |              |
| Apple juice          | â€            | 20 Å°C |              |
| Apple juice          | â€            | 20 Å°C |              |
| Benzene              | â€            | 20 Å°C |              |
| Benzene              | â€            | 60 Å°C |              |
| Bleaching solution   | â€            | 20 Å°C |              |
| Brake fluid          | â€            | 60 Å°C |              |
| Brake fluid          | â€            | 20 Å°C |              |
| Butyl acetate        | â€            | 60 Å°C |              |
| Butyl acetate        | â€            | 20 Å°C |              |
| Calcium chloride     | â€            | 60 Å°C |              |
| Calcium chloride     | â€            | 20 Å°C |              |
| Carbon disulphide    | 100           | 60 Å°C |              |
| Carbon disulphide    | 100           | 20 Å°C |              |
| Carbon tetrachloride | â€            | 20 Å°C |              |
| Carbon tetrachloride | â€            | 20 Å°C |              |
| Carbon tetrachloride | â€            | 60 Å°C |              |
| Chlorobenzene        | 100%          | 20 Å°C |              |
| Chlorobenzene        | 100           | 60 Å°C |              |

| Kemikalie               |      | Koncentration | Temp.  | Best ndighet |
|-------------------------|------|---------------|--------|--------------|
| Chlorobenzene           | 100  |               | 20   C |              |
| Chloroform              |      |               | 60   C |              |
| Chloroform              |      |               | 20   C |              |
| Citric acid             | 10   |               | 20   C |              |
| Citric acid             | 10   |               | 60   C |              |
| Diesel                  |      |               | 20   C |              |
| Diesel                  |      |               | 60   C |              |
| Diethylene oxide        |      |               | 20   C |              |
| Diethylene oxide        |      |               | 20   C |              |
| Ethyl acetate           | 100  |               | 20   C |              |
| Ethyl acetate           | 100  |               | 60   C |              |
| Ethyl alcohol (ethanol) | 96   |               | 60   C |              |
| Ethyl alcohol (ethanol) | 96%  |               | 20   C |              |
| Ethyl alcohol (ethanol) | 96   |               | 20   C |              |
| Ethylene chloride       | 100  |               | 20   C |              |
| Ethylene chloride       | 100  |               | 60   C |              |
| Food oil                |      |               | 20   C |              |
| Food oil                |      |               | 60   C |              |
| Food oil                |      |               | 20   C |              |
| Formic acid             | 10   |               | 20   C |              |
| Formic acid             | 10   |               | 60   C |              |
| Frost protection agent  |      |               | 20   C |              |
| Frost protection agent  |      |               | 60   C |              |
| Fuel oil                |      |               | 60   C |              |
| Fuel oil                |      |               | 20   C |              |
| Fuel, aromatic free     |      |               | 60   C |              |
| Fuel, aromatic free     |      |               | 20   C |              |
| Glycerine               | 100  |               | 60   C |              |
| Glycerine               | 100  |               | 20   C |              |
| Glycerine               | 100% |               | 20   C |              |
| Glycol                  | 100  |               | 60   C |              |
| Glycol                  | 100  |               | 20   C |              |
| Heptane                 | 100  |               | 20   C |              |
| Heptane                 | 100  |               | 60   C |              |

| Kemikalie                        | Koncentration | Temp.  | Best ndighet |
|----------------------------------|---------------|--------|--------------|
| Hydrochloric acid                | conc.         | 20   C |              |
| Hydrochloric acid                | 10            | 60   C |              |
| Hydrochloric acid                | 10            | 20   C |              |
| Hydrochloric acid                | conc.         | 60   C |              |
| Hydrochloric acid (concentrated) | conc.         | 20   C |              |
| Hydrofluoric acid                | 40%           | 20   C |              |
| Hydrofluoric acid                | 40            | 60   C |              |
| Hydrofluoric acid                | 40            | 20   C |              |
| Hydrogen peroxide                | 10            | 20   C |              |
| Hydrogen peroxide                | 10            | 60   C |              |
| Hydrogen sulfide, aqueous        |               | 20   C |              |
| Isopropyl alcohol                | 100           | 60   C |              |
| Isopropyl alcohol                | 100%          | 20   C |              |
| Isopropyl alcohol                | 100           | 20   C |              |
| Linseed oil                      |               | 60   C |              |
| Linseed oil                      |               | 20   C |              |
| Mercurochrome                    |               | 20   C |              |
| Methyl alcohol (methanol)        | 100           | 20   C |              |
| Methyl alcohol (methanol)        | 100           | 60   C |              |
| Methyl alcohol (methanol)        | 100%          | 20   C |              |
| Methyl ethyl ketone (MEK)        | 100           | 60   C |              |
| Methyl ethyl ketone (MEK)        | 100           | 20   C |              |
| Methylene chloride               | 100           | 20   C |              |
| Methylene chloride               | 100           | 60   C |              |
| Milk                             |               | 20   C |              |
| Milk                             |               | 60   C |              |
| Mineral oils, aromatic free      |               | 20   C |              |
| Mineral oils, aromatic free      |               | 60   C |              |
| Nitric acid                      | 50            | 20   C |              |
| Nitric acid                      | 50            | 60   C |              |
| Nitric acid                      | 10%           | 20   C |              |
| Nitric acid                      | 10            | 20   C |              |
| Nitric acid                      | 10            | 60   C |              |
| Paraffin oil                     | 100           | 20   C |              |

| Kemikalie                                | Koncentration | Temp.  | Best ndighet |
|------------------------------------------|---------------|--------|--------------|
| Paraffin oil                             | 100           | 60   C |              |
| Perchloroethylene                        |               | 60   C |              |
| Perchloroethylene                        |               | 20   C |              |
| Petroleum                                | 100%          | 20   C |              |
| Petroleum                                | 100           | 20   C |              |
| Petroleum ether                          | 100           | 60   C |              |
| Petroleum ether                          | 100           | 20   C |              |
| Petroleum ether                          | 100%          | 20   C |              |
| Phenol, aqueous                          | ca.9          | 20   C |              |
| Phosphoric acid                          | 50            | 20   C |              |
| Phosphoric acid                          | 50            | 60   C |              |
| Potassium hydroxide solution             | 50            | 60   C |              |
| Potassium hydroxide solution             | 50            | 20   C |              |
| Premium fuel                             |               | 60   C |              |
| Premium fuel                             |               | 20   C |              |
| Propyl alcohol                           |               | 60   C |              |
| Propyl alcohol                           |               | 20   C |              |
| Silicone oil                             |               | 20   C |              |
| Silicone oil                             |               | 60   C |              |
| Sodium carbonate, aqueous                |               | 20   C |              |
| Sodium carbonate, aqueous                |               | 60   C |              |
| Sodium chloride, aqueous                 |               | 20   C |              |
| Sodium chloride, aqueous                 |               | 60   C |              |
| Sodium hydrogen sulfite                  |               | 60   C |              |
| Sodium hydrogen sulfite                  |               | 20   C |              |
| Sodium hydrogen sulfite                  |               | 20   C |              |
| Sodium hydroxide solution (caustic soda) | 15            | 20   C |              |
| Sodium hydroxide solution (caustic soda) | 60            | 20   C |              |
| Sodium hydroxide solution (caustic soda) | 60            | 60   C |              |
| Sodium hydroxide solution (caustic soda) | 15            | 60   C |              |
| Sodium nitrate, aqueous                  |               | 20   C |              |
| Sodium thiosulfate                       |               | 20   C |              |
| Sulphuric acid                           | 96            | 20   C |              |
| Sulphuric acid                           | 96            | 60   C |              |

| Kemikalie             | Koncentration | Temp. | Best ndighet |
|-----------------------|---------------|-------|--------------|
| Tetrahydrofuran (THF) | 100           | 60  C |              |
| Tetrahydrofuran (THF) | 100           | 20  C |              |
| Toluene               | 100           | 60  C |              |
| Toluene               | 100           | 20  C |              |
| Toluene               | 100%          | 20  C |              |
| Transformer oil       |               | 60  C |              |
| Transformer oil       |               | 20  C |              |
| Trichloroethylene     | 100           | 60  C |              |
| Trichloroethylene     | 100           | 20  C |              |
| Vinegar, standard     | 5-10          | 60  C |              |
| Vinegar, standard     | 5-10          | 20  C |              |
| Vinegar, standard     | 5-10%         | 20  C |              |
| Water                 |               | 20  C |              |
| Water                 |               | 60  C |              |
| Xylene                |               | 20  C |              |
| Xylene                |               | 60  C |              |