



PET 2000x1000x12 mm natur

Artikelnr P1003825

● Beständigt ● Delvis beständigt ● Ej beständigt

Kemikalie	Koncentration	Temp.	Best�ndighet
1,4-Dioxane	100	60 ��C	�
1,4-Dioxane	100	20 ��C	�
Acetic acid	100	20 ��C	�
Acetic acid	100%	20 ��C	�
Acetic acid	100	60 ��C	�
Acetone	100	60 ��C	�
Acetone	100	20 ��C	�
Ammonia	conc.	20 ��C	�
Ammonia	conc.	60 ��C	�
Apple juice	���	20 ��C	�
Apple juice	���	20 ��C	�
Benzene	���	20 ��C	�
Benzene	���	60 ��C	�
Bleaching solution	���	20 ��C	�
Brake fluid	���	60 ��C	�
Brake fluid	���	20 ��C	�
Butyl acetate	���	60 ��C	�
Butyl acetate	���	20 ��C	�
Calcium chloride	���	60 ��C	�
Calcium chloride	���	20 ��C	�
Carbon disulphide	100	60 ��C	�
Carbon disulphide	100	20 ��C	�
Carbon tetrachloride	���	20 ��C	�
Carbon tetrachloride	���	20 ��C	�
Carbon tetrachloride	���	60 ��C	�
Chlorobenzene	100%	20 ��C	�
Chlorobenzene	100	60 ��C	�

Kemikalie	Koncentration	Temp.	Best�ndighet
Chlorobenzene	100	20 ��C	�
Chloroform	���	60 ��C	�
Chloroform	���	20 ��C	�
Citric acid	10	20 ��C	�
Citric acid	10	60 ��C	�
Diesel	���	20 ��C	�
Diesel	���	60 ��C	�
Diethylene oxide	���	20 ��C	�
Diethylene oxide	���	20 ��C	�
Ethyl acetate	100	20 ��C	�
Ethyl acetate	100	60 ��C	�
Ethyl alcohol (ethanol)	96	60 ��C	�
Ethyl alcohol (ethanol)	96%	20 ��C	�
Ethyl alcohol (ethanol)	96	20 ��C	�
Ethylene chloride	100	20 ��C	�
Ethylene chloride	100	60 ��C	�
Food oil	���	20 ��C	�
Food oil	���	60 ��C	�
Food oil	���	20 ��C	�
Formic acid	10	20 ��C	�
Formic acid	10	60 ��C	�
Frost protection agent	���	20 ��C	�
Frost protection agent	���	60 ��C	�
Fuel oil	���	60 ��C	�
Fuel oil	���	20 ��C	�
Fuel, aromatic free	���	60 ��C	�
Fuel, aromatic free	���	20 ��C	�
Glycerine	100	60 ��C	�
Glycerine	100	20 ��C	�
Glycerine	100%	20 ��C	�
Glycol	100	60 ��C	�
Glycol	100	20 ��C	�
Heptane	100	20 ��C	�
Heptane	100	60 ��C	�

Kemikalie	Koncentration	Temp.	Best�ndighet
Hydrochloric acid	conc.	20 ��C	�
Hydrochloric acid	10	60 ��C	�
Hydrochloric acid	10	20 ��C	�
Hydrochloric acid	conc.	60 ��C	�
Hydrochloric acid (concentrated)	conc.	20 ��C	�
Hydrofluoric acid	40%	20 ��C	�
Hydrofluoric acid	40	60 ��C	�
Hydrofluoric acid	40	20 ��C	�
Hydrogen peroxide	10	20 ��C	�
Hydrogen peroxide	10	60 ��C	�
Hydrogen sulfide, aqueous	���	20 ��C	�
Isopropyl alcohol	100	60 ��C	�
Isopropyl alcohol	100%	20 ��C	�
Isopropyl alcohol	100	20 ��C	�
Linseed oil	���	60 ��C	�
Linseed oil	���	20 ��C	�
Mercurochrome	���	20 ��C	�
Methyl alcohol (methanol)	100	20 ��C	�
Methyl alcohol (methanol)	100	60 ��C	�
Methyl alcohol (methanol)	100%	20 ��C	�
Methyl ethyl ketone (MEK)	100	60 ��C	�
Methyl ethyl ketone (MEK)	100	20 ��C	�
Methylene chloride	100	20 ��C	�
Methylene chloride	100	60 ��C	�
Milk	���	20 ��C	�
Milk	���	60 ��C	�
Mineral oils, aromatic free	���	20 ��C	�
Mineral oils, aromatic free	���	60 ��C	�
Nitric acid	50	20 ��C	�
Nitric acid	50	60 ��C	�
Nitric acid	10%	20 ��C	�
Nitric acid	10	20 ��C	�
Nitric acid	10	60 ��C	�
Paraffin oil	100	20 ��C	�

Kemikalie	Koncentration	Temp.	Best�ndighet
Paraffin oil	100	60 ��C	�
Perchloroethylene	����	60 ��C	�
Perchloroethylene	����	20 ��C	�
Petroleum	100%	20 ��C	�
Petroleum	100	20 ��C	�
Petroleum ether	100	60 ��C	�
Petroleum ether	100	20 ��C	�
Petroleum ether	100%	20 ��C	�
Phenol, aqueous	ca.9	20 ��C	�
Phosphoric acid	50	20 ��C	�
Phosphoric acid	50	60 ��C	�
Potassium hydroxide solution	50	60 ��C	�
Potassium hydroxide solution	50	20 ��C	�
Premium fuel	����	60 ��C	�
Premium fuel	����	20 ��C	�
Propyl alcohol	����	60 ��C	�
Propyl alcohol	����	20 ��C	�
Silicone oil	����	60 ��C	�
Silicone oil	����	20 ��C	�
Sodium carbonate, aqueous	����	60 ��C	�
Sodium carbonate, aqueous	����	20 ��C	�
Sodium chloride, aqueous	����	60 ��C	�
Sodium chloride, aqueous	����	20 ��C	�
Sodium hydrogen sulfite	����	60 ��C	�
Sodium hydrogen sulfite	����	20 ��C	�
Sodium hydrogen sulfite	����	20 ��C	�
Sodium hydroxide solution (caustic soda)	15	60 ��C	�
Sodium hydroxide solution (caustic soda)	60	20 ��C	�
Sodium hydroxide solution (caustic soda)	60	60 ��C	�
Sodium hydroxide solution (caustic soda)	15	20 ��C	�
Sodium nitrate, aqueous	����	20 ��C	�
Sodium thiosulfate	����	20 ��C	�
Sulphuric acid	96	20 ��C	�
Sulphuric acid	96	60 ��C	�

Kemikalie	Koncentration	Temp.	Best�ndighet
Tetrahydrofuran (THF)	100	60 �C	�
Tetrahydrofuran (THF)	100	20 �C	�
Toluene	100	60 �C	�
Toluene	100	20 �C	�
Toluene	100%	20 �C	�
Transformer oil	��	60 �C	�
Transformer oil	��	20 �C	�
Trichloroethylene	100	60 �C	�
Trichloroethylene	100	20 �C	�
Vinegar, standard	5-10	60 �C	�
Vinegar, standard	5-10	20 �C	�
Vinegar, standard	5-10%	20 �C	�
Water	��	20 �C	�
Water	��	60 �C	�
Xylene	��	20 �C	�
Xylene	��	60 �C	�