



POM C 100/70x3000 mm black

Artikelnr P1005750
Kategori POM

Tekniska egenskaper

Density & Weight

Egenskap	V�rde	Enhet	Provningsstandard
Density	1.24	g/cm���	ASTM D792

Tensile Properties

Egenskap	V�rde	Enhet	Provningsstandard
Tensile Strength	51	MPa	DIN EN ISO 527-2
Modulus of elasticity (tensile)	1200	MPa	ASTM D790
Breakdown Voltage	76.5	MPa	ISO 527
Break Elongation	300	%	ASTM D638

Temperature Limits

Egenskap	V�rde	Enhet	Provningsstandard
Melting point	222	��C	ISO 3146
Maximal operating temperature (short-term)	129	��C	UL746B
Maximum Operating Temperature	90	��C	
Minimum temperature	-46.25	��C	
Heat deflection temperature (HDT/A)	105	��C	ASTM D648
Heat deflection temperature (HDT/B)	155	��C	ISO 75
Vicat softening temperature (VST/B/50)	50	��C	ISO 306

Insulation Properties

Egenskap	V�rde	Enhet	Provningsstandard
Dielectric Strength	85	kV/mm	IEC 60243-1

Egenskap	V�rde	Enhet	Provningsstandard
Volume Resistivity	10�1�2	��I	IEC 60093
Dielectric Constant (1 MHz)	3.7	-	IEC 60250
Dielectric loss factor (1 MHz)	0.0	-	IEC 60250
Dielectric loss factor (100 Hz)	0.0	-	IEC 60250

Fire Classification

Egenskap	V�rde	Enhet	Provningsstandard
Flammability Classification (UL 94)	60695		UL 94

Flexural Properties

Egenskap	V�rde	Enhet	Provningsstandard
Flexural Strength	58	MPa	ASTM D638

Thermal Conductivity

Egenskap	V�rde	Enhet	Provningsstandard
Thermal Conductivity	0.3	W/(m��K)	DIN 52612

Static spread

Egenskap	V�rde	Enhet	Provningsstandard
Surface Resistivity	10�1�3	��I	IEC 60093
Comparative Tracking Index (CTI)	600	V	IEC 60112

Moisture Absorption

Egenskap	V�rde	Enhet	Provningsstandard
Water absorption to saturation	2.2	%	ASTM D955
Water Absorption to Saturation	0.5	%	ASTM D570

Impact Resistance

Egenskap	V�rde	Enhet	Provningsstandard
Notched impact strength (Charpy)	6	kJ/m�2	DIN EN ISO 179-1
Impact Resistance (Charpy)	19	kJ/m�2	ISO 179/1eU

Thermal Expansion

Egenskap	V�rde	Enhet	Provningsstandard
Thermal Expansion Coefficient	0.4	10���/K	ISO 11359

Hardness

Egenskap	V�rde	Enhet	Provningsstandard
Hardness Shore D	83	� Shore D	ISO 868
Ball pressure hardness	230	MPa	ISO 2039-1

Godk nnanden

- EU 10/2011
- FDA
- REACH
- RoHS