PLASTSHOP.SE

Kemisk beständighet

PlastShop.se - 2026-03-26

POM C FG 56/30x1000 mm svart

Artikelnr P1007031

Beständig Delvis beständig Ej beständig

Kemikalie	Koncentration	Temp.	Beständighet
1,4-Dioxane	100%	20 °C	Delvis beständig
2-Hydroxypropionic acid (lactic acid)	90%	20 °C	Beständig
Acetic acid	100%	20 °C	Delvis beständig
Acetone	100%	20 °C	Beständig
Ammonia	conc.	20 °C	Beständig
Ammonium chloride	-	20 °C	Delvis beständig
Amyl alcohol	-	20 °C	Beständig
Apple juice	-	20 °C	Beständig
Benzene	-	20 °C	Delvis beständig
Bleaching solution	12.5 cl	20 °C	Ej beständig
Boric acid	100%	20 °C	Delvis beständig
Brake fluid	-	20 °C	Beständig
Butyl acetate	-	20 °C	Beständig
Calcium chloride	-	20 °C	Beständig
Carbon disulphide	100%	20 °C	Beständig
Carbon tetrachloride	-	20 °C	Beständig
Chlorobenzene	100%	20 °C	Delvis beständig
Chloroform	-	20 °C	Ej beständig
Citric acid	10%	20 °C	Delvis beständig
Cyclohexanone	100%	20 °C	Beständig
Cyclohexene	100%	20 °C	Beständig
Diesel	-	20 °C	Beständig
Diethylene oxide	-	20 °C	Beständig
Ethyl acetate	100%	20 °C	Delvis beständig
Ethyl alcohol (ethanol)	96%	20 °C	Beständig
Food oil	-	20 °C	Beständig

Kemikalie	Koncentration	Temp.	Beständighet
Formaldehyde, aqueous	40%	20 °C	🟢
Formic acid	10%	20 °C	🟢
Frost protection agent	-	20 °C	🟢
Fuel oil	-	20 °C	🟢
Fuel, aromatic free	-	20 °C	🟢
Glycerine	100%	20 °C	🟢
Glycol	100%	20 °C	🟢
Heptane	100%	20 °C	🟢
Hydrochloric acid	10%	20 °C	🔴
Hydrochloric acid (concentrated)	conc.	20 °C	🔴
Hydrofluoric acid	40%	20 °C	🔴
Hydrogen peroxide	10%	20 °C	🟢
Hydrogen sulfide, aqueous	-	20 °C	🟢
Isopropyl alcohol	100%	20 °C	🟢
Linseed oil	-	20 °C	🟢
Mercurochrome	-	20 °C	🔴
Methyl alcohol (methanol)	100%	20 °C	🟢
Methyl ethyl ketone (MEK)	100%	20 °C	🟡
Methylene chloride	100%	20 °C	🔴
Milk	-	20 °C	🟢
Mineral oils (aromatic free)	-	20 °C	🟢
Nitric acid	10%	20 °C	🔴
Nitric acid (50%)	50%	20 °C	🔴
Nitrobenzene	-	20 °C	🟡
Oxalic acid	-	20 °C	🔴
Ozone (gas)	≤0.5 ppm	20 °C	🔴
Paraffin oil	100%	20 °C	🟢
Perchloroethylene	-	20 °C	🟢
Petroleum	100%	20 °C	🟢
Petroleum ether	100%	20 °C	🟢
Phenol, aqueous	ca. 9%	20 °C	🔴
Phosphoric acid	50%	20 °C	🔴
Potassium hydroxide solution	50%	20 °C	🟡
Premium fuel	-	20 °C	🟢

Kemikalie	Koncentration	Temp.	Beständighet
Propyl alcohol	-	20 °C	🟢
Silicone oil	-	20 °C	🟢
Sodium carbonate, aqueous	-	20 °C	🟢
Sodium chloride, aqueous	-	20 °C	🟢
Sodium hydrogen sulfite	-	20 °C	🔴
Sodium hydroxide solution (15%)	15%	20 °C	🟢
Sodium hydroxide solution (60%)	60%	20 °C	🟡
Sodium nitrate, aqueous	-	20 °C	🟢
Sulphuric acid	96%	20 °C	🔴
Tetrahydrofuran (THF)	100%	20 °C	🟡
Toluene	100%	20 °C	🟢
Transformer oil	-	20 °C	🟢
Trichloroethylene	100%	20 °C	🟡
Vinegar, standard	5-10%	20 °C	🟢
Water	-	20 °C	🟢
Xylene	-	20 °C	🟢