POM H 3000x500x30 mm svart

Artikelnr P1008726

BestÃ□ndig Delvis bestÃ□ndig Ej bestÃ□ndig

Kemikalie	Koncentration	Temp.	BestÃ□ndighet
1,4-Dioxane	100%	20 Â°C	
2-Hydroxypropionic Acid	90%	20 Â°C	
Acetic Acid	100%	20 Â°C	
Acetone	100%	20 Â°C	
Ammonia	conc.	20 Â°C	
Ammonium Chloride	â€”	20 Â°C	
Amyl Alcohol	â€”	20 Â°C	
Apple Juice	â€”	20 Â°C	
Benzene	â€”	20 Â°C	
Bleaching Solution	12.5 cl	20 Â°C	
Boric Acid	100%	20 Â°C	
Brake Fluid	â€”	20 Â°C	
Butyl Acetate	â€”	20 Â°C	
Calcium Chloride	â€”	20 Â°C	
Carbon Disulfide	100%	20 Â°C	
Carbon Tetrachloride	â€”	20 Â°C	
Chlorine (gas)	100%	20 Â°C	
Chlorobenzene	100%	20 Â°C	
Chloroform	â€”	20 Â°C	
Citric Acid	10%	20 Â°C	
Cresol	â€”	20 Â°C	
Cyclohexanone	100%	20 Â°C	
Cyclohexene	100%	20 Â°C	
Diesel Fuel	â€”	20 Â°C	
Diethylene Oxide	â€”	20 Â°C	
Ethyl Acetate	100%	20 Â°C	
Ethyl Alcohol	96%	20 Â°C	

Kemikalie	Koncentration	Temp.	BestÃ□ndighet
Ethylene Chloride	100%	20 Â°C	🟢
Food Oil	â€”	20 Â°C	🟢
Formaldehyde, aqueous	40%	20 Â°C	🟢
Formic Acid	10%	20 Â°C	🟢
Frost Protection Agent	â€”	20 Â°C	🟢
Fuel, aromatic free	â€”	20 Â°C	🟢
Glycerine	100%	20 Â°C	🟢
Glycol	100%	20 Â°C	🟢
Heating Oil	â€”	20 Â°C	🟢
Heptane	100%	20 Â°C	🟢
Hydrochloric Acid	10%	20 Â°C	🔴
Hydrochloric Acid (concentrated)	conc.	20 Â°C	🔴
Hydrofluoric Acid	40%	20 Â°C	🔴
Hydrogen Peroxide	10%	20 Â°C	🟢
Hydrogen Sulfide, aqueous solution	â€”	20 Â°C	🟢
Isopropyl Alcohol	100%	20 Â°C	🟢
Linseed Oil	â€”	20 Â°C	🟢
Mercurochrome	â€”	20 Â°C	🔴
Methyl Alcohol	100%	20 Â°C	🟢
Methyl Ethyl Ketone (MEK)	100%	20 Â°C	🟡
Methylene Chloride	100%	20 Â°C	🔴
Milk	â€”	20 Â°C	🟢
Mineral Oils (aromatic free)	â€”	20 Â°C	🟢
Nitric Acid	10%	20 Â°C	🔴
Nitric Acid (50%)	50%	20 Â°C	🔴
Nitrobenzene	â€”	20 Â°C	🟡
Oxalic Acid	â€”	20 Â°C	🔴
Ozone Gas	â‰¤0.5 ppm	20 Â°C	🔴
Paraffine Oil	100%	20 Â°C	🟢
Perchloroethylene	â€”	20 Â°C	🟢
Petroleum	100%	20 Â°C	🟢
Petroleum Ether	100%	20 Â°C	🟢
Phenol, aqueous	ca. 9%	20 Â°C	🔴
Phosphoric Acid	50%	20 Â°C	🔴
Potassium Hydroxide liquor	50%	20 Â°C	🟡

Kemikalie	Koncentration	Temp.	BestÃ□ndighet
Premium Fuel	â€”	20 Â°C	
Propyl Alcohol	â€”	20 Â°C	
Pyridine	â€”	20 Â°C	
Silicone Oil	â€”	20 Â°C	
Sodium Carbonate, aqueous	â€”	20 Â°C	
Sodium Chloride, aqueous	â€”	20 Â°C	
Sodium Hydrogen Sulfite	â€”	20 Â°C	
Sodium Hydroxide liquor (15%)	15%	20 Â°C	
Sodium Hydroxide liquor (60%)	60%	20 Â°C	
Sodium Nitrate, aqueous	â€”	20 Â°C	
Sodium Thiosulfate	â€”	20 Â°C	
Sulfuric Acid	96%	20 Â°C	
Tetrahydrofuran, THF	100%	20 Â°C	
Toluene	100%	20 Â°C	
Transformer Oil	â€”	20 Â°C	
Trichloroethylene	100%	20 Â°C	
Vinegar, standard	5-10%	20 Â°C	
Water	â€”	20 Â°C	
Xylene	â€”	20 Â°C	

This document is for informational purposes only. Specifications may change without notice. Generated 2026-03-23