



PP-H 2000x1000x120 mm natur

Artikelnr P2201318

Beständig Delvis beständig Ej beständig

Kemikalie	Koncentration	Temp.	Beständighet
1,4-Dioxane	100	20 Å°C	
2-Hydroxypropionic acid (lactic acid)	90	20 Å°C	
Acetic acid	100	20 Å°C	
Acetone	100	20 Å°C	
Ammonia	â€”	20 Å°C	
Ammonium chloride	â€”	20 Å°C	
Amyl alcohol	â€”	20 Å°C	
Benzene	â€”	20 Å°C	
Bleaching solution	â€”	20 Å°C	
Boric acid	100	20 Å°C	
Brake fluid	â€”	20 Å°C	
Butyl acetate	â€”	20 Å°C	
Calcium chloride	â€”	20 Å°C	
Carbon disulphide	100	20 Å°C	
Carbon tetrachloride	â€”	20 Å°C	
Chlorine (gas)	100	20 Å°C	
Chlorobenzene	100	20 Å°C	
Chloroform	â€”	20 Å°C	
Citric acid	10	20 Å°C	
Cresol	â€”	20 Å°C	
Cyclohexanone	100	20 Å°C	
Cyclohexene	100	20 Å°C	
Diesel	â€”	20 Å°C	
Diethylene oxide	â€”	20 Å°C	
Ethyl acetate	100	20 Å°C	
Ethyl alcohol (ethanol)	96	20 Å°C	
Ethylene chloride	100	20 Å°C	

Kemikalie	Koncentrasjon	Temp.	BestÃndighet
Food oil	â€”	20 Â°C	🟢
Formaldehyde, aqueous	40	20 Â°C	🟢
Formic acid	10	20 Â°C	🟢
Frost protection agent	â€”	20 Â°C	🟢
Fuel oil	â€”	20 Â°C	🟢
Fuel, aromatic free	â€”	20 Â°C	🟢
Glycerine	100	20 Â°C	🟢
Glycol	100	20 Â°C	🟢
Heptane	100	20 Â°C	🟡
Hydrochloric acid	10	20 Â°C	🟢
Hydrochloric acid (concentrated)	â€”	20 Â°C	🟢
Hydrofluoric acid	40	20 Â°C	🟢
Hydrogen peroxide	10	20 Â°C	🟢
Hydrogen sulfide, aqueous	â€”	20 Â°C	🟢
Isopropyl alcohol	100	20 Â°C	🟢
Linseed oil	â€”	20 Â°C	🟢
Mercurochrome	â€”	20 Â°C	🟢
Methyl alcohol (methanol)	100	20 Â°C	🟢
Methyl ethyl ketone (MEK)	100	20 Â°C	🟢
Methylene chloride	100	20 Â°C	🟡
Milk	â€”	20 Â°C	🟢
Mineral oils (aromatic free)	â€”	20 Â°C	🟢
Nitric acid	50	20 Â°C	🔴
Nitric acid	10	20 Â°C	🟢
Nitrobenzene	â€”	20 Â°C	🟢
Oxalic acid	â€”	20 Â°C	🟢
Ozone (gas)	â‰¥ 0.5 ppm	20 Â°C	🔴
Paraffin oil	100	20 Â°C	🟢
Perchloroethylene	â€”	20 Â°C	🟡
Petroleum ether	100	20 Â°C	🟢
Phenol, aqueous	ca. 9	20 Â°C	🟢
Phosphoric acid	50	20 Â°C	🟢
Potassium hydroxide solution	50	20 Â°C	🟢
Premium fuel	â€”	20 Â°C	🟢
Propyl alcohol	â€”	20 Â°C	🟢

