



**PP-H 4000x2000x12 mm vit**

Artikelnr P2201515

| Kategori | PP |
|----------|----|
|----------|----|

## Tekniska egenskaper

## Density & Weight

| Egenskap | Värde | Enhet | Provningsstandard |
|----------|-------|-------|-------------------|
| Density  | 0.91  | g/cm³ | ISO 1183          |

## Tensile Properties

| Egenskap                        | VÄrde | Enhet | Provningsstandard |
|---------------------------------|-------|-------|-------------------|
| Tensile Strength                | 36    | MPa   | ISO 527           |
| Modulus of elasticity (tensile) | 1700  | MPa   | ISO 527-2         |
| Breakdown Voltage               | 30    | MPa   | ISO 527           |
| Break Elongation                | 8     | %     | ISO 527-2         |

## Temperature Limits

| Egenskap                                   | VÄrde | Enhet | Provningsstandard |
|--------------------------------------------|-------|-------|-------------------|
| Melting point                              | 161   | Å°C   | DIN EN ISO 11357  |
| Maximal operating temperature (short-term) | 127   | Å°C   | UL746B            |
| Maximum Operating Temperature              | 80    | Å°C   |                   |
| Minimum temperature                        | -7    | Å°C   |                   |
| Heat deflection temperature (HDT/A)        | 54    | Å°C   | ISO 75            |
| Heat deflection temperature (HDT/B)        | 90    | Å°C   | ISO 75            |
| Vicat softening temperature (VST/B/50)     | 50    | Å°C   | ISO 306           |

## Insulation Properties

| Egenskap                        | Värde     | Enhet                    | Provningsstandard |
|---------------------------------|-----------|--------------------------|-------------------|
| Dielectric Strength             | 40        | kV/mm                    | IEC 60243-1       |
| Volume Resistivity              | $10^{14}$ | $\Omega \cdot \text{cm}$ | DIN EN 62631-3-1  |
| Dielectric Constant (1 MHz)     | 2.4       | -                        | IEC 60250         |
| Dielectric loss factor (1 MHz)  | 13.4      | -                        | IEC 60250         |
| Dielectric loss factor (100 Hz) | 0.0       | -                        | IEC 60250         |

- EU 10/2011   FDA   REACH   RoHS

