



# PP-H AlphaPlus 2000x1000x30 mm grÅ¥

Artikelnr P2201041  
Kategori PP

## Tekniska egenskaper

### Density & Weight

| Egenskap | VÄrde | Enhet | Provningsstandard |
|----------|-------|-------|-------------------|
| Density  | 0.91  | g/cm³ | ISO 1183          |

### Tensile Properties

| Egenskap                        | VÄrde | Enhet | Provningsstandard |
|---------------------------------|-------|-------|-------------------|
| Tensile Strength                | 36    | MPa   | ISO 527           |
| Modulus of elasticity (tensile) | 1700  | MPa   | ISO 527-2         |
| Breakdown Voltage               | 30    | MPa   | ISO 527           |
| Break Elongation                | 8     | %     | ISO 527-2         |

### Temperature Limits

| Egenskap                                   | VÄrde | Enhet | Provningsstandard |
|--------------------------------------------|-------|-------|-------------------|
| Melting point                              | 161   | °C    | DIN EN ISO 11357  |
| Maximal operating temperature (short-term) | 127   | °C    | UL746B            |
| Maximum Operating Temperature              | 80    | °C    |                   |
| Minimum temperature                        | -7    | °C    |                   |
| Heat deflection temperature (HDT/A)        | 54    | °C    | ISO 75            |
| Heat deflection temperature (HDT/B)        | 90    | °C    | ISO 75            |
| Vicat softening temperature (VST/B/50)     | 50    | °C    | ISO 306           |

### Insulation Properties

| Egenskap                        | VÄrde | Enhet | Provningsstandard |
|---------------------------------|-------|-------|-------------------|
| Dielectric Strength             | 40    | kV/mm | IEC 60243-1       |
| Volume Resistivity              | 10¹³  | Ω·m   | DIN EN 62631-3-1  |
| Dielectric Constant (1 MHz)     | 2.4   | -     | IEC 60250         |
| Dielectric loss factor (1 MHz)  | 13.4  | -     | IEC 60250         |
| Dielectric loss factor (100 Hz) | 0.0   | -     | IEC 60250         |

## Flexural Properties

| Egenskap                            | VÄrde | Enhet | Provningsstandard |
|-------------------------------------|-------|-------|-------------------|
| Flammability Classification (UL 94) | 60695 |       | UL 94             |

## Static spread

| Egenskap                         | VÄrde               | Enhet | Provningsstandard |
|----------------------------------|---------------------|-------|-------------------|
| Surface Resistivity              | 10 <sup>10</sup> Å³ | Î©    | IEC 60093         |
| Comparative Tracking Index (CTI) | 600                 | V     | IEC 60112         |

### Water Absorption to Saturation

| Impact Resistance                |       |        |                   |
|----------------------------------|-------|--------|-------------------|
| Egenskap                         | VÄrde | Enhet  | Provningsstandard |
| Notched impact strength (Charpy) | 9     | kJ/mÅ² | ISO 179/1eA       |

## Hardness

| Egenskap               | V rde | Enhet     | Provningsstandard |
|------------------------|-------|-----------|-------------------|
| Hardness Shore D       | 72    |   Shore D | ISO 868           |
| Ball pressure hardness | 110   | MPa       | ISO 2039          |

# Godkännanden

