



PP-H AlphaPlus 4000x2000x8 mm grÃƒŸ

Artikelnr P2201065
Kategori PP

Tekniska egenskaper

Density & Weight

Egenskap	VÃƒrde	Enhet	Provningsstandard
Density	0.91	g/cmÃƒ³	ISO 1183

Tensile Properties

Egenskap	VÃƒrde	Enhet	Provningsstandard
Tensile Strength	36	MPa	ISO 527
Modulus of elasticity (tensile)	1700	MPa	ISO 527-2
Breakdown Voltage	30	MPa	ISO 527
Break Elongation	8	%	ISO 527-2

Temperature Limits

Egenskap	VÃƒrde	Enhet	Provningsstandard
Melting point	161	Ãƒ°C	DIN EN ISO 11357
Maximal operating temperature (short-term)	127	Ãƒ°C	UL746B
Maximum Operating Temperature	80	Ãƒ°C	
Minimum temperature	-7	Ãƒ°C	
Heat deflection temperature (HDT/A)	54	Ãƒ°C	ISO 75
Heat deflection temperature (HDT/B)	90	Ãƒ°C	ISO 75
Vicat softening temperature (VST/B/50)	50	Ãƒ°C	ISO 306

Insulation Properties

Egenskap	VÃƒrde	Enhet	Provningsstandard
Dielectric Strength	40	kV/mm	IEC 60243-1
Volume Resistivity	10Ãƒ¹Ãƒ¸	Î©	DIN EN 62631-3-1
Dielectric Constant (1 MHz)	2.4	-	IEC 60250
Dielectric loss factor (1 MHz)	13.4	-	IEC 60250
Dielectric loss factor (100 Hz)	0.0	-	IEC 60250

- EU 10/2011 FDA REACH RoHS

