



PTFE 1200x1200x8 mm natur

Artikelnr P1501524

Material PTFE

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Density	2.1	g/cm ³	ASTM D1457
Tensile Strength	22	MPa	ASTM D4894
Modulus of elasticity (tensile)	750	MPa	ISO 527
Breakdown Voltage	18	MPa	ASTM D1457
Break Elongation	300	%	ASTM D1457
Maximal operating temperature (short-term)	260	°C	
Maximum Operating Temperature	260	°C	
Minimum temperature	-200	°C	
Volume Resistivity	10 ⁴	Ω·cm	ASTM D257
Flexural Strength	6	MPa	ISO 178
Notched impact strength (Charpy)	16	kJ/m ²	ISO 179
Hardness Shore D	58.5	° Shore D	ASTM D1706
Ball pressure hardness	45	MPa	ISO 2039

2. Kemisk beständighet

● Beständig ● Delvis beständig ● Ej beständig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100	●
2-Hydroxypropionic Acid	90	●
Acetic Acid	100	●
Acetone	100	●
Ammonia	-	●
Ammonium Chloride	-	●
Amyl Alcohol	-	●
Apple Juice	-	●

Kemikalie	Konc.	Resultat
Benzene	-	●
Bleaching Solution	-	●
Boric Acid	100	●
Brake Fluid	-	●
Butyl Acetate	-	●
Calcium Chloride	-	●
Carbon Disulfide	100	●
Carbon Tetrachloride	-	●
Chlorine (gas)	100	●
Chlorobenzene	100	●
Chloroform	-	●
Citric Acid	10	●
Cresol	-	●
Cyclohexanone	100	●
Cyclohexene	100	●
Diesel Fuel	-	●
Diethylene Oxide	-	●
Ethyl Acetate	100	●
Ethyl Alcohol	96	●
Ethylene Chloride	100	●
Food Oil	-	●
Formaldehyde (aqueous)	40	●
Formic Acid	10	●
Frost Protection Agent	-	●
Fuel, aromatic free	-	●
Glycerine	100	●
Glycol	100	●
Heating Oil	-	●
Heptane	100	●
Hydrochloric Acid	10	●
Hydrochloric Acid (concentrated)	-	●
Hydrofluoric Acid	40	●
Hydrogen Peroxide	10	●
Hydrogen Sulfide (aqueous)	-	●
Isopropyl Alcohol	100	●

Kemikalie	Konc.	Resultat
Linseed Oil	-	●
Mercurochrome	-	●
Methyl Alcohol	100	●
Methyl Ethyl Ketone (MEK)	100	●
Methylene Chloride	100	●
Milk	-	●
Mineral Oils (aromatic free)	-	●
Nitric Acid	10	●
Nitric Acid (50%)	50	●
Nitrobenzene	-	●
Oxalic Acid	-	●
Ozone Gas	≤ 0.5 ppm	●
Paraffine Oil	100	●
Perchloroethylene	-	●
Petroleum	100	●
Petroleum Ether	100	●
Phenol (aqueous)	ca. 9	●
Phosphoric Acid	50	●
Potassium Hydroxide liquor	50	●
Premium Fuel	-	●
Propyl Alcohol	-	●
Pyridine	-	●
Silicone Oil	-	●
Sodium Carbonate (aqueous)	-	●
Sodium Chloride (aqueous)	-	●
Sodium Hydrogen Sulfite	-	●
Sodium Hydroxide liquor	15	●
Sodium Hydroxide liquor (60)	60	●
Sodium Nitrate (aqueous)	-	●
Sodium Thiosulfate	-	●
Sulfuric Acid	96	●
Tetrahydrofuran (THF)	100	●
Toluene	100	●
Transformer Oil	-	●

Kemikalie	Konc.	Resultat
Trichloroethylene	100	●
Vinegar (standard)	5 - 10	●
Water	-	●
Xylene	-	●