# PTFE 600x600x110 mm natural

Artikelnr P1203073

BestÃ¤ndig Delvis bestÃ¤ndig Ej bestÃ¤ndig

| Kemikalie | Koncentration | Temp. | BestÃ¤ndighet |
|---|---|---|---|
| 1,4-Dioxane | 100 | 20 Â°C | Delvis bestÃ¤ndig |
| 2-Hydroxypropionic Acid | 90 | 20 Â°C | BestÃ¤ndig |
| Acetic Acid | 100 | 20 Â°C | BestÃ¤ndig |
| Acetone | 100 | 20 Â°C | BestÃ¤ndig |
| Ammonia | â€” | 20 Â°C | BestÃ¤ndig |
| Ammonium Chloride | â€” | 20 Â°C | BestÃ¤ndig |
| Amyl Alcohol | â€” | 20 Â°C | BestÃ¤ndig |
| Apple Juice | â€” | 20 Â°C | BestÃ¤ndig |
| Benzene | â€” | 20 Â°C | BestÃ¤ndig |
| Bleaching Solution | â€” | 20 Â°C | Delvis bestÃ¤ndig |
| Boric Acid | 100 | 20 Â°C | BestÃ¤ndig |
| Brake Fluid | â€” | 20 Â°C | BestÃ¤ndig |
| Butyl Acetate | â€” | 20 Â°C | BestÃ¤ndig |
| Calcium Chloride | â€” | 20 Â°C | BestÃ¤ndig |
| Carbon Disulfide | 100 | 20 Â°C | BestÃ¤ndig |
| Carbon Tetrachloride | â€” | 20 Â°C | BestÃ¤ndig |
| Chlorine (gas) | 100 | 20 Â°C | BestÃ¤ndig |
| Chlorobenzene | 100 | 20 Â°C | BestÃ¤ndig |
| Chloroform | â€” | 20 Â°C | BestÃ¤ndig |
| Citric Acid | 10 | 20 Â°C | BestÃ¤ndig |
| Cresol | â€” | 20 Â°C | BestÃ¤ndig |
| Cyclohexanone | 100 | 20 Â°C | BestÃ¤ndig |
| Cyclohexene | 100 | 20 Â°C | BestÃ¤ndig |
| Diesel Fuel | â€” | 20 Â°C | BestÃ¤ndig |
| Diethylene Oxide | â€” | 20 Â°C | BestÃ¤ndig |
| Ethyl Acetate | 100 | 20 Â°C | BestÃ¤ndig |
| Ethyl Alcohol | 96 | 20 Â°C | BestÃ¤ndig |

| Kemikalie | Koncentration | Temp. | BestÃ¤ndighet |
|---|---|---|---|
| Ethylene Chloride | 100 | 20 Â°C | 🟢 |
| Food Oil | â€” | 20 Â°C | 🟢 |
| Formaldehyde (aqueous) | 40 | 20 Â°C | 🟢 |
| Formic Acid | 10 | 20 Â°C | 🟢 |
| Frost Protection Agent | â€” | 20 Â°C | 🟢 |
| Fuel, aromatic free | â€” | 20 Â°C | 🟢 |
| Glycerine | 100 | 20 Â°C | 🟢 |
| Glycol | 100 | 20 Â°C | 🟢 |
| Heating Oil | â€” | 20 Â°C | 🟢 |
| Heptane | 100 | 20 Â°C | 🟢 |
| Hydrochloric Acid | 10 | 20 Â°C | 🟢 |
| Hydrochloric Acid (concentrated) | â€” | 20 Â°C | 🟢 |
| Hydrofluoric Acid | 40 | 20 Â°C | 🟢 |
| Hydrogen Peroxide | 10 | 20 Â°C | 🟢 |
| Hydrogen Sulfide (aqueous) | â€” | 20 Â°C | 🟢 |
| Isopropyl Alcohol | 100 | 20 Â°C | 🟢 |
| Linseed Oil | â€” | 20 Â°C | 🟢 |
| Mercurochrome | â€” | 20 Â°C | 🟢 |
| Methyl Alcohol | 100 | 20 Â°C | 🟢 |
| Methyl Ethyl Ketone (MEK) | 100 | 20 Â°C | 🔴 |
| Methylene Chloride | 100 | 20 Â°C | 🟡 |
| Milk | â€” | 20 Â°C | 🟢 |
| Mineral Oils (aromatic free) | â€” | 20 Â°C | 🟢 |
| Nitric Acid | 10 | 20 Â°C | 🟢 |
| Nitric Acid (50%) | 50 | 20 Â°C | 🟢 |
| Nitrobenzene | â€” | 20 Â°C | 🟢 |
| Oxalic Acid | â€” | 20 Â°C | 🟢 |
| Ozone Gas | â‰¤ 0.5 ppm | 20 Â°C | 🟢 |
| Paraffine Oil | 100 | 20 Â°C | 🟢 |
| Perchloroethylene | â€” | 20 Â°C | 🟢 |
| Petroleum | 100 | 20 Â°C | 🟢 |
| Petroleum Ether | 100 | 20 Â°C | 🟢 |
| Phenol (aqueous) | ca. 9 | 20 Â°C | 🟢 |
| Phosphoric Acid | 50 | 20 Â°C | 🟢 |
| Potassium Hydroxide liquor | 50 | 20 Â°C | 🟢 |

| Kemikalie | Koncentration | Temp. | BestÃ¤ndighet |
|---|---|---|---|
| Premium Fuel | â€” | 20 Â°C | 🟢 |
| Propyl Alcohol | â€” | 20 Â°C | 🟢 |
| Pyridine | â€” | 20 Â°C | 🔴 |
| Silicone Oil | â€” | 20 Â°C | 🟢 |
| Sodium Carbonate (aqueous) | â€” | 20 Â°C | 🟢 |
| Sodium Chloride (aqueous) | â€” | 20 Â°C | 🟢 |
| Sodium Hydrogen Sulfite | â€” | 20 Â°C | 🟢 |
| Sodium Hydroxide liquor | 15 | 20 Â°C | 🟢 |
| Sodium Hydroxide liquor (60) | 60 | 20 Â°C | 🟢 |
| Sodium Nitrate (aqueous) | â€” | 20 Â°C | 🟢 |
| Sodium Thiosulfate | â€” | 20 Â°C | 🟢 |
| Sulfuric Acid | 96 | 20 Â°C | 🟢 |
| Tetrahydrofuran (THF) | 100 | 20 Â°C | 🟡 |
| Toluene | 100 | 20 Â°C | 🟢 |
| Transformer Oil | â€” | 20 Â°C | 🟢 |
| Trichloroethylene | 100 | 20 Â°C | 🟢 |
| Vinegar (standard) | 5 - 10 | 20 Â°C | 🟢 |
| Water | â€” | 20 Â°C | 🟢 |
| Xylene | â€” | 20 Â°C | 🟢 |



*This document is for informational purposes only. Specifications may change without notice. Generated 2026-03-16*