

## PVC U 2000x1000x2 mm dark grÅ

Artikelnr P2201902

● Beständig
 ● Delvis beständig
 ● Ej beständig

| Kemikalie                             | Koncentration | Temp.  | Beständighet |
|---------------------------------------|---------------|--------|--------------|
| 1,4-Dioxane                           | 100%          | 20 Å°C | ●            |
| 2-Hydroxypropionic acid (lactic acid) | 90%           | 20 Å°C | ●            |
| Acetic acid                           | 100%          | 20 Å°C | ●            |
| Acetone                               | 100%          | 20 Å°C | ●            |
| Ammonia                               | conc.         | 20 Å°C | ●            |
| Ammonium chloride                     | â€            | 20 Å°C | ●            |
| Amyl alcohol                          | â€            | 20 Å°C | ●            |
| Apple juice                           | â€            | 20 Å°C | ●            |
| Benzene                               | â€            | 20 Å°C | ●            |
| Bleaching solution                    | 12.5 cl       | 20 Å°C | ●            |
| Boric acid                            | 100%          | 20 Å°C | ●            |
| Brake fluid                           | â€            | 20 Å°C | ●            |
| Butyl acetate                         | â€            | 20 Å°C | ●            |
| Calcium chloride                      | â€            | 20 Å°C | ●            |
| Carbon disulphide                     | 100%          | 20 Å°C | ●            |
| Carbon tetrachloride                  | â€            | 20 Å°C | ●            |
| Chlorine (gas)                        | 100%          | 20 Å°C | ●            |
| Chlorobenzene                         | 100%          | 20 Å°C | ●            |
| Chloroform                            | â€            | 20 Å°C | ●            |
| Citric acid                           | 10%           | 20 Å°C | ●            |
| Cresol                                | â€            | 20 Å°C | ●            |
| Cyclohexanone                         | 100%          | 20 Å°C | ●            |
| Cyclohexene                           | 100%          | 20 Å°C | ●            |
| Diesel                                | â€            | 20 Å°C | ●            |
| Diethylene oxide                      | â€            | 20 Å°C | ●            |
| Ethyl acetate                         | 100%          | 20 Å°C | ●            |
| Ethyl alcohol (ethanol)               | 96%           | 20 Å°C | ●            |

| Kemikalie                        | Koncentration | Temp. | Best ndighet |
|----------------------------------|---------------|-------|--------------|
| Ethylene chloride                | 100%          | 20  C | ●            |
| Food oil                         |               | 20  C | ●            |
| Formaldehyde (aqueous)           | 40%           | 20  C | ●            |
| Formic acid                      | 10%           | 20  C | ●            |
| Frost protection agent           |               | 20  C | ●            |
| Fuel (aromatic free)             |               | 20  C | ●            |
| Fuel oil                         |               | 20  C | ●            |
| Glycerine                        | 100%          | 20  C | ●            |
| Glycol                           | 100%          | 20  C | ●            |
| Heptane                          | 100%          | 20  C | ●            |
| Hydrochloric acid                | 10%           | 20  C | ●            |
| Hydrochloric acid (concentrated) | conc.         | 20  C | ●            |
| Hydrofluoric acid                | 40%           | 20  C | ●            |
| Hydrogen peroxide                | 10%           | 20  C | ●            |
| Hydrogen sulfide (aqueous)       |               | 20  C | ●            |
| Isopropyl alcohol                | 100%          | 20  C | ●            |
| Linseed oil                      |               | 20  C | ●            |
| Mercurochrome                    |               | 20  C | ●            |
| Methyl alcohol (methanol)        | 100%          | 20  C | ●            |
| Methyl ethyl ketone (MEK)        | 100%          | 20  C | ●            |
| Methylene chloride               | 100%          | 20  C | ●            |
| Milk                             |               | 20  C | ●            |
| Mineral oils (aromatic free)     |               | 20  C | ●            |
| Nitric acid                      | 50%           | 20  C | ●            |
| Nitric acid                      | 10%           | 20  C | ●            |
| Nitrobenzene                     |               | 20  C | ●            |
| Oxalic acid                      |               | 20  C | ●            |
| Ozone (gas)                      |    0.5 ppm    | 20  C | ●            |
| Paraffin oil                     | 100%          | 20  C | ●            |
| Perchloroethylene                |               | 20  C | ●            |
| Petroleum                        | 100%          | 20  C | ●            |
| Petroleum ether                  | 100%          | 20  C | ●            |
| Phenol (aqueous)                 | ca. 9%        | 20  C | ●            |
| Phosphoric acid                  | 50%           | 20  C | ●            |
| Potassium hydroxide solution     | 50%           | 20  C | ●            |

| Kemikalie                                | Koncentration | Temp. | Best ndighet |
|------------------------------------------|---------------|-------|--------------|
| Premium fuel                             |               | 20  C |              |
| Propyl alcohol                           |               | 20  C |              |
| Pyridine                                 |               | 20  C |              |
| Silicone oil                             |               | 20  C |              |
| Sodium carbonate (aqueous)               |               | 20  C |              |
| Sodium chloride (aqueous)                |               | 20  C |              |
| Sodium hydrogen sulfite                  |               | 20  C |              |
| Sodium hydroxide solution (caustic soda) | 15%           | 20  C |              |
| Sodium hydroxide solution (caustic soda) | 60%           | 20  C |              |
| Sodium nitrate (aqueous)                 |               | 20  C |              |
| Sodium thiosulfate                       |               | 20  C |              |
| Sulphuric acid                           | 96%           | 20  C |              |
| Tetrahydrofuran (THF)                    | 100%          | 20  C |              |
| Toluene                                  | 100%          | 20  C |              |
| Transformer oil                          |               | 20  C |              |
| Trichloroethylene                        | 100%          | 20  C |              |
| Vinegar (standard)                       | 5 - 10%       | 20  C |              |
| Water                                    |               | 20  C |              |
| Xylene                                   |               | 20  C |              |