



# PVC U 3000x1500x6 mm dark grÅ

Artikelnr P2201923

● Beständig

● Delvis beständig

● Ej beständig

| Kemikalie                             | Koncentration | Temp.  | Beständighet |
|---------------------------------------|---------------|--------|--------------|
| 1,4-Dioxane                           | 100%          | 20 Å°C | ●            |
| 2-Hydroxypropionic acid (lactic acid) | 90%           | 20 Å°C | ●            |
| Acetic acid                           | 100%          | 20 Å°C | ●            |
| Acetone                               | 100%          | 20 Å°C | ●            |
| Ammonia                               | conc.         | 20 Å°C | ●            |
| Ammonium chloride                     | â€”           | 20 Å°C | ●            |
| Amyl alcohol                          | â€”           | 20 Å°C | ●            |
| Apple juice                           | â€”           | 20 Å°C | ●            |
| Benzene                               | â€”           | 20 Å°C | ●            |
| Bleaching solution                    | 12.5 cl       | 20 Å°C | ●            |
| Boric acid                            | 100%          | 20 Å°C | ●            |
| Brake fluid                           | â€”           | 20 Å°C | ●            |
| Butyl acetate                         | â€”           | 20 Å°C | ●            |
| Calcium chloride                      | â€”           | 20 Å°C | ●            |
| Carbon disulphide                     | 100%          | 20 Å°C | ●            |
| Carbon tetrachloride                  | â€”           | 20 Å°C | ●            |
| Chlorine (gas)                        | 100%          | 20 Å°C | ●            |
| Chlorobenzene                         | 100%          | 20 Å°C | ●            |
| Chloroform                            | â€”           | 20 Å°C | ●            |
| Citric acid                           | 10%           | 20 Å°C | ●            |
| Cresol                                | â€”           | 20 Å°C | ●            |
| Cyclohexanone                         | 100%          | 20 Å°C | ●            |
| Cyclohexene                           | 100%          | 20 Å°C | ●            |
| Diesel                                | â€”           | 20 Å°C | ●            |
| Diethylene oxide                      | â€”           | 20 Å°C | ●            |
| Ethyl acetate                         | 100%          | 20 Å°C | ●            |
| Ethyl alcohol (ethanol)               | 96%           | 20 Å°C | ●            |

| Kemikalie                        | Koncentration | Temp.  | Best ndighet |
|----------------------------------|---------------|--------|--------------|
| Ethylene chloride                | 100%          | 20   C |              |
| Food oil                         |               | 20   C |              |
| Formaldehyde (aqueous)           | 40%           | 20   C |              |
| Formic acid                      | 10%           | 20   C |              |
| Frost protection agent           |               | 20   C |              |
| Fuel (aromatic free)             |               | 20   C |              |
| Fuel oil                         |               | 20   C |              |
| Glycerine                        | 100%          | 20   C |              |
| Glycol                           | 100%          | 20   C |              |
| Heptane                          | 100%          | 20   C |              |
| Hydrochloric acid                | 10%           | 20   C |              |
| Hydrochloric acid (concentrated) | conc.         | 20   C |              |
| Hydrofluoric acid                | 40%           | 20   C |              |
| Hydrogen peroxide                | 10%           | 20   C |              |
| Hydrogen sulfide (aqueous)       |               | 20   C |              |
| Isopropyl alcohol                | 100%          | 20   C |              |
| Linseed oil                      |               | 20   C |              |
| Mercurochrome                    |               | 20   C |              |
| Methyl alcohol (methanol)        | 100%          | 20   C |              |
| Methyl ethyl ketone (MEK)        | 100%          | 20   C |              |
| Methylene chloride               | 100%          | 20   C |              |
| Milk                             |               | 20   C |              |
| Mineral oils (aromatic free)     |               | 20   C |              |
| Nitric acid                      | 50%           | 20   C |              |
| Nitric acid                      | 10%           | 20   C |              |
| Nitrobenzene                     |               | 20   C |              |
| Oxalic acid                      |               | 20   C |              |
| Ozone (gas)                      |     0.5 ppm   | 20   C |              |
| Paraffin oil                     | 100%          | 20   C |              |
| Perchloroethylene                |               | 20   C |              |
| Petroleum                        | 100%          | 20   C |              |
| Petroleum ether                  | 100%          | 20   C |              |
| Phenol (aqueous)                 | ca. 9%        | 20   C |              |
| Phosphoric acid                  | 50%           | 20   C |              |
| Potassium hydroxide solution     | 50%           | 20   C |              |

