



## PA6 GF30 180x1000 mm svart

Artikelnr P1001431

Kategori PA

### Tekniska egenskaper

#### Density & Weight

Egenskap	VÄrde	Enhet	Provningsstandard
Density	1.34	g/cm <sup>3</sup>	ISO 1183

#### Tensile Properties

Egenskap	VÄrde	Enhet	Provningsstandard
Modulus of elasticity (tensile)	8700	MPa	ISO 527-2

#### Temperature Limits

Egenskap	VÄrde	Enhet	Provningsstandard
Melting point	220	Å°C	ISO 3146
Maximal operating temperature (short-term)	180	Å°C	
Maximum Operating Temperature	100	Å°C	
Minimum temperature	-20	Å°C	
Heat deflection temperature (HDT/A)	210	Å°C	ISO 75-2

#### Insulation Properties

Egenskap	VÄrde	Enhet	Provningsstandard
Volume Resistivity	10 <sup>14</sup> Å	Î@Å·cm	IEC 60093

#### Flexural Properties

Egenskap	VÄrde	Enhet	Provningsstandard
Flexural Strength	120	MPa	ISO 527-2

## Thermal Conductivity

Egenskap	V�rde	Enhet	Provningsstandard
Thermal Conductivity	0.28	W/(m�K)	DIN 52612

## Static spread

Egenskap	V�rde	Enhet	Provningsstandard
Surface Resistivity	10���	�	IEC 60093

## Moisture Absorption

Egenskap	V�rde	Enhet	Provningsstandard
Water absorption to saturation	2.1	%	ISO 62
Water Absorption to Saturation	6.6	%	ISO 62

## Impact Resistance

Egenskap	V�rde	Enhet	Provningsstandard
Notched impact strength (Charpy)	5	kJ/m��	ISO 179/1eA
Impact Resistance (Charpy)	50	kJ/m��	ISO 179/1eU

## Thermal Expansion

Egenskap	V�rde	Enhet	Provningsstandard
Thermal Expansion Coefficient	0.26	10��/K	DIN 11359

## Hardness

Egenskap	V�rde	Enhet	Provningsstandard
Ball pressure hardness	43	MPa	ISO 2039-1

## Godk nnanden

REACH

RoHS