



PA6.6 FG 60x3000 mm natur

Artikelnr P1002358
Kategori PA

Tekniska egenskaper

Density & Weight

Egenskap	V�rde	Enhet	Provningsstandard
Density	1.14	g/cm���	ISO 1183

Tensile Properties

Egenskap	V�rde	Enhet	Provningsstandard
Tensile Strength	80	MPa	ISO 527
Modulus of elasticity (tensile)	3285	MPa	ISO 527-2
Break Elongation	55	%	ISO 527-2

Temperature Limits

Egenskap	V�rde	Enhet	Provningsstandard
Melting point	260	��C	ISO 3146
Maximal operating temperature (short-term)	140	��C	UL746B
Maximum Operating Temperature	95	��C	
Minimum temperature	-30	��C	
Heat deflection temperature (HDT/A)	92.5	��C	ISO 75-2
Heat deflection temperature (HDT/B)	200	��C	ISO 75-2

Insulation Properties

Egenskap	V�rde	Enhet	Provningsstandard
Dielectric Strength	28.5	kV/mm	IEC 60243-1
Volume Resistivity	~10�����	�������	IEC 60093

Egenskap	VÄrde	Enhet	Provningsstandard
Dielectric Constant (1 MHz)	3.45	-	IEC 60250
Dielectric Constant (100 Hz)	3.8	-	IEC 60250
Dielectric loss factor (1 MHz)	0.11	-	IEC 60250
Dielectric loss factor (100 Hz)	0.0	-	IEC 60250

Flexural Properties

Egenskap	VÄrde	Enhet	Provningsstandard
Flexural Strength	1455	MPa	ISO 178

Thermal Conductivity

Egenskap	VÄrde	Enhet	Provningsstandard
Thermal Conductivity	0.28	W/(mÂ·K)	DIN 52612

Static spread

Egenskap	VÄrde	Enhet	Provningsstandard
Surface Resistivity	10Â¹Â³	Î©	IEC 60093
Comparative Tracking Index (CTI)	600	V	IEC 60112

Moisture Absorption

Egenskap	VÄrde	Enhet	Provningsstandard
Water absorption to saturation	5.45	%	ISO 62
Water Absorption to Saturation	8.75	%	ISO 62

Impact Resistance

Egenskap	VÄrde	Enhet	Provningsstandard
Notched impact strength (Charpy)	6	kJ/mÂ²	ISO 179/1eA

Thermal Expansion

Egenskap	VÄrde	Enhet	Provningsstandard
Thermal Expansion Coefficient	0.8	10â»/K	DIN 11359

Hardness

Egenskap	VÄrde	Enhet	Provningsstandard
Hardness Shore D	83	Â° Shore D	ISO 868
Ball pressure hardness	160	MPa	ISO 2039-1

Godk nnanden

EU 10/2011 FDA REACH RoHS