



PA6.6 GF30 28x1000 mm svart

Artikelnr P1002483  
Material PA

1. Tekniskt datablad

| Egenskap                                   | Värde             | Enhet               | Standard    |
|--------------------------------------------|-------------------|---------------------|-------------|
| Density                                    | 1.3               | g/cm³               | ISO 1183    |
| Tensile Strength                           | 100               | MPa                 | ISO 527     |
| Modulus of elasticity (tensile)            | 5900              | MPa                 | ISO 527-2   |
| Breakdown Voltage                          | 100               | MPa                 | ISO 527-2   |
| Break Elongation                           | 5                 | %                   | ISO 527-2   |
| Melting point                              | 257.5             | °C                  | ISO 3146    |
| Maximal operating temperature (short-term) | 175               | °C                  | UL746B      |
| Maximum Operating Temperature              | 120               | °C                  |             |
| Minimum temperature                        | -20               | °C                  |             |
| Heat deflection temperature (HDT/A)        | 150               | °C                  | ISO 75-2    |
| Heat deflection temperature (HDT/B)        | 250               | °C                  | ISO 75      |
| Dielectric Strength                        | 30                | kV/mm               | IEC 60243-1 |
| Volume Resistivity                         | ~10 <sup>14</sup> | Ω·cm                | IEC 60093   |
| Dielectric Constant (1 MHz)                | 3.6               | -                   | IEC 60250   |
| Dielectric loss factor (1 MHz)             | 0.0               | -                   | IEC 60250   |
| Thermal Conductivity                       | 0.31              | W/(m·K)             | DIN 52612   |
| Surface Resistivity                        | ~10 <sup>13</sup> | Ω                   | IEC 60093   |
| Comparative Tracking Index (CTI)           | 475               | V                   | IEC 60112   |
| Water absorption to saturation             | 3.6               | %                   | ISO 62      |
| Water Absorption to Saturation             | 5.5               | %                   | ISO 62      |
| Notched impact strength (Charpy)           | 6                 | kJ/m²               | ISO 179/1eA |
| Impact Resistance (Charpy)                 | 50                | kJ/m²               | ISO 179/1eU |
| Thermal Expansion Coefficient              | 0.5               | 10 <sup>-4</sup> /K | ISO 11359   |
| Hardness Shore D                           | 85                | ° Shore D           | ISO 868     |
| Ball pressure hardness                     | 165               | MPa                 | ISO 2039-1  |

## 2. Kemisk beständighet

● Beständig    ● Delvis beständig    ● Ej beständig

| Kemikalie               | Konc.   | Resultat       |
|-------------------------|---------|----------------|
| 1,4-Dioxane             | 100     | <span>●</span> |
| 2-Hydroxypropionic Acid | 90      | <span>●</span> |
| Acetic Acid             | 100     | <span>●</span> |
| Acetone                 | 100     | <span>●</span> |
| Ammonia                 | conc.   | <span>●</span> |
| Ammonium Chloride       | -       | <span>●</span> |
| Amyl Alcohol            | -       | <span>●</span> |
| Apple Juice             | -       | <span>●</span> |
| Benzene                 | -       | <span>●</span> |
| Bleaching Solution      | 12.5 cl | <span>●</span> |
| Boric Acid              | 100     | <span>●</span> |
| Brake Fluid             | -       | <span>●</span> |
| Butyl Acetate           | -       | <span>●</span> |
| Calcium Chloride        | -       | <span>●</span> |
| Carbon Disulfide        | 100     | <span>●</span> |
| Carbon Tetrachloride    | -       | <span>●</span> |
| Chlorine (gas)          | 100     | <span>●</span> |
| Chlorobenzene           | 100     | <span>●</span> |
| Chloroform              | -       | <span>●</span> |
| Citric Acid             | 10      | <span>●</span> |
| Cresol                  | -       | <span>●</span> |
| Cyclohexanone           | 100     | <span>●</span> |
| Cyclohexene             | 100     | <span>●</span> |
| Diesel Fuel             | -       | <span>●</span> |
| Diethylene Oxide        | -       | <span>●</span> |
| Ethyl Acetate           | 100     | <span>●</span> |
| Ethyl Alcohol           | 96      | <span>●</span> |
| Ethylene Chloride       | 100     | <span>●</span> |
| Food Oil                | -       | <span>●</span> |
| Formaldehyde (aqueous)  | 40      | <span>●</span> |
| Formic Acid             | 10      | <span>●</span> |
| Frost Protection Agent  | -       | <span>●</span> |

| Kemikalie                        | Konc.     | Resultat    |
|----------------------------------|-----------|-------------|
| Fuel (aromatic free)             | -         | <div></div> |
| Glycerine                        | 100       | <div></div> |
| Glycol                           | 100       | <div></div> |
| Heating Oil                      | -         | <div></div> |
| Heptane                          | 100       | <div></div> |
| Hydrochloric Acid                | 10        | <div></div> |
| Hydrochloric Acid (concentrated) | conc.     | <div></div> |
| Hydrofluoric Acid                | 40        | <div></div> |
| Hydrogen Peroxide                | 10        | <div></div> |
| Hydrogen Sulfide (aqueous)       | -         | <div></div> |
| Isopropyl Alcohol                | 100       | <div></div> |
| Linseed Oil                      | -         | <div></div> |
| Mercurochrome                    | -         | <div></div> |
| Methyl Alcohol                   | 100       | <div></div> |
| Methyl Ethyl Ketone (MEK)        | 100       | <div></div> |
| Methylene Chloride               | 100       | <div></div> |
| Milk                             | -         | <div></div> |
| Mineral Oils (aromatic free)     | -         | <div></div> |
| Nitric Acid                      | 10        | <div></div> |
| Nitric Acid                      | 50        | <div></div> |
| Nitrobenzene                     | -         | <div></div> |
| Oxalic Acid                      | -         | <div></div> |
| Ozone Gas                        | ≤ 0.5 ppm | <div></div> |
| Paraffine Oil                    | 100       | <div></div> |
| Perchloroethylene                | -         | <div></div> |
| Petroleum                        | 100       | <div></div> |
| Petroleum Ether                  | 100       | <div></div> |
| Phenol (aqueous)                 | ca. 9     | <div></div> |
| Phosphoric Acid                  | 50        | <div></div> |
| Potassium Hydroxide liquor       | 50        | <div></div> |
| Premium Fuel                     | -         | <div></div> |
| Propyl Alcohol                   | -         | <div></div> |
| Pyridine                         | -         | <div></div> |
| Silicone Oil                     | -         | <div></div> |

| Kemikalie                  | Konc.  | Resultat |
|----------------------------|--------|----------|
| Sodium Carbonate (aqueous) | -      | ●        |
| Sodium Chloride (aqueous)  | -      | ●        |
| Sodium Hydrogen Sulfite    | -      | ●        |
| Sodium Hydroxide liquor    | 60     | ●        |
| Sodium Hydroxide liquor    | 15     | ●        |
| Sodium Nitrate (aqueous)   | -      | ●        |
| Sodium Thiosulfate         | -      | ●        |
| Sulfuric Acid              | 96     | ●        |
| Tetrahydrofuran (THF)      | 100    | ●        |
| Toluene                    | 100    | ●        |
| Transformer Oil            | -      | ●        |
| Trichloroethylene          | 100    | ●        |
| Vinegar (standard)         | 5 - 10 | ●        |
| Water                      | -      | ●        |
| Xylene                     | -      | ●        |