



Artikelnr P1002803

| Egenskap                                   | V rde                           | Enhet              | Standard    |
|--------------------------------------------|---------------------------------|--------------------|-------------|
| Density                                    | 1.2                             | g/cm  <sup>3</sup> | ISO 1183    |
| Tensile Strength                           | 75                              | MPa                | ISO 527     |
| Modulus of elasticity (tensile)            | 2400                            | MPa                | ISO 527-2   |
| Breakdown Voltage                          | 60                              | MPa                |             |
| Break Elongation                           | 50                              | %                  | ISO 527-2   |
| Melting point                              | 160                             |   C                | ISO 3146    |
| Maximal operating temperature (short-term) | 119                             |   C                | UL746B      |
| Maximum Operating Temperature              | 113.75                          |   C                |             |
| Minimum temperature                        | -54                             |   C                | UL746B      |
| Heat deflection temperature (HDT/A)        | 130                             |   C                | ISO 75-2    |
| Heat deflection temperature (HDT/B)        | 140                             |   C                | ISO 75      |
| Vicat softening temperature (VST/B/50)     | 150                             |   C                | ISO 306     |
| Dielectric Strength                        | 29                              | kV/mm              | IEC 60243-1 |
| Volume Resistivity                         | 10  <sup>1</sup>   <sup>3</sup> |       cm           | IEC 60093   |
| Dielectric Constant (1 MHz)                | 2.98                            | -                  | IEC 60250   |
| Dielectric Constant (100 Hz)               | 3                               | -                  | IEC 60250   |
| Dielectric loss factor (1 MHz)             | 0.0                             | -                  | IEC 60250   |
| Dielectric loss factor (100 Hz)            | 0.0                             | -                  | IEC 60250   |
| Flammability Classification (UL 94)        | 0                               |                    | UL 94       |
| Flexural Strength                          | 2400                            | MPa                | ISO 178     |
| Thermal Conductivity                       | 0.21                            | W/(m  K)           | DIN 52612   |
| Surface Resistivity                        | 10  <sup>1</sup>                |                    | IEC 60093   |
| Comparative Tracking Index (CTI)           | 279.2                           | V                  | IEC 60112   |
| Water absorption to saturation             | 0.15                            | %                  | ISO 62      |
| Water Absorption to Saturation             | 0.35                            | %                  | ISO 62      |
| Notched impact strength (Charpy)           | 9                               | kJ/m  <sup>2</sup> | ISO 179/1eA |
| Thermal Expansion Coefficient              | 0.65                            | 10      /K         | DIN 11359   |

| Egenskap               | V rde | Enhet     | Standard   |
|------------------------|-------|-----------|------------|
| Hardness Shore D       | 85    |   Shore D | ISO 868    |
| Ball pressure hardness | 120   | MPa       | ISO 2039-1 |

2. Kemisk best ndighet

● Best ndig ● Delvis best ndig ● Ej best ndig

| Kemikalie                             | Konc.   | Resultat |
|---------------------------------------|---------|----------|
| 1,4-Dioxane                           | 100%    | ●        |
| 2-Hydroxypropionic acid (lactic acid) | 90%     | ●        |
| Acetic acid                           | 100%    | ●        |
| Acetone                               | 100%    | ●        |
| Ammonia                               | conc.   | ●        |
| Ammonium chloride                     |         | ●        |
| Apple juice                           |         | ●        |
| Benzene                               |         | ●        |
| Bleaching solution                    | 12.5 cl | ●        |
| Boric acid                            | 100%    | ●        |
| Butyl acetate                         |         | ●        |
| Calcium chloride                      |         | ●        |
| Carbon disulphide                     | 100%    | ●        |
| Carbon tetrachloride                  |         | ●        |
| Chlorine (gas)                        | 100%    | ●        |
| Chlorobenzene                         | 100%    | ●        |
| Chloroform                            |         | ●        |
| Citric acid                           | 10%     | ●        |
| Cresol                                |         | ●        |
| Cyclohexanone                         | 100%    | ●        |
| Cyclohexene                           | 100%    |          |
| Diesel                                |         | ●        |
| Diethylene oxide                      |         |          |
| Ethyl acetate                         | 100%    |          |
| Ethyl alcohol (ethanol)               | 96%     | ●        |
| Ethylene chloride                     | 100%    |          |
| Food oil                              |         | ●        |
| Formaldehyde, aqueous                 | 40%     | ●        |

| Kemikalie                        | Konc.       | Resultat |
|----------------------------------|-------------|----------|
|                                  |             |          |
| Formic acid                      | 10%         | ●        |
| Frost protection agent           | â€”         | ●        |
| Fuel oil                         | â€”         | ●        |
| Fuel, aromatic free              | â€”         | ●        |
| Glycerine                        | 100%        | ●        |
| Glycol                           | 100%        | ●        |
| Heptane                          | 100%        | ●        |
| Hydrochloric acid                | 10%         | ●        |
| Hydrochloric acid (concentrated) | conc.       | ●        |
| Hydrofluoric acid                | 40%         | ●        |
| Hydrogen peroxide                | 10%         | ●        |
| Hydrogen sulfide, aqueous        | â€”         | ●        |
| Isopropyl alcohol                | 100%        | ●        |
| Linseed oil                      | â€”         | ●        |
| Mercurochrome                    | â€”         | ●        |
| Methyl alcohol (methanol)        | 100%        | ●        |
| Methyl ethyl ketone (MEK)        | 100%        | ●        |
| Methylene chloride               | 100%        | ●        |
| Milk                             | â€”         | ●        |
| Nitric acid (10%)                | 10%         | ●        |
| Nitric acid (50%)                | 50%         | ●        |
| Nitrobenzene                     | â€”         | ●        |
| Oxalic acid                      | â€”         | ●        |
| Ozone (gas)                      | â‰‰ 0.5 ppm | ●        |
| Paraffin oil                     | 100%        | ●        |
| Perchloroethylene                | â€”         | ●        |
| Petroleum                        | 100%        | ●        |
| Petroleum ether                  | 100%        | ●        |
| Phenol, aqueous                  | ca. 9%      | ●        |
| Phosphoric acid                  | 50%         | ●        |
| Potassium hydroxide solution     | 50%         | ●        |
| Premium fuel                     | â€”         | ●        |
| Propyl alcohol                   | â€”         | ●        |
| Pyridine                         | â€”         | ●        |

| Kemikalie                       | Konc. | Resultat |
|---------------------------------|-------|----------|
| Silicone oil                    | â€”   | ●        |
| Sodium carbonate, aqueous       | â€”   | ●        |
| Sodium chloride, aqueous        | â€”   | ●        |
| Sodium hydrogen sulfite         | â€”   | ●        |
| Sodium hydroxide solution (15%) | 15%   | ●        |
| Sodium hydroxide solution (60%) | 60%   | ●        |
| Sodium nitrate, aqueous         | â€”   | ●        |
| Sulphuric acid                  | 96%   | ●        |
| Tetrahydrofuran (THF)           | 100%  | ●        |
| Toluene                         | 100%  | ●        |
| Trichloroethylene               | 100%  | ●        |
| Vinegar, standard               | 5-10% | ●        |
| Water                           | â€”   | ●        |
| Xylene                          | â€”   | ●        |