



Artikelnr P1002823

Egenskap	V�rde	Enhet	Standard
Density	1.2	g/cm� ³	ISO 1183
Tensile Strength	75	MPa	ISO 527
Modulus of elasticity (tensile)	2400	MPa	ISO 527-2
Breakdown Voltage	60	MPa	
Break Elongation	50	%	ISO 527-2
Melting point	160	��C	ISO 3146
Maximal operating temperature (short-term)	119	��C	UL746B
Maximum Operating Temperature	113.75	��C	
Minimum temperature	-54	��C	UL746B
Heat deflection temperature (HDT/A)	130	��C	ISO 75-2
Heat deflection temperature (HDT/B)	140	��C	ISO 75
Vicat softening temperature (VST/B/50)	150	��C	ISO 306
Dielectric Strength	29	kV/mm	IEC 60243-1
Volume Resistivity	10� ¹¹ �� ³	����������	IEC 60093
Dielectric Constant (1 MHz)	2.98	-	IEC 60250
Dielectric Constant (100 Hz)	3	-	IEC 60250
Dielectric loss factor (1 MHz)	0.0	-	IEC 60250
Dielectric loss factor (100 Hz)	0.0	-	IEC 60250
Flammability Classification (UL 94)	0		UL 94
Flexural Strength	2400	MPa	ISO 178
Thermal Conductivity	0.21	W/(m���K)	DIN 52612
Surface Resistivity	10� ¹¹ ��	���	IEC 60093
Comparative Tracking Index (CTI)	279.2	V	IEC 60112
Water absorption to saturation	0.15	%	ISO 62
Water Absorption to Saturation	0.35	%	ISO 62
Notched impact strength (Charpy)	9	kJ/m� ²	ISO 179/1eA
Thermal Expansion Coefficient	0.65	10� ⁻⁶ ���/K	DIN 11359

Egenskap	V�rde	Enhet	Standard
Hardness Shore D	85	� Shore D	ISO 868
Ball pressure hardness	120	MPa	ISO 2039-1

2. Kemisk best ndighet

● Best ndig ● Delvis best ndig ● Ej best ndig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100%	●
2-Hydroxypropionic acid (lactic acid)	90%	●
Acetic acid	100%	●
Acetone	100%	●
Ammonia	conc.	●
Ammonium chloride	���	●
Apple juice	���	●
Benzene	���	●
Bleaching solution	12.5 cl	●
Boric acid	100%	●
Butyl acetate	���	●
Calcium chloride	���	●
Carbon disulphide	100%	●
Carbon tetrachloride	���	●
Chlorine (gas)	100%	●
Chlorobenzene	100%	●
Chloroform	���	●
Citric acid	10%	●
Cresol	���	●
Cyclohexanone	100%	●
Cyclohexene	100%	�
Diesel	���	●
Diethylene oxide	���	�
Ethyl acetate	100%	�
Ethyl alcohol (ethanol)	96%	●
Ethylene chloride	100%	�
Food oil	���	●
Formaldehyde, aqueous	40%	●

Kemikalie	Konc.	Resultat
Formic acid	10%	●
Frost protection agent	â€”	●
Fuel oil	â€”	●
Fuel, aromatic free	â€”	●
Glycerine	100%	●
Glycol	100%	●
Heptane	100%	●
Hydrochloric acid	10%	●
Hydrochloric acid (concentrated)	conc.	●
Hydrofluoric acid	40%	●
Hydrogen peroxide	10%	●
Hydrogen sulfide, aqueous	â€”	●
Isopropyl alcohol	100%	●
Linseed oil	â€”	●
Mercurochrome	â€”	●
Methyl alcohol (methanol)	100%	●
Methyl ethyl ketone (MEK)	100%	●
Methylene chloride	100%	●
Milk	â€”	●
Nitric acid (10%)	10%	●
Nitric acid (50%)	50%	●
Nitrobenzene	â€”	●
Oxalic acid	â€”	●
Ozone (gas)	â‰‰ 0.5 ppm	●
Paraffin oil	100%	●
Perchloroethylene	â€”	●
Petroleum	100%	●
Petroleum ether	100%	●
Phenol, aqueous	ca. 9%	●
Phosphoric acid	50%	●
Potassium hydroxide solution	50%	●
Premium fuel	â€”	●
Propyl alcohol	â€”	●
Pyridine	â€”	●

Kemikalie	Konc.	Resultat
Silicone oil	â€”	●
Sodium carbonate, aqueous	â€”	●
Sodium chloride, aqueous	â€”	●
Sodium hydrogen sulfite	â€”	●
Sodium hydroxide solution (15%)	15%	●
Sodium hydroxide solution (60%)	60%	●
Sodium nitrate, aqueous	â€”	●
Sulphuric acid	96%	●
Tetrahydrofuran (THF)	100%	●
Toluene	100%	●
Trichloroethylene	100%	●
Vinegar, standard	5-10%	●
Water	â€”	●
Xylene	â€”	●