



## PC 150x1000 mm transparent

Artikelnr    P1002630

Material    PC

### Tekniska egenskaper

#### Density & Weight

| Egenskap | Värde | Enhet | Provningsstandard |
|----------|-------|-------|-------------------|
| Density  | 1.2   | g/cm³ | ISO 1183          |

#### Tensile Properties

| Egenskap                        | Värde | Enhet | Provningsstandard |
|---------------------------------|-------|-------|-------------------|
| Tensile Strength                | 75    | MPa   | ISO 527           |
| Modulus of elasticity (tensile) | 2400  | MPa   | ISO 527-2         |
| Breakdown Voltage               | 60    | MPa   |                   |
| Break Elongation                | 50    | %     | ISO 527-2         |

#### Temperature Limits

| Egenskap                                   | Värde  | Enhet | Provningsstandard |
|--------------------------------------------|--------|-------|-------------------|
| Melting point                              | 160    | °C    | ISO 3146          |
| Maximal operating temperature (short-term) | 119    | °C    | UL746B            |
| Maximum Operating Temperature              | 113.75 | °C    |                   |
| Minimum temperature                        | -54    | °C    | UL746B            |
| Heat deflection temperature (HDT/A)        | 130    | °C    | ISO 75-2          |
| Heat deflection temperature (HDT/B)        | 140    | °C    | ISO 75            |
| Vicat softening temperature (VST/B/50)     | 150    | °C    | ISO 306           |

#### Insulation Properties

| Egenskap                        | Värde            | Enhet | Provningsstandard |
|---------------------------------|------------------|-------|-------------------|
| Dielectric Strength             | 29               | kV/mm | IEC 60243-1       |
| Volume Resistivity              | 10 <sup>13</sup> | Ω·cm  | IEC 60093         |
| Dielectric Constant (1 MHz)     | 2.98             | -     | IEC 60250         |
| Dielectric Constant (100 Hz)    | 3                | -     | IEC 60250         |
| Dielectric loss factor (1 MHz)  | 0.0              | -     | IEC 60250         |
| Dielectric loss factor (100 Hz) | 0.0              | -     | IEC 60250         |

Fire Classification

| Egenskap                            | Värde | Enhet | Provningsstandard |
|-------------------------------------|-------|-------|-------------------|
| Flammability Classification (UL 94) | 0     |       | UL 94             |

Flexural Properties

| Egenskap          | Värde | Enhet | Provningsstandard |
|-------------------|-------|-------|-------------------|
| Flexural Strength | 2400  | MPa   | ISO 178           |

Thermal Conductivity

| Egenskap             | Värde | Enhet   | Provningsstandard |
|----------------------|-------|---------|-------------------|
| Thermal Conductivity | 0.21  | W/(m·K) | DIN 52612         |

Static spread

| Egenskap                         | Värde            | Enhet | Provningsstandard |
|----------------------------------|------------------|-------|-------------------|
| Surface Resistivity              | 10 <sup>15</sup> | Ω     | IEC 60093         |
| Comparative Tracking Index (CTI) | 279.2            | V     | IEC 60112         |

Moisture Absorption

| Egenskap                       | Värde | Enhet | Provningsstandard |
|--------------------------------|-------|-------|-------------------|
| Water absorption to saturation | 0.15  | %     | ISO 62            |
| Water Absorption to Saturation | 0.35  | %     | ISO 62            |

Impact Resistance

| Egenskap                         | Värde | Enhet | Provningsstandard |
|----------------------------------|-------|-------|-------------------|
| Notched impact strength (Charpy) | 9     | kJ/m² | ISO 179/1eA       |

Thermal Expansion

| Egenskap                      | Värde | Enhet               | Provningsstandard |
|-------------------------------|-------|---------------------|-------------------|
| Thermal Expansion Coefficient | 0.65  | 10 <sup>-4</sup> /K | DIN 11359         |

Hardness

| Egenskap               | Värde | Enhet     | Provningsstandard |
|------------------------|-------|-----------|-------------------|
| Hardness Shore D       | 85    | ° Shore D | ISO 868           |
| Ball pressure hardness | 120   | MPa       | ISO 2039-1        |

Godkännanden

- EU 10/2011
- FDA
- REACH
- RoHS
- UL 94