



PC 15x1000 mm transparent

Artikelnr P1002602
Material PC

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Density	1.2	g/cm³	ISO 1183
Tensile Strength	75	MPa	ISO 527
Modulus of elasticity (tensile)	2400	MPa	ISO 527-2
Breakdown Voltage	60	MPa	
Break Elongation	50	%	ISO 527-2
Melting point	160	°C	ISO 3146
Maximal operating temperature (short-term)	119	°C	UL746B
Maximum Operating Temperature	113.75	°C	
Minimum temperature	-54	°C	UL746B
Heat deflection temperature (HDT/A)	130	°C	ISO 75-2
Heat deflection temperature (HDT/B)	140	°C	ISO 75
Vicat softening temperature (VST/B/50)	150	°C	ISO 306
Dielectric Strength	29	kV/mm	IEC 60243-1
Volume Resistivity	10 ¹³	Ω·cm	IEC 60093
Dielectric Constant (1 MHz)	2.98	-	IEC 60250
Dielectric Constant (100 Hz)	3	-	IEC 60250
Dielectric loss factor (1 MHz)	0.0	-	IEC 60250
Dielectric loss factor (100 Hz)	0.0	-	IEC 60250
Flammability Classification (UL 94)	0		UL 94
Flexural Strength	2400	MPa	ISO 178
Thermal Conductivity	0.21	W/(m·K)	DIN 52612
Surface Resistivity	10 ¹⁵	Ω	IEC 60093
Comparative Tracking Index (CTI)	279.2	V	IEC 60112
Water absorption to saturation	0.15	%	ISO 62
Water Absorption to Saturation	0.35	%	ISO 62

Egenskap	Värde	Enhet	Standard
Notched impact strength (Charpy)	9	kJ/m²	ISO 179/1eA
Thermal Expansion Coefficient	0.65	10 ⁻⁴ /K	DIN 11359
Hardness Shore D	85	° Shore D	ISO 868
Ball pressure hardness	120	MPa	ISO 2039-1

2. Kemisk beständighet

● Beständig ● Delvis beständig ● Ej beständig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100%	●
2-Hydroxypropionic acid (lactic acid)	90%	●
Acetic acid	100%	●
Acetone	100%	●
Ammonia	conc.	●
Ammonium chloride	-	●
Apple juice	-	●
Benzene	-	●
Bleaching solution	12.5 cl	●
Boric acid	100%	●
Butyl acetate	-	●
Calcium chloride	-	●
Carbon disulphide	100%	●
Carbon tetrachloride	-	●
Chlorine (gas)	100%	●
Chlorobenzene	100%	●
Chloroform	-	●
Citric acid	10%	●
Cresol	-	●
Cyclohexanone	100%	●
Cyclohexene	100%	●
Diesel	-	●
Diethylene oxide	-	●
Ethyl acetate	100%	●
Ethyl alcohol (ethanol)	96%	●
Ethylene chloride	100%	●

Kemikalie	Konc.	Resultat
Food oil	-	●
Formaldehyde, aqueous	40%	●
Formic acid	10%	●
Frost protection agent	-	●
Fuel oil	-	●
Fuel, aromatic free	-	●
Glycerine	100%	●
Glycol	100%	●
Heptane	100%	●
Hydrochloric acid	10%	●
Hydrochloric acid (concentrated)	conc.	●
Hydrofluoric acid	40%	●
Hydrogen peroxide	10%	●
Hydrogen sulfide, aqueous	-	●
Isopropyl alcohol	100%	●
Linseed oil	-	●
Mercurochrome	-	●
Methyl alcohol (methanol)	100%	●
Methyl ethyl ketone (MEK)	100%	●
Methylene chloride	100%	●
Milk	-	●
Nitric acid (10%)	10%	●
Nitric acid (50%)	50%	●
Nitrobenzene	-	●
Oxalic acid	-	●
Ozone (gas)	≤ 0.5 ppm	●
Paraffin oil	100%	●
Perchloroethylene	-	●
Petroleum	100%	●
Petroleum ether	100%	●
Phenol, aqueous	ca. 9%	●
Phosphoric acid	50%	●
Potassium hydroxide solution	50%	●
Premium fuel	-	●
Propyl alcohol	-	●

Kemikalie	Konc.	Resultat
Pyridine	-	
Silicone oil	-	
Sodium carbonate, aqueous	-	
Sodium chloride, aqueous	-	
Sodium hydrogen sulfite	-	
Sodium hydroxide solution (15%)	15%	
Sodium hydroxide solution (60%)	60%	
Sodium nitrate, aqueous	-	
Sulphuric acid	96%	
Tetrahydrofuran (THF)	100%	
Toluene	100%	
Trichloroethylene	100%	
Vinegar, standard	5-10%	
Water	-	
Xylene	-	