



PE Ultra HD Ast 50x2000 mm svart

Artikelnr P1400148

1. Tekniskt datablad

Egenskap	V�rde	Enhet	Standard
Density	3	g/cm���	DIN EN ISO 1183-1
Tensile Strength	20	MPa	DIN EN ISO 527
Modulus of elasticity (tensile)	650	MPa	DIN EN ISO 527
Break Elongation	50	%	DIN EN ISO 527
Melting point	133	��C	ISO 11357-3
Maximal operating temperature (short-term)	130	��C	
Maximum Operating Temperature	80	��C	
Minimum temperature	-200	��C	
Volume Resistivity	10���	���	DIN EN 62631-3-1
Flammability Classification (UL 94)	3		UL 94
Thermal Conductivity	0.4	W/(m���K)	DIN 52612
Surface Resistivity	10���	���	DIN EN 62631-3-2
Water absorption to saturation	0.01	%	
Water Absorption to Saturation	0.01	%	
Notched impact strength (Charpy)	2	kJ/m���	DIN EN ISO 179
Impact Resistance (Charpy)	2	kJ/m���	DIN EN ISO 179
Thermal Expansion Coefficient	1.75	10������K	DIN 53 752
Hardness Shore D	60	�� Shore D	DIN EN ISO 868
Ball pressure hardness	34	MPa	ISO 2039-1

2. Kemisk best  ndighet

   Best  ndig    Delvis best  ndig    Ej best  ndig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100%	��
2-Hydroxypropionic Acid	90%	��
Acetaldehyde	���	��

Kemikalie	Konc.	Resultat
Acetic Acid	100%	●
Acetic acid	100%	●
Acetic acid	3%	●
Acetic acid	3% w/w	●
Acetic acid	3%	●
Acetic acid	3%	●
Acetic acid, aqueous	70%	●
Acetic anhydride	â€”	●
Acetone	â€”	●
Acetone	100%	●
Acronal dispersions	â€”	●
Acrylonitrile	â€”	●
Allyl acetate	â€”	●
Allyl alcohol	96%	●
Allyl chloride	â€”	●
Aluminium chloride, aqueous	any	●
Aluminium chloride, solid	â€”	●
Aluminium fluoride	Conc.	●
Aluminium hydroxide	â€”	●
Aluminium metaphosphate	â€”	●
Aluminium sulphate, aqueous saturated	â€”	●
Aluminium sulphate, solid	â€”	●
Ammonia	concentrated	●
Ammonia, gaseous	â€”	●
Ammonia, liquid	â€”	●
Ammonium Chloride	â€”	●
Amyl Alcohol	â€”	●
Aniline	any	●
Anisole	â€”	●
Apple Juice	â€”	●
Aqua regia	â€”	●
Beer	â€”	●
Benzaldehyde, aqueous	any	●
Benzene	technically grade	●

Kemikalie	Konc.	Resultat
Benzene	â€™	●
Benzoic acid, aqueous	any	●
Benzyl alcohol	â€™	●
Bitumen	â€™	●
Bleaching Solution	12.5 cl	●
Boric Acid	100%	●
Brake Fluid	â€™	●
Bromine, liquid	100%	●
Butanol, aqueous	any	●
Butter	â€™	●
Butyl Acetate	â€™	●
Calcium Chloride	â€™	●
Calcium carbonate	â€™	●
Calcium carbonate	â€™	●
Calcium hypochlorite, aqueous suspension	any	●
Camphor	â€™	●
Carbon Disulfide	100%	●
Carbon Tetrachloride	â€™	●
Carbon disulphide	â€™	●
Caustic soda	any	●
Chlorine (gas)	100%	●
Chlorine, liquid	â€™	●
Chloroacetic acid, aqueous	â‰ƒ85%	●
Chlorobenzene	100%	●
Chlorobenzene	â€™	●
Chloroform	â€™	●
Chloroform	technically grade	●
Chromosulphuric acid	â€™	●
Cider	â€™	●
Citric Acid	10%	●
Citrus fruit juices	â€™	●
Coconut oil	â€™	●
Cod liver oil	â€™	●
Cresol	â€™	●
Cresol	100%	●

Kemikalie	Konc.	Resultat
Cyclohexane	â€”	●
Cyclohexanol	â€”	●
Cyclohexanone	100%	●
Cyclohexanone	â€”	●
Cyclohexene	100%	●
Detergents	â€”	●
Dibutyl ether	â€”	●
Dibutyl phthalate	â€”	●
Dichloroacetic acid	â€”	●
Dichloroethane	â€”	●
Diesel Fuel	â€”	●
Diesel fuel	â€”	●
Diethylene Oxide	â€”	●
Diglycolic acid, aqueous	30%	●
Dimethyl formamide	â€”	●
Dimethylamine	â€”	●
Dioxane	â€”	●
Ethanol	10%	●
Ethanol	10% v/v	●
Ethanol	10%	●
Ethanol	10%	●
Ethyl Acetate	100%	●
Ethyl Alcohol	96%	●
Ethyl acetate	â€”	●
Ethylene Chloride	100%	●
Ethylene alcohol	96%	●
Ethylene chloride	â€”	●
Ethylene diamine	â€”	●
Ethylene glycol	â€”	●
Ferric chloride, aqueous	any	●
Ferric nitrate, aqueous saturated	â€”	●
Ferric sulphate, aqueous saturated	â€”	●
Ferrous (II) chloride, aqueous saturated	â€”	●
Ferrous (II) sulfate, aqueous saturated	â€”	●
Ferrous (III) chloride, aqueous saturated	â€”	●

Kemikalie	Konc.	Resultat
Ferrous (III) nitrate, aqueous saturated	â€”	●
Ferrous (III) sulfate, aqueous saturated	â€”	●
Food Oil	â€”	●
Formaldehyde (aqueous)	40%	●
Formaldehyde, aqueous	â‰‰40%	●
Formic Acid	10%	●
Formic acid, aqueous	85%	●
Frigen 12 (Freon 12)	100%	●
Frost Protection Agent	â€”	●
Fruit juices	any	●
Fuel (aromatic free)	â€”	●
Fuel oil	â€”	●
Furfural	â€”	●
Glycerin, aqueous	any	●
Glycerine	100%	●
Glycol	100%	●
Glykol, aqueous	as supplied	●
Glysantin	â€”	●
Heating Oil	â€”	●
Heptane	100%	●
Heptane	â€”	●
Hexane	â€”	●
Honey	â€”	●
Hydrobromic acid, aqueous	50%	●
Hydrochloric Acid	10%	●
Hydrochloric Acid (concentrated)	concentrated	●
Hydrochloric acid, aqueous	any	●
Hydrofluoric Acid	40%	●
Hydrogen Peroxide	10%	●
Hydrogen Sulfide (aqueous solution)	â€”	●
Ink	â€”	●
Iodine in potassium iodide solution	3% iodine	●
Isooctane	â€”	●
Isopropanol	â€”	●
Isopropyl Alcohol	100%	●

Kemikalie	Konc.	Resultat
Isopropyl ether	â€”	
Jam	â€”	
Kerosene	â€”	
Linseed Oil	â€”	
Linseed oil	technically grade	
Lithium bromide	â€”	
Magnesium stearate	â€”	
Magnesium stearate	â€”	
Maleic acid, aqueous	any	
Menthol	â€”	
Mercurochrome	â€”	
Mercury	â€”	
Methanol	technically grade	
Methyl Alcohol	100%	
Methyl Ethyl Ketone (MEK)	100%	
Methyl chloride	gaseous, technically grade	
Methyl ethyl ketone	technically grade	
Methylene Chloride	100%	
Milk	â€”	
Milk	â€”	
Mineral Oil (aromatic free)	â€”	
Molasses	â€”	
Motor oil (heavy duty oil) without additives	â€”	
Naphtha	â€”	
Naphthalene	â€”	
Nitric Acid	10%	
Nitric Acid (50%)	50%	
Nitric acid, aqueous	50%	
Nitric acid, aqueous	25%	
Nitrobenzene	â€”	
Nitrobenzene	â€”	
Oils, ethereal	â€”	
Oils, vegetable and animal	â€”	
Oleic acid	â€”	
Oleum	any	

Kemikalie	Konc.	Resultat
Olive oil	â€”	●
Olive oil	â€”	●
Olive oil	â€”	●
Olive oil	â€”	●
Oxalic Acid	â€”	●
Oxalic acid, aqueous	any	●
Oxygen	â€”	●
Ozone	50 ppm	●
Ozone Gas	â‰¤0.5 ppm	●
Paraffine Oil	100%	●
Perchloric acid, aqueous	20%	●
Perchloric acid, aqueous	50%	●
Perchloric acid, aqueous	70%	●
Perchloroethylene	â€”	●
Petroleum	â€”	●
Petroleum	100%	●
Petroleum Ether	100%	●
Petroleum ether	â€”	●
Phenol	â€”	●
Phenol (aqueous)	â‰ˆ9%	●
Phosphoric Acid	50%	●
Phosphoric acid, aqueous	80% L 95%	●
Phosphoric acid, aqueous	50%	●
Phosphorus trichloride	â€”	●
Photographic developers	â€”	●
Photographic emulsions	as supplied	●
Photographic fixing baths	as supplied	●
Phthalic acid, aqueous	50%	●
Polyester resins	â€”	●
Potassium Hydroxide liquor	50%	●
Premium Fuel	â€”	●
Propionic acid, aqueous	any	●
Propyl Alcohol	â€”	●
Pyridine	â€”	●
Pyridine	â€”	●

Kemikalie	Konc.	Resultat
Sea water	â€”	●
Silicon dioxide	â€”	●
Silicon dioxide	â€”	●
Silicone Oil	â€”	●
Silicone oil	technically grade	●
Sodium Carbonate (aqueous)	â€”	●
Sodium Chloride (aqueous)	â€”	●
Sodium Hydrogen Sulfite	â€”	●
Sodium Hydroxide liquor	15%	●
Sodium Hydroxide liquor (60%)	60%	●
Sodium Nitrate (aqueous)	â€”	●
Sodium Thiosulfate	â€”	●
Sodium borate	â€”	●
Sodium bromide	â€”	●
Sodium hydroxide, aqueous	any	●
Sodium hydroxide, solid	â€”	●
Stearic acid	â€”	●
Sugar syrup	â€”	●
Sulfuric Acid	96%	●
Sulphuric acid, aqueous	98%	●
Sulphuric acid, aqueous	â‰ƒ50%	●
Sulphuric acid, aqueous	80%	●
Sulphuric acid, aqueous	70%	●
Tallow	technically grade	●
Tannic acid (tannin), aqueous	10%	●
Tetrahydrofuran	technically grade	●
Tetrahydrofuran (THF)	100%	●
Thionyl chloride	â€”	●
Thiophene	â€”	●
Tin (II) chloride, aqueous	any	●
Tin (IV) chloride, aqueous	saturated	●
Titanium dioxide	â€”	●
Titanium dioxide	â€”	●
Toluene	100%	●

Kemikalie	Konc.	Resultat
Toluene	technically grade	
Transformer Oil	â€”	
Transformer oil (insulating oil)	technically grade	
Trichloroacetic acid	technically grade	
Trichloroethylene	technically grade	
Trichloroethylene	100%	
Triethanolamine	â€”	
Triethanolamine	â€”	
Turpentine oil	technically grade	
Urea, aqueous	â‰ƒ33%	
Vaseline	technically grade	
Vinegar (standard)	5-10%	
Washing up liquids	usual	
Water	â€”	
Water, distilled	â€”	
Wine	â€”	
Xylene	â€”	
Xylene	â€”	
Zinc sludge	â€”	