PLASTSHOP.SE

Kemisk beständighet

PlastShop.se - 2026-03-26

PE-500 160x2000 mm natur

Artikelnr P2200631

Beständig Delvis beständig Ej beständig

Kemikalie	Koncentration	Temp.	Beständighet
1,4-Dioxane	100%	20 °C	
2-Hydroxypropionic Acid	90%	20 °C	
Acetaldehyde	-	20 °C	
Acetic Acid	100%	20 °C	
Acetic acid	100%	20 °C	
Acetic acid	3%	100 °C	
Acetic acid	3% w/w	20 °C	
Acetic acid	3%	100 °C	
Acetic acid	3%	100 °C	
Acetic acid, aqueous	70%	20 °C	
Acetic anhydride	-	20 °C	
Acetone	-	20 °C	
Acetone	100%	20 °C	
Acronal dispersions	-	20 °C	
Acrylonitrile	-	20 °C	
Allyl acetate	-	20 °C	
Allyl alcohol	96%	20 °C	
Allyl chloride	-	20 °C	
Aluminium chloride, aqueous	any	20 °C	
Aluminium chloride, solid	-	20 °C	
Aluminium fluoride	Conc.	20 °C	
Aluminium hydroxide	-	20 °C	
Aluminium metaphosphate	-	20 °C	
Aluminium sulphate, aqueous saturated	-	20 °C	
Aluminium sulphate, solid	-	20 °C	
Ammonia	concentrated	20 °C	

Kemikalie	Koncentration	Temp.	Beständighet
Ammonia, gaseous	-	20 °C	🟢
Ammonia, liquid	-	20 °C	🟢
Ammonium Chloride	-	20 °C	🟢
Amyl Alcohol	-	20 °C	🟢
Aniline	any	20 °C	🟢
Anisole	-	20 °C	🟢
Apple Juice	-	20 °C	🟢
Aqua regia	-	20 °C	🔴
Beer	-	20 °C	🟢
Benzaldehyde, aqueous	any	20 °C	🟢
Benzene	technically grade	20 °C	🔴
Benzene	-	20 °C	🟢
Benzoic acid, aqueous	any	20 °C	🟢
Benzyl alcohol	-	20 °C	🟢
Bitumen	-	20 °C	🟢
Bleaching Solution	12.5 cl	20 °C	🟡
Boric Acid	100%	20 °C	🟢
Brake Fluid	-	20 °C	🟢
Bromine, liquid	100%	20 °C	🔴
Butanol, aqueous	any	20 °C	🟢
Butter	-	20 °C	🟢
Butyl Acetate	-	20 °C	🟢
Calcium Chloride	-	20 °C	🟢
Calcium carbonate	-	20 °C	🟢
Calcium carbonate	-	20 °C	🟢
Calcium hypochlorite, aqueous suspension	any	20 °C	🟢
Camphor	-	20 °C	🟡
Carbon Disulfide	100%	20 °C	🟡
Carbon Tetrachloride	-	20 °C	🟡
Carbon disulphide	-	20 °C	🔴
Caustic soda	any	20 °C	🟢
Chlorine (gas)	100%	20 °C	🟡
Chlorine, liquid	-	20 °C	🔴
Chloroacetic acid, aqueous	≤85%	20 °C	🟢

Kemikalie	Koncentration	Temp.	Beständighet
Chlorobenzene	100%	20 °C	🟡
Chlorobenzene	-	20 °C	🟡
Chloroform	technically grade	20 °C	🟡
Chloroform	-	20 °C	🟡
Chromosulphuric acid	-	20 °C	🔴
Cider	-	20 °C	🟢
Citric Acid	10%	20 °C	🟢
Citrus fruit juices	-	20 °C	🟢
Coconut oil	-	20 °C	🟢
Cod liver oil	-	20 °C	🟢
Cresol	-	20 °C	🟢
Cresol	100%	20 °C	🟢
Cyclohexane	-	20 °C	🟢
Cyclohexanol	-	20 °C	🟢
Cyclohexanone	100%	20 °C	🟢
Cyclohexanone	-	20 °C	🟢
Cyclohexene	100%	20 °C	🟢
Detergents	-	20 °C	🟢
Dibutyl ether	-	20 °C	🟢
Dibutyl phthalate	-	20 °C	🟢
Dichloroacetic acid	-	20 °C	🟢
Dichloroethane	-	20 °C	🟡
Diesel Fuel	-	20 °C	🟢
Diesel fuel	-	20 °C	🟢
Diethylene Oxide	-	20 °C	🟢
Diglycolic acid, aqueous	30%	20 °C	🟢
Dimethyl formamide	-	20 °C	🟢
Dimethylamine	-	20 °C	🟢
Dioxane	-	20 °C	🟢
Ethanol	10%	100 °C	🟢
Ethanol	10%	100 °C	🟢
Ethanol	10% v/v	20 °C	🟢
Ethanol	10%	100 °C	🟢
Ethyl Acetate	100%	20 °C	🟢

Kemikalie	Koncentration	Temp.	Beständighet
Ethyl Alcohol	96%	20 °C	●
Ethyl acetate	-	20 °C	●
Ethylene Chloride	100%	20 °C	●
Ethylene alcohol	96%	20 °C	●
Ethylene chloride	-	20 °C	●
Ethylene diamine	-	20 °C	●
Ethylene glycol	-	20 °C	●
Ferric chloride, aqueous	any	20 °C	●
Ferric nitrate, aqueous saturated	-	20 °C	●
Ferric sulphate, aqueous saturated	-	20 °C	●
Ferrous (II) chloride, aqueous saturated	-	20 °C	●
Ferrous (II) sulfate, aqueous saturated	-	20 °C	●
Ferrous (III) chloride, aqueous saturated	-	20 °C	●
Ferrous (III) nitrate, aqueous saturated	-	20 °C	●
Ferrous (III) sulfate, aqueous saturated	-	20 °C	●
Food Oil	-	20 °C	●
Formaldehyde (aqueous)	40%	20 °C	●
Formaldehyde, aqueous	≤40%	20 °C	●
Formic Acid	10%	20 °C	●
Formic acid, aqueous	85%	20 °C	●
Frigen 12 (Freon 12)	100%	20 °C	●
Frost Protection Agent	-	20 °C	●
Fruit juices	any	20 °C	●
Fuel (aromatic free)	-	20 °C	●
Fuel oil	-	20 °C	●
Furfural	-	20 °C	●
Glycerin, aqueous	any	20 °C	●
Glycerine	100%	20 °C	●
Glycol	100%	20 °C	●
Glykol, aqueous	as supplied	20 °C	●
Glysantin	-	20 °C	●
Heating Oil	-	20 °C	●
Heptane	-	20 °C	●
Heptane	100%	20 °C	●

Kemikalie	Koncentration	Temp.	Beständighet
Hexane	-	20 °C	🟢
Honey	-	20 °C	🟢
Hydrobromic acid, aqueous	50%	20 °C	🟢
Hydrochloric Acid	10%	20 °C	🟢
Hydrochloric Acid (concentrated)	concentrated	20 °C	🟢
Hydrochloric acid, aqueous	any	20 °C	🟢
Hydrofluoric Acid	40%	20 °C	🟢
Hydrogen Peroxide	10%	20 °C	🟢
Hydrogen Sulfide (aqueous solution)	-	20 °C	🟢
Ink	-	20 °C	🟢
Iodine in potassium iodide solution	3% iodine	20 °C	🟢
Isooctane	-	20 °C	🟢
Isopropanol	-	20 °C	🟢
Isopropyl Alcohol	100%	20 °C	🟢
Isopropyl ether	-	20 °C	🟡
Jam	-	20 °C	🟢
Kerosene	-	20 °C	🟢
Linseed Oil	-	20 °C	🟢
Linseed oil	technically grade	20 °C	🟢
Lithium bromide	-	20 °C	🟢
Magnesium stearate	-	20 °C	🟢
Magnesium stearate	-	20 °C	🟢
Maleic acid, aqueous	any	20 °C	🟢
Menthol	-	20 °C	🟢
Mercurochrome	-	20 °C	🟢
Mercury	-	20 °C	🟢
Methanol	technically grade	20 °C	🟢
Methyl Alcohol	100%	20 °C	🟢
Methyl Ethyl Ketone (MEK)	100%	20 °C	🔴
Methyl chloride	gaseous, technically grade	20 °C	🔴
Methyl ethyl ketone	technically grade	20 °C	🟢
Methylene Chloride	100%	20 °C	🟡
Milk	-	20 °C	🟢
Milk	-	20 °C	🟢

Kemikalie	Koncentration	Temp.	Beständighet
Mineral Oil (aromatic free)	-	20 °C	🟢
Molasses	-	20 °C	🟢
Motor oil (heavy duty oil) without additives	-	20 °C	🟢
Naphtha	-	20 °C	🟢
Naphthalene	-	20 °C	🟢
Nitric Acid	10%	20 °C	🟢
Nitric Acid (50%)	50%	20 °C	🟡
Nitric acid, aqueous	50%	20 °C	🟡
Nitric acid, aqueous	25%	20 °C	🟢
Nitrobenzene	-	20 °C	🟢
Nitrobenzene	-	20 °C	🟢
Oils, ethereal	-	20 °C	🟡
Oils, vegetable and animal	-	20 °C	🟢
Oleic acid	-	20 °C	🟢
Oleum	any	20 °C	🔴
Olive oil	-	100 °C	🟢
Olive oil	-	100 °C	🟢
Olive oil	-	100 °C	🟢
Olive oil	-	20 °C	🟢
Oxalic Acid	-	20 °C	🟢
Oxalic acid, aqueous	any	20 °C	🟢
Oxygen	-	20 °C	🟢
Ozone	50 ppm	20 °C	🟡
Ozone Gas	≤0.5 ppm	20 °C	🟢
Paraffine Oil	100%	20 °C	🟢
Perchloric acid, aqueous	50%	20 °C	🟢
Perchloric acid, aqueous	70%	20 °C	🟢
Perchloric acid, aqueous	20%	20 °C	🟢
Perchloroethylene	-	20 °C	🟡
Petroleum	-	20 °C	🟢
Petroleum	100%	20 °C	🟢
Petroleum Ether	100%	20 °C	🟢
Petroleum ether	-	20 °C	🟢
Phenol	-	20 °C	🟢
Phenol (aqueous)	≈9%	20 °C	🟢

Kemikalie	Koncentration	Temp.	Beständighet
Phosphoric Acid	50%	20 °C	🟢
Phosphoric acid, aqueous	50%	20 °C	🟢
Phosphoric acid, aqueous	80% L 95%	20 °C	🟢
Phosphorus trichloride	-	20 °C	🔴
Photographic developers	-	20 °C	🟢
Photographic emulsions	as supplied	20 °C	🟢
Photographic fixing baths	as supplied	20 °C	🟢
Phthalic acid, aqueous	50%	20 °C	🟢
Polyester resins	-	20 °C	🔴
Potassium Hydroxide liquor	50%	20 °C	🟢
Premium Fuel	-	20 °C	🟢
Propionic acid, aqueous	any	20 °C	🟢
Propyl Alcohol	-	20 °C	🟢
Pyridine	-	20 °C	🟢
Pyridine	-	20 °C	🟢
Sea water	-	20 °C	🟢
Silicon dioxide	-	20 °C	🟢
Silicon dioxide	-	20 °C	🟢
Silicone Oil	-	20 °C	🟢
Silicone oil	technically grade	20 °C	🟢
Sodium Carbonate (aqueous)	-	20 °C	🟢
Sodium Chloride (aqueous)	-	20 °C	🟢
Sodium Hydrogen Sulfite	-	20 °C	🟢
Sodium Hydroxide liquor	15%	20 °C	🟢
Sodium Hydroxide liquor (60%)	60%	20 °C	🟢
Sodium Nitrate (aqueous)	-	20 °C	🟢
Sodium Thiosulfate	-	20 °C	🟢
Sodium borate	-	20 °C	🟢
Sodium bromide	-	20 °C	🟢
Sodium hydroxide, aqueous	any	20 °C	🟢
Sodium hydroxide, solid	-	20 °C	🟢
Stearic acid	-	20 °C	🟢
Sugar syrup	-	20 °C	🟢
Sulfuric Acid	96%	20 °C	🟡
Sulphuric acid, aqueous	≤50%	20 °C	🟢

Kemikalie	Koncentration	Temp.	Beständighet
Sulphuric acid, aqueous	98%	20 °C	🟢
Sulphuric acid, aqueous	80%	20 °C	🟢
Sulphuric acid, aqueous	70%	20 °C	🟢
Tallow	technically grade	20 °C	🟢
Tannic acid (tannin), aqueous	10%	20 °C	🟢
Tetrahydrofuran	technically grade	20 °C	🔴
Tetrahydrofuran (THF)	100%	20 °C	🟡
Thionyl chloride	-	20 °C	🔴
Thiophene	-	20 °C	🔴
Tin (II) chloride, aqueous	any	20 °C	🟢
Tin (IV) chloride, aqueous	saturated	20 °C	🟢
Titanium dioxide	-	20 °C	🟢
Titanium dioxide	-	20 °C	🟢
Toluene	100%	20 °C	🟡
Toluene	technically grade	20 °C	🔴
Transformer Oil	-	20 °C	🟢
Transformer oil (insulating oil)	technically grade	20 °C	🟢
Trichloracetic acid	technically grade	20 °C	🟢
Trichloroethylene	technically grade	20 °C	🔴
Trichloroethylene	100%	20 °C	🟢
Triethanolamine	-	20 °C	🟢
Triethanolamine	-	20 °C	🟢
Turpentine oil	technically grade	20 °C	🟢
Urea, aqueous	≤33%	20 °C	🟢
Vaseline	technically grade	20 °C	🟢
Vinegar (standard)	5-10%	20 °C	🟢
Washing up liquids	usual	20 °C	🟢
Water	-	20 °C	🟢
Water, distilled	-	20 °C	🟢
Wine	-	20 °C	🟢
Xylene	-	20 °C	🔴
Xylene	-	20 °C	🔴
Zinc sludge	-	20 °C	🟢