

PE-HD 10"x1220 mm natur

Artikelnr P2200421

 ● **Beständig** ● **Delvis beständig** ● **Ej beständig**

Kemikalie	Koncentration	Temp.	Beständighet
1,4-Dioxane	100%	20 °C	●
2-Hydroxypropionic acid (lactic acid)	90%	20 °C	●
Acetaldehyde	-	20 °C	●
Acetic acid	100%	20 °C	●
Acetic acid	100%	20 °C	●
Acetic acid, aqueous	70%	20 °C	●
Acetic anhydride	-	20 °C	●
Acetone	-	20 °C	●
Acetone	100%	20 °C	●
Acronal dispersions	-	20 °C	●
Acrylonitrile	-	20 °C	●
Allyl acetate	-	20 °C	●
Allyl alcohol	96%	20 °C	●
Allyl chloride	-	20 °C	●
Aluminium chloride, aqueous	any	20 °C	●
Aluminium chloride, solid	-	20 °C	●
Aluminium fluoride	Conc.	20 °C	●
Aluminium hydroxide	-	20 °C	●
Aluminium metaphosphate	-	20 °C	●
Aluminium sulphate, aqueous saturated	-	20 °C	●
Aluminium sulphate, solid	-	20 °C	●
Ammonia	concentrated	20 °C	●
Ammonia, gaseous	-	20 °C	●
Ammonia, liquid	-	20 °C	●
Ammonium chloride	-	20 °C	●
Amyl alcohol	-	20 °C	●

Kemikalie	Koncentration	Temp.	Beständighet
Aniline	any	20 °C	●
Anisole	-	20 °C	●
Aqua regia	-	20 °C	●
Beer	-	20 °C	●
Benzaldehyde, aqueous	any	20 °C	●
Benzene	technically grade	20 °C	●
Benzene	-	20 °C	●
Benzoic acid, aqueous	any	20 °C	●
Benzyl alcohol	-	20 °C	●
Bitumen	-	20 °C	●
Bleaching solution	12.5 cl	20 °C	●
Boric acid	100%	20 °C	●
Brake fluid	-	20 °C	●
Bromine, liquid	100%	20 °C	●
Butanol, aqueous	any	20 °C	●
Butter	-	20 °C	●
Butyl acetate	-	20 °C	●
Calcium chloride	-	20 °C	●
Calcium hypochlorite, aqueous suspension	any	20 °C	●
Camphor	-	20 °C	●
Carbon disulphide	-	20 °C	●
Carbon disulphide	100%	20 °C	●
Carbon tetrachloride	-	20 °C	●
Caustic soda (NaOH)	any	20 °C	●
Chlorine (gas)	100%	20 °C	●
Chlorine, liquid	-	20 °C	●
Chloroacetic acid, aqueous	≤85%	20 °C	●
Chlorobenzene	-	20 °C	●
Chlorobenzene	100%	20 °C	●
Chloroform	technically grade	20 °C	●
Chloroform	-	20 °C	●
Chromosulphuric acid	-	20 °C	●
Cider	-	20 °C	●
Citric acid	10%	20 °C	●

Kemikalie	Koncentration	Temp.	Beständighet
Citrus fruit juices	-	20 °C	●
Coconut oil	-	20 °C	●
Cod liver oil	-	20 °C	●
Cresol	100%	20 °C	●
Cresol	-	20 °C	●
Cyclohexane	-	20 °C	●
Cyclohexanol	-	20 °C	●
Cyclohexanone	-	20 °C	●
Cyclohexanone	100%	20 °C	●
Cyclohexene	100%	20 °C	●
Detergents	-	20 °C	●
Detergents	usual	20 °C	●
Dibutyl ether	-	20 °C	●
Dibutyl phthalate	-	20 °C	●
Dichloroacetic acid	-	20 °C	●
Dichloroethane	-	20 °C	●
Diesel	-	20 °C	●
Diesel	-	20 °C	●
Diethylene oxide	-	20 °C	●
Diglycolic acid, aqueous	30%	20 °C	●
Dimethyl formamide (DMF)	-	20 °C	●
Dimethylamine	-	20 °C	●
Dioxane	-	20 °C	●
Essential oils	-	20 °C	●
Ethyl acetate	100%	20 °C	●
Ethyl acetate	-	20 °C	●
Ethyl alcohol (ethanol)	96%	20 °C	●
Ethylene alcohol	96%	20 °C	●
Ethylene chloride	-	20 °C	●
Ethylene chloride	100%	20 °C	●
Ethylene diamine	-	20 °C	●
Ethylene glycol	-	20 °C	●
Ferric chloride, aqueous	any	20 °C	●
Ferric nitrate, aqueous saturated	-	20 °C	●
Ferric nitrate, aqueous saturated	-	20 °C	●

Kemikalie	Koncentration	Temp.	Beständighet
Ferric sulphate, aqueous saturated	-	20 °C	●
Ferric sulphate, aqueous saturated	-	20 °C	●
Ferrous (II) chloride, aqueous saturated	-	20 °C	●
Ferrous (II) sulfate, aqueous saturated	-	20 °C	●
Ferrous (III) chloride, aqueous saturated	-	20 °C	●
Food oil	-	20 °C	●
Formaldehyde (aqueous)	40%	20 °C	●
Formaldehyde, aqueous	≤40%	20 °C	●
Formic acid	10%	20 °C	●
Formic acid, aqueous	85%	20 °C	●
Frigen 12 (Freon 12)	100%	20 °C	●
Frost protection agent	-	20 °C	●
Fruit juices	any	20 °C	●
Fuel (aromatic free)	-	20 °C	●
Fuel oil	-	20 °C	●
Fuel oil	-	20 °C	●
Furfural	-	20 °C	●
Glycerine	100%	20 °C	●
Glycerine, aqueous	any	20 °C	●
Glycol	100%	20 °C	●
Glycol, aqueous	as supplied	20 °C	●
Glysantin	-	20 °C	●
Heptane	100%	20 °C	●
Heptane	-	20 °C	●
Hexane	-	20 °C	●
Honey	-	20 °C	●
Hydrobromic acid, aqueous	50%	20 °C	●
Hydrochloric acid	10%	20 °C	●
Hydrochloric acid (concentrated)	concentrated	20 °C	●
Hydrochloric acid, aqueous	any	20 °C	●
Hydrofluoric acid	40%	20 °C	●
Hydrogen peroxide	10%	20 °C	●
Hydrogen sulfide (aqueous)	-	20 °C	●
Ink	-	20 °C	●
Iodine in potassium iodide solution	3% iodine	20 °C	●

Kemikalie	Koncentration	Temp.	Beständighet
Isooctane	-	20 °C	●
Isopropanol	-	20 °C	●
Isopropyl alcohol	100%	20 °C	●
Isopropyl ether	-	20 °C	●
Jam	-	20 °C	●
Kerosene	-	20 °C	●
Linseed oil	technically grade	20 °C	●
Linseed oil	-	20 °C	●
Lithium bromide	-	20 °C	●
Maleic acid, aqueous	any	20 °C	●
Menthol	-	20 °C	●
Mercurochrome	-	20 °C	●
Mercury	-	20 °C	●
Methanol	technically grade	20 °C	●
Methyl alcohol (methanol)	100%	20 °C	●
Methyl chloride	gaseous, technically grade	20 °C	●
Methyl ethyl ketone (MEK)	technically grade	20 °C	●
Methyl ethyl ketone (MEK)	100%	20 °C	●
Methylene chloride	100%	20 °C	●
Milk	-	20 °C	●
Milk	-	20 °C	●
Mineral oil (aromatic free)	-	20 °C	●
Molasses	-	20 °C	●
Motor oil (heavy duty) without additives	-	20 °C	●
Naphtha	-	20 °C	●
Naphthalene	-	20 °C	●
Nitric acid	10%	20 °C	●
Nitric acid (50%)	50%	20 °C	●
Nitric acid, aqueous	50%	20 °C	●
Nitric acid, aqueous	25%	20 °C	●
Nitrobenzene	-	20 °C	●
Nitrobenzene	-	20 °C	●
Oils, vegetable and animal	-	20 °C	●
Oleic acid	-	20 °C	●

Kemikalie	Koncentration	Temp.	Beständighet
Oleum (fuming sulphuric acid)	any	20 °C	●
Oxalic acid	-	20 °C	●
Oxalic acid, aqueous	any	20 °C	●
Oxygen	-	20 °C	●
Ozone	50 ppm	20 °C	●
Ozone (gas)	≤0.5 ppm	20 °C	●
Paraffin oil	100%	20 °C	●
Perchloric acid, aqueous	50%	20 °C	●
Perchloric acid, aqueous	70%	20 °C	●
Perchloric acid, aqueous	20%	20 °C	●
Perchloroethylene	-	20 °C	●
Petroleum	-	20 °C	●
Petroleum ether	100%	20 °C	●
Petroleum ether	-	20 °C	●
Phenol	-	20 °C	●
Phenol (aqueous)	≈9%	20 °C	●
Phosphoric acid	50%	20 °C	●
Phosphoric acid, aqueous	50%	20 °C	●
Phosphoric acid, aqueous	80% L 95%	20 °C	●
Phosphorus trichloride	-	20 °C	●
Photographic developer	-	20 °C	●
Photographic emulsion	as supplied	20 °C	●
Photographic fixing bath	as supplied	20 °C	●
Phthalic acid, aqueous	50%	20 °C	●
Polyester resins	-	20 °C	●
Potassium hydroxide solution	50%	20 °C	●
Premium fuel	-	20 °C	●
Propionic acid, aqueous	any	20 °C	●
Propyl alcohol	-	20 °C	●
Pyridine	-	20 °C	●
Pyridine	-	20 °C	●
Sea water	-	20 °C	●
Silicone oil	technically grade	20 °C	●
Silicone oil	-	20 °C	●

Kemikalie	Koncentration	Temp.	Beständighet
Sodium borate (borax)	-	20 °C	●
Sodium bromide	-	20 °C	●
Sodium carbonate (aqueous)	-	20 °C	●
Sodium chloride (aqueous)	-	20 °C	●
Sodium hydrogen sulfite	-	20 °C	●
Sodium hydroxide solution (60%)	60%	20 °C	●
Sodium hydroxide solution (caustic soda)	15%	20 °C	●
Sodium hydroxide, aqueous	any	20 °C	●
Sodium hydroxide, solid	-	20 °C	●
Sodium nitrate (aqueous)	-	20 °C	●
Sodium thiosulfate	-	20 °C	●
Stearic acid	-	20 °C	●
Sugar syrup	-	20 °C	●
Sulphuric acid	96%	20 °C	●
Sulphuric acid, aqueous	≤50%	20 °C	●
Sulphuric acid, aqueous	70%	20 °C	●
Sulphuric acid, aqueous	80%	20 °C	●
Sulphuric acid, aqueous	98%	20 °C	●
Tallow	technically grade	20 °C	●
Tannic acid (tannin), aqueous	10%	20 °C	●
Tetrahydrofuran (THF)	100%	20 °C	●
Tetrahydrofuran (THF)	technically grade	20 °C	●
Thionyl chloride	-	20 °C	●
Thiophene	-	20 °C	●
Tin (II) chloride, aqueous	any	20 °C	●
Tin (IV) chloride, aqueous	saturated	20 °C	●
Toluene	100%	20 °C	●
Toluene	technically grade	20 °C	●
Transformer oil	-	20 °C	●
Transformer oil (insulating oil)	technically grade	20 °C	●
Trichloroacetic acid	technically grade	20 °C	●
Trichloroethylene	100%	20 °C	●
Trichloroethylene	technically grade	20 °C	●
Triethanolamine	-	20 °C	●

Kemikalie	Koncentration	Temp.	Beständighet
Turpentine oil	technically grade	20 °C	●
Urea, vattenl.	≤33%	20 °C	●
Vaseline	technically grade	20 °C	●
Vinegar (standard)	5-10%	20 °C	●
Water	-	20 °C	●
Water, distilled	-	20 °C	●
Wine	-	20 °C	●
Xylene	-	20 °C	●
Xylene	-	20 °C	●
Zinc sludge	-	20 °C	●