



PE-HD 125x1000 mm natur

Artikelnr P1003297

Beständig Delvis beständig Ej beständig

| Kemikalie                             | Koncentration | Temp. | Beständighet |
|---------------------------------------|---------------|-------|--------------|
| 1,4-Dioxane                           | 100%          | 20 °C | Beständig    |
| 2-Hydroxypropionic acid (lactic acid) | 90%           | 20 °C | Beständig    |
| Acetaldehyde                          | -             | 20 °C | Beständig    |
| Acetic acid                           | 100%          | 20 °C | Beständig    |
| Acetic acid                           | 100%          | 20 °C | Beständig    |
| Acetic acid, aqueous                  | 70%           | 20 °C | Beständig    |
| Acetic anhydride                      | -             | 20 °C | Beständig    |
| Acetone                               | -             | 20 °C | Beständig    |
| Acetone                               | 100%          | 20 °C | Beständig    |
| Acronal dispersions                   | -             | 20 °C | Beständig    |
| Acrylonitrile                         | -             | 20 °C | Beständig    |
| Allyl acetate                         | -             | 20 °C | Beständig    |
| Allyl alcohol                         | 96%           | 20 °C | Beständig    |
| Allyl chloride                        | -             | 20 °C | Beständig    |
| Aluminium chloride, aqueous           | any           | 20 °C | Beständig    |
| Aluminium chloride, solid             | -             | 20 °C | Beständig    |
| Aluminium fluoride                    | Conc.         | 20 °C | Beständig    |
| Aluminium hydroxide                   | -             | 20 °C | Beständig    |
| Aluminium metaphosphate               | -             | 20 °C | Beständig    |
| Aluminium sulphate, aqueous saturated | -             | 20 °C | Beständig    |
| Aluminium sulphate, solid             | -             | 20 °C | Beständig    |
| Ammonia                               | concentrated  | 20 °C | Beständig    |
| Ammonia, gaseous                      | -             | 20 °C | Beständig    |
| Ammonia, liquid                       | -             | 20 °C | Beständig    |
| Ammonium chloride                     | -             | 20 °C | Beständig    |
| Amyl alcohol                          | -             | 20 °C | Beständig    |

| Kemikalie                                | Koncentration     | Temp. | Beständighet |
|------------------------------------------|-------------------|-------|--------------|
| Aniline                                  | any               | 20 °C | ●            |
| Anisole                                  | -                 | 20 °C | ●            |
| Aqua regia                               | -                 | 20 °C | ●            |
| Beer                                     | -                 | 20 °C | ●            |
| Benzaldehyde, aqueous                    | any               | 20 °C | ●            |
| Benzene                                  | technically grade | 20 °C | ●            |
| Benzene                                  | -                 | 20 °C | ●            |
| Benzoic acid, aqueous                    | any               | 20 °C | ●            |
| Benzyl alcohol                           | -                 | 20 °C | ●            |
| Bitumen                                  | -                 | 20 °C | ●            |
| Bleaching solution                       | 12.5 cl           | 20 °C | ●            |
| Boric acid                               | 100%              | 20 °C | ●            |
| Brake fluid                              | -                 | 20 °C | ●            |
| Bromine, liquid                          | 100%              | 20 °C | ●            |
| Butanol, aqueous                         | any               | 20 °C | ●            |
| Butter                                   | -                 | 20 °C | ●            |
| Butyl acetate                            | -                 | 20 °C | ●            |
| Calcium chloride                         | -                 | 20 °C | ●            |
| Calcium hypochlorite, aqueous suspension | any               | 20 °C | ●            |
| Camphor                                  | -                 | 20 °C | ●            |
| Carbon disulphide                        | 100%              | 20 °C | ●            |
| Carbon disulphide                        | -                 | 20 °C | ●            |
| Carbon tetrachloride                     | -                 | 20 °C | ●            |
| Caustic soda (NaOH)                      | any               | 20 °C | ●            |
| Chlorine (gas)                           | 100%              | 20 °C | ●            |
| Chlorine, liquid                         | -                 | 20 °C | ●            |
| Chloroacetic acid, aqueous               | ≤85%              | 20 °C | ●            |
| Chlorobenzene                            | 100%              | 20 °C | ●            |
| Chlorobenzene                            | -                 | 20 °C | ●            |
| Chloroform                               | technically grade | 20 °C | ●            |
| Chloroform                               | -                 | 20 °C | ●            |
| Chromosulphuric acid                     | -                 | 20 °C | ●            |
| Cider                                    | -                 | 20 °C | ●            |
| Citric acid                              | 10%               | 20 °C | ●            |

| Kemikalie                         | Koncentration | Temp. | Beständighet |
|-----------------------------------|---------------|-------|--------------|
| Citrus fruit juices               | -             | 20 °C | ●            |
| Coconut oil                       | -             | 20 °C | ●            |
| Cod liver oil                     | -             | 20 °C | ●            |
| Cresol                            | 100%          | 20 °C | ●            |
| Cresol                            | -             | 20 °C | ●            |
| Cyclohexane                       | -             | 20 °C | ●            |
| Cyclohexanol                      | -             | 20 °C | ●            |
| Cyclohexanone                     | 100%          | 20 °C | ●            |
| Cyclohexanone                     | -             | 20 °C | ●            |
| Cyclohexene                       | 100%          | 20 °C | ●            |
| Detergents                        | usual         | 20 °C | ●            |
| Detergents                        | -             | 20 °C | ●            |
| Dibutyl ether                     | -             | 20 °C | ●            |
| Dibutyl phthalate                 | -             | 20 °C | ●            |
| Dichloroacetic acid               | -             | 20 °C | ●            |
| Dichloroethane                    | -             | 20 °C | ●            |
| Diesel                            | -             | 20 °C | ●            |
| Diesel                            | -             | 20 °C | ●            |
| Diethylene oxide                  | -             | 20 °C | ●            |
| Diglycolic acid, aqueous          | 30%           | 20 °C | ●            |
| Dimethyl formamide (DMF)          | -             | 20 °C | ●            |
| Dimethylamine                     | -             | 20 °C | ●            |
| Dioxane                           | -             | 20 °C | ●            |
| Essential oils                    | -             | 20 °C | ●            |
| Ethyl acetate                     | -             | 20 °C | ●            |
| Ethyl acetate                     | 100%          | 20 °C | ●            |
| Ethyl alcohol (ethanol)           | 96%           | 20 °C | ●            |
| Ethylene alcohol                  | 96%           | 20 °C | ●            |
| Ethylene chloride                 | 100%          | 20 °C | ●            |
| Ethylene chloride                 | -             | 20 °C | ●            |
| Ethylene diamine                  | -             | 20 °C | ●            |
| Ethylene glycol                   | -             | 20 °C | ●            |
| Ferric chloride, aqueous          | any           | 20 °C | ●            |
| Ferric nitrate, aqueous saturated | -             | 20 °C | ●            |
| Ferric nitrate, aqueous saturated | -             | 20 °C | ●            |

| Kemikalie                                 | Koncentration | Temp. | Beständighet |
|-------------------------------------------|---------------|-------|--------------|
| Ferric sulphate, aqueous saturated        | -             | 20 °C | ●            |
| Ferric sulphate, aqueous saturated        | -             | 20 °C | ●            |
| Ferrous (II) chloride, aqueous saturated  | -             | 20 °C | ●            |
| Ferrous (II) sulfate, aqueous saturated   | -             | 20 °C | ●            |
| Ferrous (III) chloride, aqueous saturated | -             | 20 °C | ●            |
| Food oil                                  | -             | 20 °C | ●            |
| Formaldehyde (aqueous)                    | 40%           | 20 °C | ●            |
| Formaldehyde, aqueous                     | ≤40%          | 20 °C | ●            |
| Formic acid                               | 10%           | 20 °C | ●            |
| Formic acid, aqueous                      | 85%           | 20 °C | ●            |
| Frigen 12 (Freon 12)                      | 100%          | 20 °C | ●            |
| Frost protection agent                    | -             | 20 °C | ●            |
| Fruit juices                              | any           | 20 °C | ●            |
| Fuel (aromatic free)                      | -             | 20 °C | ●            |
| Fuel oil                                  | -             | 20 °C | ●            |
| Fuel oil                                  | -             | 20 °C | ●            |
| Furfural                                  | -             | 20 °C | ●            |
| Glycerine                                 | 100%          | 20 °C | ●            |
| Glycerine, aqueous                        | any           | 20 °C | ●            |
| Glycol                                    | 100%          | 20 °C | ●            |
| Glycol, aqueous                           | as supplied   | 20 °C | ●            |
| Glysantin                                 | -             | 20 °C | ●            |
| Heptane                                   | 100%          | 20 °C | ●            |
| Heptane                                   | -             | 20 °C | ●            |
| Hexane                                    | -             | 20 °C | ●            |
| Honey                                     | -             | 20 °C | ●            |
| Hydrobromic acid, aqueous                 | 50%           | 20 °C | ●            |
| Hydrochloric acid                         | 10%           | 20 °C | ●            |
| Hydrochloric acid (concentrated)          | concentrated  | 20 °C | ●            |
| Hydrochloric acid, aqueous                | any           | 20 °C | ●            |
| Hydrofluoric acid                         | 40%           | 20 °C | ●            |
| Hydrogen peroxide                         | 10%           | 20 °C | ●            |
| Hydrogen sulfide (aqueous)                | -             | 20 °C | ●            |
| Ink                                       | -             | 20 °C | ●            |
| Iodine in potassium iodide solution       | 3% iodine     | 20 °C | ●            |

| Kemikalie                                | Koncentration              | Temp. | Beständighet |
|------------------------------------------|----------------------------|-------|--------------|
| Isooctane                                | -                          | 20 °C | ●            |
| Isopropanol                              | -                          | 20 °C | ●            |
| Isopropyl alcohol                        | 100%                       | 20 °C | ●            |
| Isopropyl ether                          | -                          | 20 °C | ●            |
| Jam                                      | -                          | 20 °C | ●            |
| Kerosene                                 | -                          | 20 °C | ●            |
| Linseed oil                              | technically grade          | 20 °C | ●            |
| Linseed oil                              | -                          | 20 °C | ●            |
| Lithium bromide                          | -                          | 20 °C | ●            |
| Maleic acid, aqueous                     | any                        | 20 °C | ●            |
| Menthol                                  | -                          | 20 °C | ●            |
| Mercurochrome                            | -                          | 20 °C | ●            |
| Mercury                                  | -                          | 20 °C | ●            |
| Methanol                                 | technically grade          | 20 °C | ●            |
| Methyl alcohol (methanol)                | 100%                       | 20 °C | ●            |
| Methyl chloride                          | gaseous, technically grade | 20 °C | ●            |
| Methyl ethyl ketone (MEK)                | 100%                       | 20 °C | ●            |
| Methyl ethyl ketone (MEK)                | technically grade          | 20 °C | ●            |
| Methylene chloride                       | 100%                       | 20 °C | ●            |
| Milk                                     | -                          | 20 °C | ●            |
| Milk                                     | -                          | 20 °C | ●            |
| Mineral oil (aromatic free)              | -                          | 20 °C | ●            |
| Molasses                                 | -                          | 20 °C | ●            |
| Motor oil (heavy duty) without additives | -                          | 20 °C | ●            |
| Naphtha                                  | -                          | 20 °C | ●            |
| Naphthalene                              | -                          | 20 °C | ●            |
| Nitric acid                              | 10%                        | 20 °C | ●            |
| Nitric acid (50%)                        | 50%                        | 20 °C | ●            |
| Nitric acid, aqueous                     | 50%                        | 20 °C | ●            |
| Nitric acid, aqueous                     | 25%                        | 20 °C | ●            |
| Nitrobenzene                             | -                          | 20 °C | ●            |
| Nitrobenzene                             | -                          | 20 °C | ●            |
| Oils, vegetable and animal               | -                          | 20 °C | ●            |
| Oleic acid                               | -                          | 20 °C | ●            |

| Kemikalie                     | Koncentration     | Temp. | Beständighet |
|-------------------------------|-------------------|-------|--------------|
| Oleum (fuming sulphuric acid) | any               | 20 °C | <div></div>  |
| Oxalic acid                   | -                 | 20 °C | <div></div>  |
| Oxalic acid, aqueous          | any               | 20 °C | <div></div>  |
| Oxygen                        | -                 | 20 °C | <div></div>  |
| Ozone                         | 50 ppm            | 20 °C | <div></div>  |
| Ozone (gas)                   | ≤0.5 ppm          | 20 °C | <div></div>  |
| Paraffin oil                  | 100%              | 20 °C | <div></div>  |
| Perchloric acid, aqueous      | 20%               | 20 °C | <div></div>  |
| Perchloric acid, aqueous      | 50%               | 20 °C | <div></div>  |
| Perchloric acid, aqueous      | 70%               | 20 °C | <div></div>  |
| Perchloroethylene             | -                 | 20 °C | <div></div>  |
| Petroleum                     | -                 | 20 °C | <div></div>  |
| Petroleum ether               | -                 | 20 °C | <div></div>  |
| Petroleum ether               | 100%              | 20 °C | <div></div>  |
| Phenol                        | -                 | 20 °C | <div></div>  |
| Phenol (aqueous)              | ≈9%               | 20 °C | <div></div>  |
| Phosphoric acid               | 50%               | 20 °C | <div></div>  |
| Phosphoric acid, aqueous      | 50%               | 20 °C | <div></div>  |
| Phosphoric acid, aqueous      | 80% L 95%         | 20 °C | <div></div>  |
| Phosphorus trichloride        | -                 | 20 °C | <div></div>  |
| Photographic developer        | -                 | 20 °C | <div></div>  |
| Photographic emulsion         | as supplied       | 20 °C | <div></div>  |
| Photographic fixing bath      | as supplied       | 20 °C | <div></div>  |
| Phthalic acid, aqueous        | 50%               | 20 °C | <div></div>  |
| Polyester resins              | -                 | 20 °C | <div></div>  |
| Potassium hydroxide solution  | 50%               | 20 °C | <div></div>  |
| Premium fuel                  | -                 | 20 °C | <div></div>  |
| Propionic acid, aqueous       | any               | 20 °C | <div></div>  |
| Propyl alcohol                | -                 | 20 °C | <div></div>  |
| Pyridine                      | -                 | 20 °C | <div></div>  |
| Pyridine                      | -                 | 20 °C | <div></div>  |
| Sea water                     | -                 | 20 °C | <div></div>  |
| Silicone oil                  | technically grade | 20 °C | <div></div>  |
| Silicone oil                  | -                 | 20 °C | <div></div>  |

| Kemikalie                                | Koncentration     | Temp. | Beständighet |
|------------------------------------------|-------------------|-------|--------------|
| Sodium borate (borax)                    | -                 | 20 °C | ●            |
| Sodium bromide                           | -                 | 20 °C | ●            |
| Sodium carbonate (aqueous)               | -                 | 20 °C | ●            |
| Sodium chloride (aqueous)                | -                 | 20 °C | ●            |
| Sodium hydrogen sulfite                  | -                 | 20 °C | ●            |
| Sodium hydroxide solution (60%)          | 60%               | 20 °C | ●            |
| Sodium hydroxide solution (caustic soda) | 15%               | 20 °C | ●            |
| Sodium hydroxide, aqueous                | any               | 20 °C | ●            |
| Sodium hydroxide, solid                  | -                 | 20 °C | ●            |
| Sodium nitrate (aqueous)                 | -                 | 20 °C | ●            |
| Sodium thiosulfate                       | -                 | 20 °C | ●            |
| Stearic acid                             | -                 | 20 °C | ●            |
| Sugar syrup                              | -                 | 20 °C | ●            |
| Sulphuric acid                           | 96%               | 20 °C | ●            |
| Sulphuric acid, aqueous                  | ≤50%              | 20 °C | ●            |
| Sulphuric acid, aqueous                  | 98%               | 20 °C | ●            |
| Sulphuric acid, aqueous                  | 80%               | 20 °C | ●            |
| Sulphuric acid, aqueous                  | 70%               | 20 °C | ●            |
| Tallow                                   | technically grade | 20 °C | ●            |
| Tannic acid (tannin), aqueous            | 10%               | 20 °C | ●            |
| Tetrahydrofuran (THF)                    | technically grade | 20 °C | ●            |
| Tetrahydrofuran (THF)                    | 100%              | 20 °C | ●            |
| Thionyl chloride                         | -                 | 20 °C | ●            |
| Thiophene                                | -                 | 20 °C | ●            |
| Tin (II) chloride, aqueous               | any               | 20 °C | ●            |
| Tin (IV) chloride, aqueous               | saturated         | 20 °C | ●            |
| Toluene                                  | 100%              | 20 °C | ●            |
| Toluene                                  | technically grade | 20 °C | ●            |
| Transformer oil                          | -                 | 20 °C | ●            |
| Transformer oil (insulating oil)         | technically grade | 20 °C | ●            |
| Trichloroacetic acid                     | technically grade | 20 °C | ●            |
| Trichloroethylene                        | technically grade | 20 °C | ●            |
| Trichloroethylene                        | 100%              | 20 °C | ●            |
| Triethanolamine                          | -                 | 20 °C | ●            |

| Kemikalie          | Koncentration     | Temp. | Beständighet |
|--------------------|-------------------|-------|--------------|
| Turpentine oil     | technically grade | 20 °C | ●            |
| Urea, vattenl.     | ≤33%              | 20 °C | ●            |
| Vaseline           | technically grade | 20 °C | ●            |
| Vinegar (standard) | 5-10%             | 20 °C | ●            |
| Water              | -                 | 20 °C | ●            |
| Water, distilled   | -                 | 20 °C | ●            |
| Wine               | -                 | 20 °C | ●            |
| Xylene             | -                 | 20 °C | ●            |
| Xylene             | -                 | 20 °C | ●            |
| Zinc sludge        | -                 | 20 °C | ●            |