



PEEK GF30 22x3000 mm beige

Artikelnr P1500922

1. Tekniskt datablad

Egenskap	Värde	Enhet	Standard
Density	1.51	g/cm³	ISO 1183
Tensile Strength	105	MPa	ISO 527
Modulus of elasticity (tensile)	6380	MPa	ISO 527
Breakdown Voltage	180	MPa	ISO 527
Break Elongation	2.7	%	ISO 527
Melting point	341	°C	DIN EN ISO 11357
Maximal operating temperature (short-term)	300	°C	
Maximum Operating Temperature	260	°C	
Heat deflection temperature (HDT/A)	328	°C	ISO 75
Vicat softening temperature (VST/B/50)	50	°C	ISO 306
Dielectric Strength	20	kV/mm	IEC 60243-1
Volume Resistivity	10¹³	Ω·m	IEC 60093
Dielectric Constant (1 MHz)	1	-	IEC 60250
Dielectric loss factor (1 MHz)	0.0	-	IEC 60250
Flammability Classification (UL 94)	0		UL 94
Flexural Strength	164	MPa	ISO 178
Thermal Conductivity	0.35	W/(m·K)	ISO 22007-4
Surface Resistivity	10¹³	Ω·m	IEC 60093
Water absorption to saturation	0.3	%	ISO 62
Impact Resistance (Charpy)	32	kJ/m²	ISO 179
Thermal Expansion Coefficient	0.38	10⁻⁶/K	ISO 11359
Hardness Shore D	90	° Shore D	ISO 868

2. Kemisk beständighet

Beständig Delvis beständig Ej beständig

Kemikalie	Konc.	Resultat
-----------	-------	----------

Kemikalie	Konc.	Resultat
1,4-Dioxane	100	●
2-Hydroxypropionic acid (lactic acid)	90	●
Acetic acid	100	●
Acetone	100	●
Ammonia	â€”	●
Ammonium chloride	â€”	●
Amyl alcohol	â€”	●
Apple juice	â€”	●
Benzene	â€”	●
Boric acid	100	●
Brake fluid	â€”	●
Butyl acetate	â€”	●
Calcium chloride	â€”	●
Carbon tetrachloride	â€”	●
Chlorine (gas)	100	●
Chlorobenzene	100	●
Chloroform	â€”	●
Citric acid	10	●
Cyclohexanone	100	●
Cyclohexene	100	●
Diesel	â€”	●
Diethylene oxide	â€”	●
Ethyl acetate	100	●
Ethyl alcohol (ethanol)	96	●
Ethylene chloride	100	●
Food oil	â€”	●
Formaldehyde (aqueous)	40	●
Formic acid	10	●
Frost protection agent	â€”	●
Fuel oil	â€”	●
Fuel, aromatic free	â€”	●
Glycerine	100	●
Glycol	100	●
Heptane	100	●

Kemikalie	Konc.	Resultat
Hydrochloric acid	10	
Hydrochloric acid (concentrated)	â€	
Hydrofluoric acid	40	
Hydrogen peroxide	10	
Hydrogen sulfide (aqueous)	â€	
Isopropyl alcohol	100	
Linseed oil	â€	
Mercurochrome	â€	
Methyl alcohol (methanol)	100	
Methyl ethyl ketone (MEK)	100	
Methylene chloride	100	
Milk	â€	
Mineral oils (aromatic free)	â€	
Nitric acid	10	
Nitric acid	50	
Nitrobenzene	â€	
Oxalic acid	â€	
Ozone (gas)	â€	
Paraffin oil	100	
Perchloroethylene	â€	
Petroleum	100	
Petroleum ether	100	
Phenol (aqueous)	9	
Phosphoric acid	50	
Potassium hydroxide solution	50	
Premium fuel	â€	
Propyl alcohol	â€	
Pyridine	â€	
Silicone oil	â€	
Sodium carbonate (aqueous)	â€	
Sodium chloride (aqueous)	â€	
Sodium hydrogen sulfite	â€	
Sodium hydroxide solution (caustic soda)	60	
Sodium hydroxide solution (caustic soda)	15	
Sodium nitrate (aqueous)	â€	

Kemikalie	Konc.	Resultat
Sodium thiosulfate	â€	●
Sulphuric acid	96	●
Tetrahydrofuran (THF)	100	●
Toluene	100	●
Transformer oil	â€	●
Trichloroethylene	100	●
Vinegar (standard)	5-10	●
Water	â€	●
Xylene	â€	●