



## PEEK MG 30x1000 mm black

Artikelnr P1501602

Kategori PEEK

### Tekniska egenskaper

#### Density & Weight

Egenskap	VÄrde	Enhet	Provningsstandard
Density	1.31	g/cm <sup>3</sup>	ISO 1183

#### Tensile Properties

Egenskap	VÄrde	Enhet	Provningsstandard
Tensile Strength	112	MPa	ISO527-2
Modulus of elasticity (tensile)	4400	MPa	ISO 527-2
Breakdown Voltage	67	MPa	ISO 527
Break Elongation	20	%	ISO 527-2

#### Temperature Limits

Egenskap	VÄrde	Enhet	Provningsstandard
Melting point	340	Å°C	ISO 3146
Maximal operating temperature (short-term)	291	Å°C	UL746B
Maximum Operating Temperature	245	Å°C	
Minimum temperature	-35	Å°C	
Heat deflection temperature (HDT/A)	160	Å°C	ISO 75-2
Heat deflection temperature (HDT/B)	240	Å°C	ISO 75
Vicat softening temperature (VST/B/50)	50	Å°C	ISO 306

#### Insulation Properties

Egenskap	VÄrde	Enhet	Provningsstandard
----------	-------	-------	-------------------

Egenskap	Värde	Enhet	Provningsstandard
Dielectric Strength	24	kV/mm	IEC 60243-1
Volume Resistivity	$10^{14}$	$\Omega \cdot \text{cm}$	IEC 60093
Dielectric Constant (1 MHz)	3.6	-	IEC 60250
Dielectric Constant (100 Hz)	3.2	-	IEC 60250
Dielectric loss factor (1 MHz)	0.0	-	IEC 60250
Dielectric loss factor (100 Hz)	0.0	-	IEC 60250

### Fire Classification

Egenskap	Värde	Enhet	Provningsstandard
Flammability Classification (UL 94)	0		UL 94

### Flexural Properties

Egenskap	Värde	Enhet	Provningsstandard
Flexural Strength	110	MPa	ISO 527-2

### Thermal Conductivity

Egenskap	Värde	Enhet	Provningsstandard
Thermal Conductivity	0.25	W/(m·K)	DIN 52612

### Static spread

Egenskap	Värde	Enhet	Provningsstandard
Surface Resistivity	$10^{14}$	$\Omega$	IEC 60093
Comparative Tracking Index (CTI)	150	V	IEC 60112

### Moisture Absorption

Egenskap	Värde	Enhet	Provningsstandard
Water absorption to saturation	0.2	%	ISO 62
Water Absorption to Saturation	0.45	%	ISO 62

### Impact Resistance

Egenskap	Värde	Enhet	Provningsstandard
Notched impact strength (Charpy)	3.5	$\text{kJ/m}^2$	ISO 179/1eA
Impact Resistance (Charpy)	92	$\text{kJ/m}^2$	ISO179/1eU

### Thermal Expansion

Egenskap	Värde	Enhet	Provningsstandard
----------	-------	-------	-------------------

Egenskap	V�rde	Enhet	Provningsstandard
Thermal Expansion Coefficient	0.5	10 <sup>-6</sup> /K	DIN 11359

### Hardness

Egenskap	V�rde	Enhet	Provningsstandard
Hardness Shore D	90	� Shore D	DIN EN ISO 868
Ball pressure hardness	230	MPa	ISO 2039-1

### Godk nnanden

- EU 10/2011
- FDA
- REACH
- RoHS
- UL 94