

PET ZX 16x1000 mm light grÅ

Artikelnr P1004103

● Beständig
 ● Delvis beständig
 ● Ej beständig

Kemikalie	Koncentration	Temp.	Beständighet
1,4-Dioxane	100	60 Å°C	●
1,4-Dioxane	100	20 Å°C	●
Acetic acid	100	20 Å°C	●
Acetic acid	100	60 Å°C	●
Acetic acid	100%	20 Å°C	●
Acetone	100	60 Å°C	●
Acetone	100	20 Å°C	●
Ammonia	conc.	60 Å°C	●
Ammonia	conc.	20 Å°C	●
Apple juice	â€	20 Å°C	●
Apple juice	â€	20 Å°C	●
Benzene	â€	20 Å°C	●
Benzene	â€	60 Å°C	●
Bleaching solution	â€	20 Å°C	●
Brake fluid	â€	60 Å°C	●
Brake fluid	â€	20 Å°C	●
Butyl acetate	â€	20 Å°C	●
Butyl acetate	â€	60 Å°C	●
Calcium chloride	â€	60 Å°C	●
Calcium chloride	â€	20 Å°C	●
Carbon disulphide	100	20 Å°C	●
Carbon disulphide	100	60 Å°C	●
Carbon tetrachloride	â€	20 Å°C	●
Carbon tetrachloride	â€	60 Å°C	●
Carbon tetrachloride	â€	20 Å°C	●
Chlorobenzene	100%	20 Å°C	●
Chlorobenzene	100	60 Å°C	●

Kemikalie	Koncentration	Temp.	Best�ndighet
Chlorobenzene	100	20 �C	●
Chloroform	��	20 �C	●
Chloroform	��	60 �C	●
Citric acid	10	20 �C	●
Citric acid	10	60 �C	●
Diesel	��	60 �C	●
Diesel	��	20 �C	●
Diethylene oxide	��	20 �C	●
Diethylene oxide	��	20 �C	●
Ethyl acetate	100	20 �C	●
Ethyl acetate	100	60 �C	●
Ethyl alcohol (ethanol)	96	60 �C	●
Ethyl alcohol (ethanol)	96%	20 �C	●
Ethyl alcohol (ethanol)	96	20 �C	●
Ethylene chloride	100	20 �C	●
Ethylene chloride	100	60 �C	●
Food oil	��	60 �C	●
Food oil	��	20 �C	●
Food oil	��	20 �C	●
Formic acid	10	20 �C	●
Formic acid	10	60 �C	●
Frost protection agent	��	60 �C	●
Frost protection agent	��	20 �C	●
Fuel oil	��	20 �C	●
Fuel oil	��	60 �C	●
Fuel, aromatic free	��	20 �C	●
Fuel, aromatic free	��	60 �C	●
Glycerine	100%	20 �C	●
Glycerine	100	60 �C	●
Glycerine	100	20 �C	●
Glycol	100	60 �C	●
Glycol	100	20 �C	●
Heptane	100	60 �C	●
Heptane	100	20 �C	●

Kemikalie	Koncentration	Temp.	Best�ndighet
Hydrochloric acid	conc.	20 �C	●
Hydrochloric acid	10	20 �C	●
Hydrochloric acid	conc.	60 �C	●
Hydrochloric acid	10	60 �C	●
Hydrochloric acid (concentrated)	conc.	20 �C	●
Hydrofluoric acid	40	60 �C	●
Hydrofluoric acid	40%	20 �C	●
Hydrofluoric acid	40	20 �C	●
Hydrogen peroxide	10	60 �C	●
Hydrogen peroxide	10	20 �C	●
Hydrogen sulfide, aqueous	�	20 �C	●
Isopropyl alcohol	100	20 �C	●
Isopropyl alcohol	100	60 �C	●
Isopropyl alcohol	100%	20 �C	●
Linseed oil	�	60 �C	●
Linseed oil	�	20 �C	●
Mercurochrome	�	20 �C	●
Methyl alcohol (methanol)	100	60 �C	●
Methyl alcohol (methanol)	100%	20 �C	●
Methyl alcohol (methanol)	100	20 �C	●
Methyl ethyl ketone (MEK)	100	20 �C	●
Methyl ethyl ketone (MEK)	100	60 �C	●
Methylene chloride	100	20 �C	●
Methylene chloride	100	60 �C	●
Milk	�	20 �C	●
Milk	�	60 �C	●
Mineral oils, aromatic free	�	60 �C	●
Mineral oils, aromatic free	�	20 �C	●
Nitric acid	50	60 �C	●
Nitric acid	10	20 �C	●
Nitric acid	50	20 �C	●
Nitric acid	10%	20 �C	●
Nitric acid	10	60 �C	●
Paraffin oil	100	60 �C	●

Kemikalie	Koncentration	Temp.	Best�ndighet
Paraffin oil	100	20 �C	●
Perchloroethylene	��	20 �C	●
Perchloroethylene	��	60 �C	●
Petroleum	100	20 �C	●
Petroleum	100%	20 �C	●
Petroleum ether	100	20 �C	●
Petroleum ether	100%	20 �C	●
Petroleum ether	100	60 �C	●
Phenol, aqueous	ca.9	20 �C	●
Phosphoric acid	50	20 �C	●
Phosphoric acid	50	60 �C	●
Potassium hydroxide solution	50	20 �C	●
Potassium hydroxide solution	50	60 �C	●
Premium fuel	��	20 �C	●
Premium fuel	��	60 �C	●
Propyl alcohol	��	60 �C	●
Propyl alcohol	��	20 �C	●
Silicone oil	��	20 �C	●
Silicone oil	��	60 �C	●
Sodium carbonate, aqueous	��	60 �C	●
Sodium carbonate, aqueous	��	20 �C	●
Sodium chloride, aqueous	��	60 �C	●
Sodium chloride, aqueous	��	20 �C	●
Sodium hydrogen sulfite	��	20 �C	●
Sodium hydrogen sulfite	��	60 �C	●
Sodium hydrogen sulfite	��	20 �C	●
Sodium hydroxide solution (caustic soda)	60	60 �C	●
Sodium hydroxide solution (caustic soda)	60	20 �C	●
Sodium hydroxide solution (caustic soda)	15	20 �C	●
Sodium hydroxide solution (caustic soda)	15	60 �C	●
Sodium nitrate, aqueous	��	20 �C	●
Sodium thiosulfate	��	20 �C	●
Sulphuric acid	96	60 �C	●
Sulphuric acid	96	20 �C	●

Kemikalie	Koncentration	Temp.	Best�ndighet
Tetrahydrofuran (THF)	100	20 �C	●
Tetrahydrofuran (THF)	100	60 �C	●
Toluene	100%	20 �C	●
Toluene	100	60 �C	●
Toluene	100	20 �C	●
Transformer oil	��	20 �C	●
Transformer oil	��	60 �C	●
Trichloroethylene	100	60 �C	●
Trichloroethylene	100	20 �C	●
Vinegar, standard	5-10%	20 �C	●
Vinegar, standard	5-10	20 �C	●
Vinegar, standard	5-10	60 �C	●
Water	��	60 �C	●
Water	��	20 �C	●
Xylene	��	20 �C	●
Xylene	��	60 �C	●