



Artikelnr P1003556

Egenskap	V�rde	Enhet	Standard
Density	1.46	g/cm����	ISO 1183
Tensile Strength	52	MPa	ISO 527
Modulus of elasticity (tensile)	3400	MPa	ISO 527-2
Breakdown Voltage	58	MPa	ISO 527
Break Elongation	5	%	ISO 527-2
Melting point	224	��C	ISO 3146
Maximal operating temperature (short-term)	138.75	��C	UL746B
Maximum Operating Temperature	97	��C	
Minimum temperature	-25	��C	
Heat deflection temperature (HDT/A)	85	��C	ISO 75
Heat deflection temperature (HDT/B)	100	��C	ISO 75
Vicat softening temperature (VST/B/50)	219	��C	ISO 306
Dielectric Strength	22	kV/mm	IEC 60243-1
Volume Resistivity	10������	��������cm	DIN EN 62631-3-1
Dielectric Constant (1 MHz)	3.3	-	IEC 60250
Dielectric loss factor (1 MHz)	0.0	-	IEC 60250
Dielectric loss factor (100 Hz)	0.0	-	IEC 60250
Flexural Strength	75.25	MPa	ISO 178
Thermal Conductivity	0.33	W/(m��K)	DIN 52612
Surface Resistivity	10������	����	IEC 60093
Comparative Tracking Index (CTI)	600	V	IEC 60112
Water absorption to saturation	0.02	%	ISO 62
Water Absorption to Saturation	0.02	%	ISO 62
Notched impact strength (Charpy)	90	kJ/m����	ISO 180
Impact Resistance (Charpy)	37	kJ/m����	ISO 179/1eU
Thermal Expansion Coefficient	0.8	10������ /K	DIN 11359

Egenskap	V�rde	Enhet	Standard
Hardness Shore D	77	� Shore D	ISO 868
Rockwell hardness	112	M-scale	
Ball pressure hardness	166	MPa	ISO 2039

2. Kemisk best ndighet

● Best ndig ● Delvis best ndig ● Ej best ndig

Kemikalie	Konc.	Resultat
1,4-Dioxane	100	●
1,4-Dioxane	100	●
Acetic acid	100	●
Acetic acid	100	●
Acetic acid	100%	●
Acetone	100	●
Acetone	100	●
Ammonia	conc.	●
Ammonia	conc.	●
Apple juice	��	●
Apple juice	��	●
Benzene	��	●
Benzene	��	●
Bleaching solution	��	●
Brake fluid	��	●
Brake fluid	��	●
Butyl acetate	��	●
Butyl acetate	��	●
Calcium chloride	��	●
Calcium chloride	��	●
Carbon disulphide	100	●
Carbon disulphide	100	●
Carbon tetrachloride	��	●
Carbon tetrachloride	��	●
Carbon tetrachloride	��	●
Chlorobenzene	100	●
Chlorobenzene	100	●
Chlorobenzene	100%	●

Kemikalie	Konc.	Resultat
Chloroform	â€”	
Chloroform	â€”	
Citric acid	10	
Citric acid	10	
Diesel	â€”	
Diesel	â€”	
Diethylene oxide	â€”	
Diethylene oxide	â€”	
Ethyl acetate	100	
Ethyl acetate	100	
Ethyl alcohol (ethanol)	96%	
Ethyl alcohol (ethanol)	96	
Ethyl alcohol (ethanol)	96	
Ethylene chloride	100	
Ethylene chloride	100	
Food oil	â€”	
Food oil	â€”	
Food oil	â€”	
Formic acid	10	
Formic acid	10	
Frost protection agent	â€”	
Frost protection agent	â€”	
Fuel oil	â€”	
Fuel oil	â€”	
Fuel, aromatic free	â€”	
Fuel, aromatic free	â€”	
Glycerine	100	
Glycerine	100	
Glycerine	100%	
Glycol	100	
Glycol	100	
Heptane	100	
Heptane	100	
Hydrochloric acid	conc.	

Kemikalie	Konc.	Resultat
Hydrochloric acid	10	●
Hydrochloric acid	conc.	●
Hydrochloric acid	10	●
Hydrochloric acid (concentrated)	conc.	●
Hydrofluoric acid	40	●
Hydrofluoric acid	40%	●
Hydrofluoric acid	40	●
Hydrogen peroxide	10	●
Hydrogen peroxide	10	●
Hydrogen sulfide, aqueous	â€”	●
Isopropyl alcohol	100	●
Isopropyl alcohol	100	●
Isopropyl alcohol	100%	●
Linseed oil	â€”	●
Linseed oil	â€”	●
Mercurochrome	â€”	●
Methyl alcohol (methanol)	100	●
Methyl alcohol (methanol)	100%	●
Methyl alcohol (methanol)	100	●
Methyl ethyl ketone (MEK)	100	●
Methyl ethyl ketone (MEK)	100	●
Methylene chloride	100	●
Methylene chloride	100	●
Milk	â€”	●
Milk	â€”	●
Mineral oils, aromatic free	â€”	●
Mineral oils, aromatic free	â€”	●
Nitric acid	50	●
Nitric acid	10	●
Nitric acid	50	●
Nitric acid	10%	●
Nitric acid	10	●
Paraffin oil	100	●
Paraffin oil	100	●
Perchloroethylene	â€”	●

Kemikalie	Konc.	Resultat
Perchloroethylene	â€”	
Petroleum	100	
Petroleum	100%	
Petroleum ether	100	
Petroleum ether	100%	
Petroleum ether	100	
Phenol, aqueous	ca.9	
Phosphoric acid	50	
Phosphoric acid	50	
Potassium hydroxide solution	50	
Potassium hydroxide solution	50	
Premium fuel	â€”	
Premium fuel	â€”	
Propyl alcohol	â€”	
Propyl alcohol	â€”	
Silicone oil	â€”	
Silicone oil	â€”	
Sodium carbonate, aqueous	â€”	
Sodium carbonate, aqueous	â€”	
Sodium chloride, aqueous	â€”	
Sodium chloride, aqueous	â€”	
Sodium hydrogen sulfite	â€”	
Sodium hydrogen sulfite	â€”	
Sodium hydrogen sulfite	â€”	
Sodium hydroxide solution (caustic soda)	60	
Sodium hydroxide solution (caustic soda)	60	
Sodium hydroxide solution (caustic soda)	15	
Sodium hydroxide solution (caustic soda)	15	
Sodium nitrate, aqueous	â€”	
Sodium thiosulfate	â€”	
Sulphuric acid	96	
Sulphuric acid	96	
Tetrahydrofuran (THF)	100	
Tetrahydrofuran (THF)	100	

Kemikalie	Konc.	Resultat
Toluene	100%	
Toluene	100	
Toluene	100	
Transformer oil	â€”	
Transformer oil	â€”	
Trichloroethylene	100	
Trichloroethylene	100	
Vinegar, standard	5-10%	
Vinegar, standard	5-10	
Vinegar, standard	5-10	
Water	â€”	
Water	â€”	
Xylene	â€”	
Xylene	â€”	