



# POM C 140x3000 mm traffic rÄ¶d

Artikelnr P1005210

Beständig Delvis beständig Ej beständig

| Kemikalie                             | Koncentration | Temp.  | Beständighet |
|---------------------------------------|---------------|--------|--------------|
| 1,4-Dioxane                           | 100%          | 20 Å°C |              |
| 2-Hydroxypropionic acid (lactic acid) | 90%           | 20 Å°C |              |
| Acetic acid                           | 100%          | 20 Å°C |              |
| Acetone                               | 100%          | 20 Å°C |              |
| Ammonia                               | conc.         | 20 Å°C |              |
| Ammonium chloride                     | â€”           | 20 Å°C |              |
| Amyl alcohol                          | â€”           | 20 Å°C |              |
| Apple juice                           | â€”           | 20 Å°C |              |
| Benzene                               | â€”           | 20 Å°C |              |
| Bleaching solution                    | 12.5 cl       | 20 Å°C |              |
| Boric acid                            | 100%          | 20 Å°C |              |
| Brake fluid                           | â€”           | 20 Å°C |              |
| Butyl acetate                         | â€”           | 20 Å°C |              |
| Calcium chloride                      | â€”           | 20 Å°C |              |
| Carbon disulphide                     | 100%          | 20 Å°C |              |
| Carbon tetrachloride                  | â€”           | 20 Å°C |              |
| Chlorobenzene                         | 100%          | 20 Å°C |              |
| Chloroform                            | â€”           | 20 Å°C |              |
| Citric acid                           | 10%           | 20 Å°C |              |
| Cyclohexanone                         | 100%          | 20 Å°C |              |
| Cyclohexene                           | 100%          | 20 Å°C |              |
| Diesel                                | â€”           | 20 Å°C |              |
| Diethylene oxide                      | â€”           | 20 Å°C |              |
| Ethyl acetate                         | 100%          | 20 Å°C |              |
| Ethyl alcohol (ethanol)               | 96%           | 20 Å°C |              |
| Food oil                              | â€”           | 20 Å°C |              |
| Formaldehyde, aqueous                 | 40%           | 20 Å°C |              |

| Kemikalie                        | Koncentration | Temp.  | Best ndighet |
|----------------------------------|---------------|--------|--------------|
| Formic acid                      | 10%           | 20   C |              |
| Frost protection agent           |               | 20   C |              |
| Fuel oil                         |               | 20   C |              |
| Fuel, aromatic free              |               | 20   C |              |
| Glycerine                        | 100%          | 20   C |              |
| Glycol                           | 100%          | 20   C |              |
| Heptane                          | 100%          | 20   C |              |
| Hydrochloric acid                | 10%           | 20   C |              |
| Hydrochloric acid (concentrated) | conc.         | 20   C |              |
| Hydrofluoric acid                | 40%           | 20   C |              |
| Hydrogen peroxide                | 10%           | 20   C |              |
| Hydrogen sulfide, aqueous        |               | 20   C |              |
| Isopropyl alcohol                | 100%          | 20   C |              |
| Linseed oil                      |               | 20   C |              |
| Mercurochrome                    |               | 20   C |              |
| Methyl alcohol (methanol)        | 100%          | 20   C |              |
| Methyl ethyl ketone (MEK)        | 100%          | 20   C |              |
| Methylene chloride               | 100%          | 20   C |              |
| Milk                             |               | 20   C |              |
| Mineral oils (aromatic free)     |               | 20   C |              |
| Nitric acid                      | 10%           | 20   C |              |
| Nitric acid (50%)                | 50%           | 20   C |              |
| Nitrobenzene                     |               | 20   C |              |
| Oxalic acid                      |               | 20   C |              |
| Ozone (gas)                      |     0.5 ppm   | 20   C |              |
| Paraffin oil                     | 100%          | 20   C |              |
| Perchloroethylene                |               | 20   C |              |
| Petroleum                        | 100%          | 20   C |              |
| Petroleum ether                  | 100%          | 20   C |              |
| Phenol, aqueous                  | ca. 9%        | 20   C |              |
| Phosphoric acid                  | 50%           | 20   C |              |
| Potassium hydroxide solution     | 50%           | 20   C |              |
| Premium fuel                     |               | 20   C |              |
| Propyl alcohol                   |               | 20   C |              |
| Silicone oil                     |               | 20   C |              |

| Kemikalie                       | Koncentration | Temp.  | Best ndighet |
|---------------------------------|---------------|--------|--------------|
| Sodium carbonate, aqueous       |               | 20   C |              |
| Sodium chloride, aqueous        |               | 20   C |              |
| Sodium hydrogen sulfite         |               | 20   C |              |
| Sodium hydroxide solution (15%) | 15%           | 20   C |              |
| Sodium hydroxide solution (60%) | 60%           | 20   C |              |
| Sodium nitrate, aqueous         |               | 20   C |              |
| Sulphuric acid                  | 96%           | 20   C |              |
| Tetrahydrofuran (THF)           | 100%          | 20   C |              |
| Toluene                         | 100%          | 20   C |              |
| Transformer oil                 |               | 20   C |              |
| Trichloroethylene               | 100%          | 20   C |              |
| Vinegar, standard               | 5-10%         | 20   C |              |
| Water                           |               | 20   C |              |
| Xylene                          |               | 20   C |              |