



POM C 200x1000 mm natural

Article No.	P1005054
Category	POM

Technical Properties

Density & Weight

Property	Value	Unit	Test standard
Density	1.24	g/cm³	ASTM D792

Moisture Absorption

Property	Value	Unit	Test standard
Water absorption to saturation	2.2	%	ASTM D955
Water Absorption to Saturation	0.5	%	ASTM D570

Tensile Properties

Property	Value	Unit	Test standard
Tensile Strength	51	MPa	DIN EN ISO 527-2
Modulus of elasticity (tensile)	1200	MPa	ASTM D790
Breakdown Voltage	76.5	MPa	ISO 527
Break Elongation	300	%	ASTM D638

Flexural Properties

Property	Value	Unit	Test standard
Flexural Strength	58	MPa	ASTM D638

Impact Resistance

Property	Value	Unit	Test standard
----------	-------	------	---------------

Static spread

Property	Value	Unit	Test standard
Surface Resistivity	10 ¹³	Ω	IEC 60093
Comparative Tracking Index (CTI)	600	V	IEC 60112

Fire Classification

Property	Value	Unit	Test standard
Flammability Classification (UL 94)	60695		UL 94