



POM CGL 35x3000 mm blå

Artikelnr P1008058

Beständig Delvis beständig Ej beständig

Kemikalie	Koncentration	Temp.	Beständighet
1,4-Dioxane	100%	20 Å°C	
2-Hydroxypropionic Acid	90%	20 Å°C	
Acetic Acid	100%	20 Å°C	
Acetone	100%	20 Å°C	
Ammonia	conc.	20 Å°C	
Ammonium Chloride	â€	20 Å°C	
Amyl Alcohol	â€	20 Å°C	
Apple Juice	â€	20 Å°C	
Benzene	â€	20 Å°C	
Bleaching Solution	12.5 cl	20 Å°C	
Boric Acid	100%	20 Å°C	
Brake Fluid	â€	20 Å°C	
Butyl Acetate	â€	20 Å°C	
Calcium Chloride	â€	20 Å°C	
Carbon Disulfide	100%	20 Å°C	
Carbon Tetrachloride	â€	20 Å°C	
Chlorine (gas)	100%	20 Å°C	
Chlorobenzene	100%	20 Å°C	
Chloroform	â€	20 Å°C	
Citric Acid	10%	20 Å°C	
Cresol	â€	20 Å°C	
Cyclohexanone	100%	20 Å°C	
Cyclohexene	100%	20 Å°C	
Diesel Fuel	â€	20 Å°C	
Diethylene Oxide	â€	20 Å°C	
Ethyl Acetate	100%	20 Å°C	
Ethyl Alcohol	96%	20 Å°C	

Kemikalie	Koncentration	Temp.	Best�ndighet
Ethylene Chloride	100%	20 ��C	�
Food Oil	��	20 ��C	�
Formaldehyde, aqueous	40%	20 ��C	�
Formic Acid	10%	20 ��C	�
Frost Protection Agent	��	20 ��C	�
Fuel, aromatic free	��	20 ��C	�
Glycerine	100%	20 ��C	�
Glycol	100%	20 ��C	�
Heating Oil	��	20 ��C	�
Heptane	100%	20 ��C	�
Hydrochloric Acid	10%	20 ��C	�
Hydrochloric Acid (concentrated)	conc.	20 ��C	�
Hydrofluoric Acid	40%	20 ��C	�
Hydrogen Peroxide	10%	20 ��C	�
Hydrogen Sulfide, aqueous solution	��	20 ��C	�
Isopropyl Alcohol	100%	20 ��C	�
Linseed Oil	��	20 ��C	�
Mercurochrome	��	20 ��C	�
Methyl Alcohol	100%	20 ��C	�
Methyl Ethyl Ketone (MEK)	100%	20 ��C	�
Methylene Chloride	100%	20 ��C	�
Milk	��	20 ��C	�
Mineral Oils (aromatic free)	��	20 ��C	�
Nitric Acid	10%	20 ��C	�
Nitric Acid (50%)	50%	20 ��C	�
Nitrobenzene	��	20 ��C	�
Oxalic Acid	��	20 ��C	�
Ozone Gas	���0.5 ppm	20 ��C	�
Paraffine Oil	100%	20 ��C	�
Perchloroethylene	��	20 ��C	�
Petroleum	100%	20 ��C	�
Petroleum Ether	100%	20 ��C	�
Phenol, aqueous	ca. 9%	20 ��C	�
Phosphoric Acid	50%	20 ��C	�
Potassium Hydroxide liquor	50%	20 ��C	�

