



POM H 45x1000 mm svart

Artikelnr P1008563

1. Tekniskt datablad

| Egenskap | V rde | Enhet | Standard |
|--|---------------------|----------------------|--------------------|
| Density | 3 | g/cm  ³ | DIN EN ISO 1183-1 |
| Tensile Strength | 53 | MPa | DIN EN ISO 527-2 |
| Modulus of elasticity (tensile) | 3000 | MPa | DIN EN ISO 527-2 |
| Break Elongation | 8 | % | DIN EN ISO 527-2 |
| Melting point | 179 |  C | DIN EN ISO 11357 |
| Maximal operating temperature (short-term) | 150 |  C | |
| Maximum Operating Temperature | 110 |  C | |
| Heat deflection temperature (HDT/A) | 141 |  C | |
| Vicat softening temperature (VST/B/50) | 90 |  C | DIN EN ISO 306 |
| Dielectric Strength | 23 | kV/mm | ISO 60243-1 |
| Volume Resistivity | 10  ¹⁴   |    | DIN EN 62631-3-1 |
| Dielectric Constant (1 MHz) | 2.4 | - | IEC 60250 |
| Flammability Classification (UL 94) | 60695 | | UL 94 |
| Flexural Strength | 53 | MPa | DIN EN ISO 527-2 |
| Thermal Conductivity | 0.46 | W/(m K) | ISO 22007-4 |
| Surface Resistivity | 10  ¹⁴   |    | DIN EN 62631-3-2 |
| Water absorption to saturation | 0.1 | % | DIN EN ISO 62 |
| Notched impact strength (Charpy) | 25 | kJ/m  ² | DIN EN ISO 179-1 |
| Impact Resistance (Charpy) | 2 | kJ/m  ² | DIN EN ISO 179-1 |
| Thermal Expansion Coefficient | 23 | 10  ⁻⁶ /K | DIN EN ISO 11359-1 |
| Hardness Shore D | 81 |   Shore D | DIN EN ISO 868 |

2. Kemisk best ndighet

Best ndig Delvis best ndig Ej best ndig

| Kemikalie | Konc. | Resultat |
|-------------|-------|----------|
| 1,4-Dioxane | 100% |   |

| Kemikalie | Konc. | Resultat |
|-------------------------|---------|----------|
| 2-Hydroxypropionic Acid | 90% | ● |
| Acetic Acid | 100% | ● |
| Acetone | 100% | ● |
| Ammonia | conc. | ● |
| Ammonium Chloride | â€” | ● |
| Amyl Alcohol | â€” | ● |
| Apple Juice | â€” | ● |
| Benzene | â€” | ● |
| Bleaching Solution | 12.5 cl | ● |
| Boric Acid | 100% | ● |
| Brake Fluid | â€” | ● |
| Butyl Acetate | â€” | ● |
| Calcium Chloride | â€” | ● |
| Carbon Disulfide | 100% | ● |
| Carbon Tetrachloride | â€” | ● |
| Chlorine (gas) | 100% | ● |
| Chlorobenzene | 100% | ● |
| Chloroform | â€” | ● |
| Citric Acid | 10% | ● |
| Cresol | â€” | ● |
| Cyclohexanone | 100% | ● |
| Cyclohexene | 100% | ● |
| Diesel Fuel | â€” | ● |
| Diethylene Oxide | â€” | ● |
| Ethyl Acetate | 100% | ● |
| Ethyl Alcohol | 96% | ● |
| Ethylene Chloride | 100% | ● |
| Food Oil | â€” | ● |
| Formaldehyde, aqueous | 40% | ● |
| Formic Acid | 10% | ● |
| Frost Protection Agent | â€” | ● |
| Fuel, aromatic free | â€” | ● |
| Glycerine | 100% | ● |
| Glycol | 100% | ● |
| Heating Oil | â€” | ● |

| Kemikalie | Konc. | Resultat |
|------------------------------------|------------|----------|
| Heptane | 100% | ● |
| Hydrochloric Acid | 10% | ● |
| Hydrochloric Acid (concentrated) | conc. | ● |
| Hydrofluoric Acid | 40% | ● |
| Hydrogen Peroxide | 10% | ● |
| Hydrogen Sulfide, aqueous solution | â€” | ● |
| Isopropyl Alcohol | 100% | ● |
| Linseed Oil | â€” | ● |
| Mercurochrome | â€” | ● |
| Methyl Alcohol | 100% | ● |
| Methyl Ethyl Ketone (MEK) | 100% | ● |
| Methylene Chloride | 100% | ● |
| Milk | â€” | ● |
| Mineral Oils (aromatic free) | â€” | ● |
| Nitric Acid | 10% | ● |
| Nitric Acid (50%) | 50% | ● |
| Nitrobenzene | â€” | ● |
| Oxalic Acid | â€” | ● |
| Ozone Gas | â‰‰0.5 ppm | ● |
| Paraffine Oil | 100% | ● |
| Perchloroethylene | â€” | ● |
| Petroleum | 100% | ● |
| Petroleum Ether | 100% | ● |
| Phenol, aqueous | ca. 9% | ● |
| Phosphoric Acid | 50% | ● |
| Potassium Hydroxide liquor | 50% | ● |
| Premium Fuel | â€” | ● |
| Propyl Alcohol | â€” | ● |
| Pyridine | â€” | ● |
| Silicone Oil | â€” | ● |
| Sodium Carbonate, aqueous | â€” | ● |
| Sodium Chloride, aqueous | â€” | ● |
| Sodium Hydrogen Sulfite | â€” | ● |

| Kemikalie | Konc. | Resultat |
|-------------------------------|-------|----------|
| Sodium Hydroxide liquor (15%) | 15% | ● |
| Sodium Hydroxide liquor (60%) | 60% | ● |
| Sodium Nitrate, aqueous | â€” | ● |
| Sodium Thiosulfate | â€” | ● |
| Sulfuric Acid | 96% | ● |
| Tetrahydrofuran, THF | 100% | ● |
| Toluene | 100% | ● |
| Transformer Oil | â€” | ● |
| Trichloroethylene | 100% | ● |
| Vinegar, standard | 5-10% | ● |
| Water | â€” | ● |
| Xylene | â€” | ● |