



PP-H 170x1000 mm grÅ

Artikelnr P1010031

Beständig Delvis beständig Ej beständig

Kemikalie	Koncentration	Temp.	Beständighet
1,4-Dioxane	100	20 Å°C	
2-Hydroxypropionic acid (lactic acid)	90	20 Å°C	
Acetic acid	100	20 Å°C	
Acetone	100	20 Å°C	
Ammonia	â€	20 Å°C	
Ammonium chloride	â€	20 Å°C	
Amyl alcohol	â€	20 Å°C	
Benzene	â€	20 Å°C	
Bleaching solution	â€	20 Å°C	
Boric acid	100	20 Å°C	
Brake fluid	â€	20 Å°C	
Butyl acetate	â€	20 Å°C	
Calcium chloride	â€	20 Å°C	
Carbon disulphide	100	20 Å°C	
Carbon tetrachloride	â€	20 Å°C	
Chlorine (gas)	100	20 Å°C	
Chlorobenzene	100	20 Å°C	
Chloroform	â€	20 Å°C	
Citric acid	10	20 Å°C	
Cresol	â€	20 Å°C	
Cyclohexanone	100	20 Å°C	
Cyclohexene	100	20 Å°C	
Diesel	â€	20 Å°C	
Diethylene oxide	â€	20 Å°C	
Ethyl acetate	100	20 Å°C	
Ethyl alcohol (ethanol)	96	20 Å°C	
Ethylene chloride	100	20 Å°C	

Kemikalie	Koncentration	Temp.	Besl�ndighet
Food oil	<=	20 Â°C	+
Formaldehyde, aqueous	40	20 Â°C	+
Formic acid	10	20 Â°C	+
Frost protection agent	<=	20 Â°C	+
Fuel oil	<=	20 Â°C	+
Fuel, aromatic free	<=	20 Â°C	+
Glycerine	100	20 Â°C	+
Glycol	100	20 Â°C	+
Heptane	100	20 Â°C	=
Hydrochloric acid	10	20 Â°C	+
Hydrochloric acid (concentrated)	<=	20 Â°C	+
Hydrofluoric acid	40	20 Â°C	+
Hydrogen peroxide	10	20 Â°C	+
Hydrogen sulfide, aqueous	<=	20 Â°C	+
Isopropyl alcohol	100	20 Â°C	+
Linseed oil	<=	20 Â°C	+
Mercurochrome	<=	20 Â°C	+
Methyl alcohol (methanol)	100	20 Â°C	+
Methyl ethyl ketone (MEK)	100	20 Â°C	+
Methylene chloride	100	20 Â°C	=
Milk	<=	20 Â°C	+
Mineral oils (aromatic free)	<=	20 Â°C	+
Nitric acid	50	20 Â°C	-
Nitric acid	10	20 Â°C	+
Nitrobenzene	<=	20 Â°C	+
Oxalic acid	<=	20 Â°C	+
Ozone (gas)	%< 0.5 ppm	20 Â°C	-
Paraffin oil	100	20 Â°C	+
Perchloroethylene	<=	20 Â°C	=
Petroleum ether	100	20 Â°C	+
Phenol, aqueous	ca. 9	20 Â°C	+
Phosphoric acid	50	20 Â°C	+
Potassium hydroxide solution	50	20 Â°C	+
Premium fuel	<=	20 Â°C	+
Propyl alcohol	<=	20 Â°C	+

