



# PP-H 170x2000 mm grÅ¥

Artikelnr P1010070

## 1. Tekniskt datablad

| Egenskap                                   | VÄrde | Enhet   | Standard         |
|--------------------------------------------|-------|---------|------------------|
| Density                                    | 0.91  | g/cm³   | ISO 1183         |
| Tensile Strength                           | 36    | MPa     | ISO 527          |
| Modulus of elasticity (tensile)            | 1700  | MPa     | ISO 527-2        |
| Breakdown Voltage                          | 30    | MPa     | ISO 527          |
| Break Elongation                           | 8     | %       | ISO 527-2        |
| Melting point                              | 161   | °C      | DIN EN ISO 11357 |
| Maximal operating temperature (short-term) | 127   | °C      | UL746B           |
| Maximum Operating Temperature              | 80    | °C      |                  |
| Minimum temperature                        | -7    | °C      |                  |
| Heat deflection temperature (HDT/A)        | 54    | °C      | ISO 75           |
| Heat deflection temperature (HDT/B)        | 90    | °C      | ISO 75           |
| Vicat softening temperature (VST/B/50)     | 50    | °C      | ISO 306          |
| Dielectric Strength                        | 40    | kV/mm   | IEC 60243-1      |
| Volume Resistivity                         | 10¹³  | Ω·cm    | DIN EN 62631-3-1 |
| Dielectric Constant (1 MHz)                | 2.4   | -       | IEC 60250        |
| Dielectric loss factor (1 MHz)             | 13.4  | -       | IEC 60250        |
| Dielectric loss factor (100 Hz)            | 0.0   | -       | IEC 60250        |
| Flammability Classification (UL 94)        | 60695 |         | UL 94            |
| Flexural Strength                          | 37    | MPa     | DIN EN ISO 527-2 |
| Thermal Conductivity                       | 0.27  | W/(m·K) | ISO 22007-4      |
| Surface Resistivity                        | 10¹³  | Ω       | IEC 60093        |
| Comparative Tracking Index (CTI)           | 600   | V       | IEC 60112        |
| Water absorption to saturation             | 0.2   | %       | ISO 62           |
| Water Absorption to Saturation             | 0.2   | %       | ISO 62           |
| Notched impact strength (Charpy)           | 9     | kJ/m²   | ISO 179/1eA      |
| Impact Resistance (Charpy)                 | 7.7   | kJ/m²   | ISO 179          |



| Kemikalie                        | Konc.       | Resultat |
|----------------------------------|-------------|----------|
| Food oil                         | â€™         | ●        |
| Formaldehyde, aqueous            | 40          | ●        |
| Formic acid                      | 10          | ●        |
| Frost protection agent           | â€™         | ●        |
| Fuel oil                         | â€™         | ●        |
| Fuel, aromatic free              | â€™         | ●        |
| Glycerine                        | 100         | ●        |
| Glycol                           | 100         | ●        |
| Heptane                          | 100         | ●        |
| Hydrochloric acid                | 10          | ●        |
| Hydrochloric acid (concentrated) | â€™         | ●        |
| Hydrofluoric acid                | 40          | ●        |
| Hydrogen peroxide                | 10          | ●        |
| Hydrogen sulfide, aqueous        | â€™         | ●        |
| Isopropyl alcohol                | 100         | ●        |
| Linseed oil                      | â€™         | ●        |
| Mercurochrome                    | â€™         | ●        |
| Methyl alcohol (methanol)        | 100         | ●        |
| Methyl ethyl ketone (MEK)        | 100         | ●        |
| Methylene chloride               | 100         | ●        |
| Milk                             | â€™         | ●        |
| Mineral oils (aromatic free)     | â€™         | ●        |
| Nitric acid                      | 10          | ●        |
| Nitric acid                      | 50          | ●        |
| Nitrobenzene                     | â€™         | ●        |
| Oxalic acid                      | â€™         | ●        |
| Ozone (gas)                      | â‰‰ 0.5 ppm | ●        |
| Paraffin oil                     | 100         | ●        |
| Perchloroethylene                | â€™         | ●        |
| Petroleum ether                  | 100         | ●        |
| Phenol, aqueous                  | ca. 9       | ●        |
| Phosphoric acid                  | 50          | ●        |
| Potassium hydroxide solution     | 50          | ●        |
| Premium fuel                     | â€™         | ●        |
| Propyl alcohol                   | â€™         | ●        |

| Kemikalie                                | Konc.  | Resultat |
|------------------------------------------|--------|----------|
| Pyridine                                 | â€”    | ●        |
| Silicone oil                             | â€”    | ●        |
| Sodium carbonate, aqueous                | â€”    | ●        |
| Sodium chloride, aqueous                 | â€”    | ●        |
| Sodium hydrogen sulfite                  | â€”    | ●        |
| Sodium hydroxide solution (caustic soda) | 15     | ●        |
| Sodium hydroxide solution (caustic soda) | 60     | ●        |
| Sodium nitrate, aqueous                  | â€”    | ●        |
| Sodium thiosulfate                       | â€”    | ●        |
| Sulphuric acid                           | 96     | ●        |
| Tetrahydrofuran (THF)                    | 100    | ●        |
| Toluene                                  | 100    | ●        |
| Transformer oil                          | â€”    | ●        |
| Trichloroethylene                        | 100    | ●        |
| Vinegar, standard                        | 5 - 10 | ●        |
| Water                                    | â€”    | ●        |
| Xylene                                   | â€”    | ●        |