



PP-H 75x1000 mm grÅ

Artikelnr P1010018

Beständig

Delvis beständig

Ej beständig

Kemikalie	Koncentration	Temp.	Beständighet
1,4-Dioxane	100	20 Å°C	
2-Hydroxypropionic acid (lactic acid)	90	20 Å°C	
Acetic acid	100	20 Å°C	
Acetone	100	20 Å°C	
Ammonia	â€”	20 Å°C	
Ammonium chloride	â€”	20 Å°C	
Amyl alcohol	â€”	20 Å°C	
Benzene	â€”	20 Å°C	
Bleaching solution	â€”	20 Å°C	
Boric acid	100	20 Å°C	
Brake fluid	â€”	20 Å°C	
Butyl acetate	â€”	20 Å°C	
Calcium chloride	â€”	20 Å°C	
Carbon disulphide	100	20 Å°C	
Carbon tetrachloride	â€”	20 Å°C	
Chlorine (gas)	100	20 Å°C	
Chlorobenzene	100	20 Å°C	
Chloroform	â€”	20 Å°C	
Citric acid	10	20 Å°C	
Cresol	â€”	20 Å°C	
Cyclohexanone	100	20 Å°C	
Cyclohexene	100	20 Å°C	
Diesel	â€”	20 Å°C	
Diethylene oxide	â€”	20 Å°C	
Ethyl acetate	100	20 Å°C	
Ethyl alcohol (ethanol)	96	20 Å°C	
Ethylene chloride	100	20 Å°C	

Kemikalie	Koncentration	Temp.	Best�ndighet
Food oil	����	20 ��C	��
Formaldehyde, aqueous	40	20 ��C	��
Formic acid	10	20 ��C	��
Frost protection agent	����	20 ��C	��
Fuel oil	����	20 ��C	��
Fuel, aromatic free	����	20 ��C	��
Glycerine	100	20 ��C	��
Glycol	100	20 ��C	��
Heptane	100	20 ��C	��
Hydrochloric acid	10	20 ��C	��
Hydrochloric acid (concentrated)	����	20 ��C	��
Hydrofluoric acid	40	20 ��C	��
Hydrogen peroxide	10	20 ��C	��
Hydrogen sulfide, aqueous	����	20 ��C	��
Isopropyl alcohol	100	20 ��C	��
Linseed oil	����	20 ��C	��
Mercurochrome	����	20 ��C	��
Methyl alcohol (methanol)	100	20 ��C	��
Methyl ethyl ketone (MEK)	100	20 ��C	��
Methylene chloride	100	20 ��C	��
Milk	����	20 ��C	��
Mineral oils (aromatic free)	����	20 ��C	��
Nitric acid	50	20 ��C	��
Nitric acid	10	20 ��C	��
Nitrobenzene	����	20 ��C	��
Oxalic acid	����	20 ��C	��
Ozone (gas)	���� 0.5 ppm	20 ��C	��
Paraffin oil	100	20 ��C	��
Perchloroethylene	����	20 ��C	��
Petroleum ether	100	20 ��C	��
Phenol, aqueous	ca. 9	20 ��C	��
Phosphoric acid	50	20 ��C	��
Potassium hydroxide solution	50	20 ��C	��
Premium fuel	����	20 ��C	��
Propyl alcohol	����	20 ��C	��

