



PP-H AlphaPlus 250x1000 mm grÅ

Artikelnr P2201114

Beständig Delvis beständig Ej beständig

Kemikalie	Koncentration	Temp.	Beständighet
1,4-Dioxane	100	20 Å°C	
2-Hydroxypropionic acid (lactic acid)	90	20 Å°C	
Acetic acid	100	20 Å°C	
Acetone	100	20 Å°C	
Ammonia	â€”	20 Å°C	
Ammonium chloride	â€”	20 Å°C	
Amyl alcohol	â€”	20 Å°C	
Benzene	â€”	20 Å°C	
Bleaching solution	â€”	20 Å°C	
Boric acid	100	20 Å°C	
Brake fluid	â€”	20 Å°C	
Butyl acetate	â€”	20 Å°C	
Calcium chloride	â€”	20 Å°C	
Carbon disulphide	100	20 Å°C	
Carbon tetrachloride	â€”	20 Å°C	
Chlorine (gas)	100	20 Å°C	
Chlorobenzene	100	20 Å°C	
Chloroform	â€”	20 Å°C	
Citric acid	10	20 Å°C	
Cresol	â€”	20 Å°C	
Cyclohexanone	100	20 Å°C	
Cyclohexene	100	20 Å°C	
Diesel	â€”	20 Å°C	
Diethylene oxide	â€”	20 Å°C	
Ethyl acetate	100	20 Å°C	
Ethyl alcohol (ethanol)	96	20 Å°C	
Ethylene chloride	100	20 Å°C	

Kemikalie	Koncentration	Temp.	Best�ndighet
Food oil	â€™"	20 Â°C	●
Formaldehyde, aqueous	40	20 Â°C	●
Formic acid	10	20 Â°C	●
Frost protection agent	â€™"	20 Â°C	●
Fuel oil	â€™"	20 Â°C	●
Fuel, aromatic free	â€™"	20 Â°C	●
Glycerine	100	20 Â°C	●
Glycol	100	20 Â°C	●
Heptane	100	20 Â°C	●
Hydrochloric acid	10	20 Â°C	●
Hydrochloric acid (concentrated)	â€™"	20 Â°C	●
Hydrofluoric acid	40	20 Â°C	●
Hydrogen peroxide	10	20 Â°C	●
Hydrogen sulfide, aqueous	â€™"	20 Â°C	●
Isopropyl alcohol	100	20 Â°C	●
Linseed oil	â€™"	20 Â°C	●
Mercurochrome	â€™"	20 Â°C	●
Methyl alcohol (methanol)	100	20 Â°C	●
Methyl ethyl ketone (MEK)	100	20 Â°C	●
Methylene chloride	100	20 Â°C	●
Milk	â€™"	20 Â°C	●
Mineral oils (aromatic free)	â€™"	20 Â°C	●
Nitric acid	50	20 Â°C	●
Nitric acid	10	20 Â°C	●
Nitrobenzene	â€™"	20 Â°C	●
Oxalic acid	â€™"	20 Â°C	●
Ozone (gas)	â%□ 0.5 ppm	20 Â°C	●
Paraffin oil	100	20 Â°C	●
Perchloroethylene	â€™"	20 Â°C	●
Petroleum ether	100	20 Â°C	●
Phenol, aqueous	ca. 9	20 Â°C	●
Phosphoric acid	50	20 Â°C	●
Potassium hydroxide solution	50	20 Â°C	●
Premium fuel	â€™"	20 Â°C	●
Propyl alcohol	â€™"	20 Â°C	●

