



PPS 20x1000 mm svart

Artikelnr P1010400

Beständig Delvis beständig Ej beständig

Kemikalie	Koncentration	Temp.	Beständighet
1,4-Dioxane	100	20 Å°C	Beständig
Acetone	100	20 Å°C	Beständig
Ammonia	â€”	20 Å°C	Beständig
Ammonium chloride	â€”	20 Å°C	Beständig
Benzene	â€”	20 Å°C	Beständig
Brake fluid	â€”	20 Å°C	Beständig
Butyl acetate	â€”	20 Å°C	Beständig
Calcium chloride	â€”	20 Å°C	Beständig
Carbon tetrachloride	â€”	20 Å°C	Beständig
Chlorobenzene	100	20 Å°C	Beständig
Chloroform	â€”	20 Å°C	Beständig
Diesel	â€”	20 Å°C	Beständig
Diethylene oxide	â€”	20 Å°C	Beständig
Ethyl acetate	100	20 Å°C	Beständig
Ethyl alcohol (ethanol)	96	20 Å°C	Beständig
Frost protection agent	â€”	20 Å°C	Beständig
Fuel, aromatic free	â€”	20 Å°C	Beständig
Glycerine	100	20 Å°C	Beständig
Hydrochloric acid (10%)	10	20 Å°C	Beständig
Hydrochloric acid (concentrated)	â€”	20 Å°C	Ej beständig
Isopropyl alcohol	100	20 Å°C	Beständig
Methyl alcohol (methanol)	100	20 Å°C	Beständig
Methyl ethyl ketone (MEK)	100	20 Å°C	Beständig
Methylene chloride	100	20 Å°C	Delvis beständig
Mineral oils (aromatic free)	â€”	20 Å°C	Beständig
Nitric acid (10%)	10	20 Å°C	Beständig
Nitric acid (50%)	50	20 Å°C	Ej beständig

Kemikalie	Koncentration	Temp.	Beständighet
Perchloroethylene	â€”	20 Å°C	●
Phenol, aqueous	9	20 Å°C	●
Phosphoric acid	50	20 Å°C	●
Premium fuel	â€”	20 Å°C	●
Sodium chloride, aqueous	â€”	20 Å°C	●
Sodium hydroxide solution (15%)	15	20 Å°C	●
Sodium hydroxide solution (60%)	60	20 Å°C	●
Sulphuric acid	96	20 Å°C	●
Tetrahydrofuran (THF)	100	20 Å°C	●
Toluene	100	20 Å°C	●
Transformer oil	â€”	20 Å°C	●
Trichloroethylene	100	20 Å°C	●
Water	â€”	20 Å°C	●
Xylene	â€”	20 Å°C	●