

PPS 40x3000 mm natur

Artikelnr P1010781

● Beständig
 ● Delvis beständig
 ● Ej beständig

Kemikalie	Koncentration	Temp.	Beständighet
1,4-Dioxane	100	20 Å°C	●
Acetone	100	20 Å°C	●
Ammonia	â€”	20 Å°C	●
Ammonium chloride	â€”	20 Å°C	●
Benzene	â€”	20 Å°C	●
Brake fluid	â€”	20 Å°C	●
Butyl acetate	â€”	20 Å°C	●
Calcium chloride	â€”	20 Å°C	●
Carbon tetrachloride	â€”	20 Å°C	●
Chlorobenzene	100	20 Å°C	●
Chloroform	â€”	20 Å°C	●
Diesel	â€”	20 Å°C	●
Diethylene oxide	â€”	20 Å°C	●
Ethyl acetate	100	20 Å°C	●
Ethyl alcohol (ethanol)	96	20 Å°C	●
Frost protection agent	â€”	20 Å°C	●
Fuel, aromatic free	â€”	20 Å°C	●
Glycerine	100	20 Å°C	●
Hydrochloric acid (10%)	10	20 Å°C	●
Hydrochloric acid (concentrated)	â€”	20 Å°C	●
Isopropyl alcohol	100	20 Å°C	●
Methyl alcohol (methanol)	100	20 Å°C	●
Methyl ethyl ketone (MEK)	100	20 Å°C	●
Methylene chloride	100	20 Å°C	●
Mineral oils (aromatic free)	â€”	20 Å°C	●
Nitric acid (10%)	10	20 Å°C	●
Nitric acid (50%)	50	20 Å°C	●

Kemikalie	Koncentration	Temp.	Best�ndighet
Perchloroethylene	��	20 �C	●
Phenol, aqueous	9	20 �C	●
Phosphoric acid	50	20 �C	●
Premium fuel	��	20 �C	●
Sodium chloride, aqueous	��	20 �C	●
Sodium hydroxide solution (15%)	15	20 �C	●
Sodium hydroxide solution (60%)	60	20 �C	●
Sulphuric acid	96	20 �C	●
Tetrahydrofuran (THF)	100	20 �C	●
Toluene	100	20 �C	●
Transformer oil	��	20 �C	●
Trichloroethylene	100	20 �C	●
Water	��	20 �C	●
Xylene	��	20 �C	●