



PPS 50x3000 mm svart

Artikelnr P1010411

Best ndig Delvis best ndig Ej best ndig

Kemikalie	Koncentration	Temp.	Best�ndighet
1,4-Dioxane	100	20 �C	Best�ndig
Acetone	100	20 �C	Best�ndig
Ammonia	��	20 �C	Best�ndig
Ammonium chloride	��	20 �C	Best�ndig
Benzene	��	20 �C	Best�ndig
Brake fluid	��	20 �C	Best�ndig
Butyl acetate	��	20 �C	Best�ndig
Calcium chloride	��	20 �C	Best�ndig
Carbon tetrachloride	��	20 �C	Best�ndig
Chlorobenzene	100	20 �C	Best�ndig
Chloroform	��	20 �C	Best�ndig
Diesel	��	20 �C	Best�ndig
Diethylene oxide	��	20 �C	Best�ndig
Ethyl acetate	100	20 �C	Best�ndig
Ethyl alcohol (ethanol)	96	20 �C	Best�ndig
Frost protection agent	��	20 �C	Best�ndig
Fuel, aromatic free	��	20 �C	Best�ndig
Glycerine	100	20 �C	Best�ndig
Hydrochloric acid (10%)	10	20 �C	Best�ndig
Hydrochloric acid (concentrated)	��	20 �C	Ej best�ndig
Isopropyl alcohol	100	20 �C	Best�ndig
Methyl alcohol (methanol)	100	20 �C	Best�ndig
Methyl ethyl ketone (MEK)	100	20 �C	Best�ndig
Methylene chloride	100	20 �C	Delvis best�ndig
Mineral oils (aromatic free)	��	20 �C	Best�ndig
Nitric acid (10%)	10	20 �C	Best�ndig
Nitric acid (50%)	50	20 �C	Ej best�ndig

Kemikalie	Koncentration	Temp.	Beständighet
Perchloroethylene	â€”	20 Å°C	●
Phenol, aqueous	9	20 Å°C	●
Phosphoric acid	50	20 Å°C	●
Premium fuel	â€”	20 Å°C	●
Sodium chloride, aqueous	â€”	20 Å°C	●
Sodium hydroxide solution (15%)	15	20 Å°C	●
Sodium hydroxide solution (60%)	60	20 Å°C	●
Sulphuric acid	96	20 Å°C	●
Tetrahydrofuran (THF)	100	20 Å°C	●
Toluene	100	20 Å°C	●
Transformer oil	â€”	20 Å°C	●
Trichloroethylene	100	20 Å°C	●
Water	â€”	20 Å°C	●
Xylene	â€”	20 Å°C	●